

Proposed 300 GPa HfH₁₀ Structure: A10B_hP22_194_bhj_c-001


This structure previously used the label(s) **A10B_hP22_194_bhj_c**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettl, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/MK58>

https://aflow.org/prototype-encyclopedia/A10B_hP22_194_bhj_c-001



Prototype	H ₁₀ Hf
AFLOW prototype label	A10B_hP22_194_bhj_c-001
Pearson symbol	hP22
Space group number	194
Space group symbol	$P6_3/mmc$
AFLOW prototype command	<code>aflow --proto=A10B_hP22_194_bhj_c-001</code> <code>--params=a, c/a, x₃, x₄, y₄</code>

Other compounds with this structure


LuH₁₀, ScH₁₀, ZrH₁₀

- This structure has only been determined computationally. At 300 GPa it is predicted to have a superconducting transitions temperature T_c above 200K.

Hexagonal primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a \hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{1}{2}a \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a \hat{\mathbf{y}} \\ \mathbf{a}_3 &= c \hat{\mathbf{z}}\end{aligned}$$

$\mathbf{a}_1$ $\mathbf{a}_2$
 $\mathbf{a}_3$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$= \frac{1}{4} \mathbf{a}_3$	$=$	$\frac{1}{4}c \hat{\mathbf{z}}$	(2b)	H I
$\mathbf{B}_2$	$= \frac{3}{4} \mathbf{a}_3$	$=$	$\frac{3}{4}c \hat{\mathbf{z}}$	(2b)	H I
$\mathbf{B}_3$	$= \frac{1}{3} \mathbf{a}_1 + \frac{2}{3} \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(2c)	Hf I
$\mathbf{B}_4$	$= \frac{2}{3} \mathbf{a}_1 + \frac{1}{3} \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(2c)	Hf I
$\mathbf{B}_5$	$= x_3 \mathbf{a}_1 + 2x_3 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$\frac{3}{2}ax_3 \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_3 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(6h)	H II
$\mathbf{B}_6$	$= -2x_3 \mathbf{a}_1 - x_3 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$-\frac{3}{2}ax_3 \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_3 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(6h)	H II
$\mathbf{B}_7$	$= x_3 \mathbf{a}_1 - x_3 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$-\sqrt{3}ax_3 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(6h)	H II
$\mathbf{B}_8$	$= -x_3 \mathbf{a}_1 - 2x_3 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$-\frac{3}{2}ax_3 \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ax_3 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(6h)	H II
$\mathbf{B}_9$	$= 2x_3 \mathbf{a}_1 + x_3 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$\frac{3}{2}ax_3 \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ax_3 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(6h)	H II
$\mathbf{B}_{10}$	$= -x_3 \mathbf{a}_1 + x_3 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$\sqrt{3}ax_3 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(6h)	H II
$\mathbf{B}_{11}$	$= x_4 \mathbf{a}_1 + y_4 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a(x_4 + y_4) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a(x_4 - y_4) \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(12j)	H III
$\mathbf{B}_{12}$	$= -y_4 \mathbf{a}_1 + (x_4 - y_4) \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a(x_4 - 2y_4) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_4 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(12j)	H III
$\mathbf{B}_{13}$	$= -(x_4 - y_4) \mathbf{a}_1 - x_4 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$-\frac{1}{2}a(2x_4 - y_4) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ay_4 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(12j)	H III
$\mathbf{B}_{14}$	$= -x_4 \mathbf{a}_1 - y_4 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$-\frac{1}{2}a(x_4 + y_4) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a(x_4 - y_4) \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(12j)	H III
$\mathbf{B}_{15}$	$= y_4 \mathbf{a}_1 - (x_4 - y_4) \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a(-x_4 + 2y_4) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ax_4 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(12j)	H III
$\mathbf{B}_{16}$	$= (x_4 - y_4) \mathbf{a}_1 + x_4 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a(2x_4 - y_4) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ay_4 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(12j)	H III
$\mathbf{B}_{17}$	$= y_4 \mathbf{a}_1 + x_4 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a(x_4 + y_4) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a(x_4 - y_4) \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(12j)	H III
$\mathbf{B}_{18}$	$= (x_4 - y_4) \mathbf{a}_1 - y_4 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a(x_4 - 2y_4) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ax_4 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(12j)	H III
$\mathbf{B}_{19}$	$= -x_4 \mathbf{a}_1 - (x_4 - y_4) \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$-\frac{1}{2}a(2x_4 - y_4) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ay_4 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(12j)	H III
$\mathbf{B}_{20}$	$= -y_4 \mathbf{a}_1 - x_4 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$-\frac{1}{2}a(x_4 + y_4) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a(x_4 - y_4) \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(12j)	H III
$\mathbf{B}_{21}$	$= -(x_4 - y_4) \mathbf{a}_1 + y_4 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a(-x_4 + 2y_4) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_4 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(12j)	H III
$\mathbf{B}_{22}$	$= x_4 \mathbf{a}_1 + (x_4 - y_4) \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a(2x_4 - y_4) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ay_4 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(12j)	H III

References

- [1] H. Xie, Y. Yao, X. Feng, D. Duan, H. Song, Z. Zhang, S. Jiang, S. A. T. Redfern, V. Z. Kresin, C. J. Pickard, and T. Cui, *Hydrogen Pentagraphenelike Structure Stabilized by Hafnium: A High-Temperature Conventional Superconductor*, Phys. Rev. Lett. **125**, 217001 (2020), doi:10.1103/PhysRevLett.125.217001.

First cited in

D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.