

Ta₃S₂ Structure:

A2B3_oC40_39_2d_2c2d-001


This structure previously used the label(s) **A2B3_oC40_39_2d_2c2d**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/4YG0>

https://aflow.org/prototype-encyclopedia/A2B3_oC40_39_2d_2c2d-001




Prototype	S ₂ Ta ₃
AFLOW prototype label	A2B3_oC40_39_2d_2c2d-001
ICSD	71143
CCDC	1632051
Pearson symbol	oC40
Space group number	39

Space group symbol *Aem*2

AFLOW prototype command `aflow --proto=A2B3_oC40_39_2d_2c2d-001`
`--params=a, b/a, c/a, x1, z1, x2, z2, x3, y3, z3, x4, y4, z4, x5, y5, z5, x6, y6, z6`

Base-centered Orthorhombic primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= a \hat{\mathbf{x}} \\ \mathbf{a}_2 &= \frac{1}{2}b \hat{\mathbf{y}} - \frac{1}{2}c \hat{\mathbf{z}} \\ \mathbf{a}_3 &= \frac{1}{2}b \hat{\mathbf{y}} + \frac{1}{2}c \hat{\mathbf{z}}\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$= x_1 \mathbf{a}_1 - (z_1 - \frac{1}{4}) \mathbf{a}_2 + (z_1 + \frac{1}{4}) \mathbf{a}_3 =$		$ax_1 \hat{\mathbf{x}} + \frac{1}{4}b \hat{\mathbf{y}} + cz_1 \hat{\mathbf{z}}$	(4c)	Ta I
$\mathbf{B}_2$	$= -x_1 \mathbf{a}_1 - (z_1 - \frac{3}{4}) \mathbf{a}_2 + (z_1 + \frac{3}{4}) \mathbf{a}_3 =$		$-ax_1 \hat{\mathbf{x}} + \frac{3}{4}b \hat{\mathbf{y}} + cz_1 \hat{\mathbf{z}}$	(4c)	Ta I
$\mathbf{B}_3$	$= x_2 \mathbf{a}_1 - (z_2 - \frac{1}{4}) \mathbf{a}_2 + (z_2 + \frac{1}{4}) \mathbf{a}_3 =$		$ax_2 \hat{\mathbf{x}} + \frac{1}{4}b \hat{\mathbf{y}} + cz_2 \hat{\mathbf{z}}$	(4c)	Ta II
$\mathbf{B}_4$	$= -x_2 \mathbf{a}_1 - (z_2 - \frac{3}{4}) \mathbf{a}_2 + (z_2 + \frac{3}{4}) \mathbf{a}_3 =$		$-ax_2 \hat{\mathbf{x}} + \frac{3}{4}b \hat{\mathbf{y}} + cz_2 \hat{\mathbf{z}}$	(4c)	Ta II
$\mathbf{B}_5$	$= x_3 \mathbf{a}_1 + (y_3 - z_3) \mathbf{a}_2 + (y_3 + z_3) \mathbf{a}_3 =$		$ax_3 \hat{\mathbf{x}} + by_3 \hat{\mathbf{y}} + cz_3 \hat{\mathbf{z}}$	(8d)	S I
$\mathbf{B}_6$	$= -x_3 \mathbf{a}_1 - (y_3 + z_3) \mathbf{a}_2 - (y_3 - z_3) \mathbf{a}_3 =$		$-ax_3 \hat{\mathbf{x}} - by_3 \hat{\mathbf{y}} + cz_3 \hat{\mathbf{z}}$	(8d)	S I
$\mathbf{B}_7$	$= x_3 \mathbf{a}_1 - (y_3 + z_3 - \frac{1}{2}) \mathbf{a}_2 + (-y_3 + z_3 + \frac{1}{2}) \mathbf{a}_3 =$		$ax_3 \hat{\mathbf{x}} - b(y_3 - \frac{1}{2}) \hat{\mathbf{y}} + cz_3 \hat{\mathbf{z}}$	(8d)	S I
$\mathbf{B}_8$	$= -x_3 \mathbf{a}_1 + (y_3 - z_3 + \frac{1}{2}) \mathbf{a}_2 + (y_3 + z_3 + \frac{1}{2}) \mathbf{a}_3 =$		$-ax_3 \hat{\mathbf{x}} + b(y_3 + \frac{1}{2}) \hat{\mathbf{y}} + cz_3 \hat{\mathbf{z}}$	(8d)	S I
$\mathbf{B}_9$	$= x_4 \mathbf{a}_1 + (y_4 - z_4) \mathbf{a}_2 + (y_4 + z_4) \mathbf{a}_3 =$		$ax_4 \hat{\mathbf{x}} + by_4 \hat{\mathbf{y}} + cz_4 \hat{\mathbf{z}}$	(8d)	S II
$\mathbf{B}_{10}$	$= -x_4 \mathbf{a}_1 - (y_4 + z_4) \mathbf{a}_2 - (y_4 - z_4) \mathbf{a}_3 =$		$-ax_4 \hat{\mathbf{x}} - by_4 \hat{\mathbf{y}} + cz_4 \hat{\mathbf{z}}$	(8d)	S II
$\mathbf{B}_{11}$	$= x_4 \mathbf{a}_1 - (y_4 + z_4 - \frac{1}{2}) \mathbf{a}_2 + (-y_4 + z_4 + \frac{1}{2}) \mathbf{a}_3 =$		$ax_4 \hat{\mathbf{x}} - b(y_4 - \frac{1}{2}) \hat{\mathbf{y}} + cz_4 \hat{\mathbf{z}}$	(8d)	S II
$\mathbf{B}_{12}$	$= -x_4 \mathbf{a}_1 + (y_4 - z_4 + \frac{1}{2}) \mathbf{a}_2 + (y_4 + z_4 + \frac{1}{2}) \mathbf{a}_3 =$		$-ax_4 \hat{\mathbf{x}} + b(y_4 + \frac{1}{2}) \hat{\mathbf{y}} + cz_4 \hat{\mathbf{z}}$	(8d)	S II
$\mathbf{B}_{13}$	$= x_5 \mathbf{a}_1 + (y_5 - z_5) \mathbf{a}_2 + (y_5 + z_5) \mathbf{a}_3 =$		$ax_5 \hat{\mathbf{x}} + by_5 \hat{\mathbf{y}} + cz_5 \hat{\mathbf{z}}$	(8d)	Ta III
$\mathbf{B}_{14}$	$= -x_5 \mathbf{a}_1 - (y_5 + z_5) \mathbf{a}_2 - (y_5 - z_5) \mathbf{a}_3 =$		$-ax_5 \hat{\mathbf{x}} - by_5 \hat{\mathbf{y}} + cz_5 \hat{\mathbf{z}}$	(8d)	Ta III
$\mathbf{B}_{15}$	$= x_5 \mathbf{a}_1 - (y_5 + z_5 - \frac{1}{2}) \mathbf{a}_2 + (-y_5 + z_5 + \frac{1}{2}) \mathbf{a}_3 =$		$ax_5 \hat{\mathbf{x}} - b(y_5 - \frac{1}{2}) \hat{\mathbf{y}} + cz_5 \hat{\mathbf{z}}$	(8d)	Ta III
$\mathbf{B}_{16}$	$= -x_5 \mathbf{a}_1 + (y_5 - z_5 + \frac{1}{2}) \mathbf{a}_2 + (y_5 + z_5 + \frac{1}{2}) \mathbf{a}_3 =$		$-ax_5 \hat{\mathbf{x}} + b(y_5 + \frac{1}{2}) \hat{\mathbf{y}} + cz_5 \hat{\mathbf{z}}$	(8d)	Ta III

$$\mathbf{B}_{17} = x_6 \mathbf{a}_1 + (y_6 - z_6) \mathbf{a}_2 + (y_6 + z_6) \mathbf{a}_3 = ax_6 \hat{\mathbf{x}} + by_6 \hat{\mathbf{y}} + cz_6 \hat{\mathbf{z}} \quad (8d) \quad \text{Ta IV}$$

$$\mathbf{B}_{18} = -x_6 \mathbf{a}_1 - (y_6 + z_6) \mathbf{a}_2 - (y_6 - z_6) \mathbf{a}_3 = -ax_6 \hat{\mathbf{x}} - by_6 \hat{\mathbf{y}} + cz_6 \hat{\mathbf{z}} \quad (8d) \quad \text{Ta IV}$$

$$\mathbf{B}_{19} = x_6 \mathbf{a}_1 - (y_6 + z_6 - \frac{1}{2}) \mathbf{a}_2 + (-y_6 + z_6 + \frac{1}{2}) \mathbf{a}_3 = ax_6 \hat{\mathbf{x}} - b(y_6 - \frac{1}{2}) \hat{\mathbf{y}} + cz_6 \hat{\mathbf{z}} \quad (8d) \quad \text{Ta IV}$$

$$\mathbf{B}_{20} = -x_6 \mathbf{a}_1 + (y_6 - z_6 + \frac{1}{2}) \mathbf{a}_2 + (y_6 + z_6 + \frac{1}{2}) \mathbf{a}_3 = -ax_6 \hat{\mathbf{x}} + b(y_6 + \frac{1}{2}) \hat{\mathbf{y}} + cz_6 \hat{\mathbf{z}} \quad (8d) \quad \text{Ta IV}$$

References

- [1] S. J. Kim, K. S. Nanjundaswamy, and T. Hughbanks, *Single-crystal structure of tantalum sulfide (Ta_3S_2). Structure and bonding in the Ta_6S_n ($n = 1, 3, 4, 5?$) pentagonal-antiprismatic chain compounds*, Inorg. Chem. **30**, 159–164 (1991), doi:10.1021/ic00002a004.

Found in

- [1] P. Villars and K. Cenzual, *Pearson's Crystal Data – Crystal Structure Database for Inorganic Compounds* (2013). ASM International.

First cited in

D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, Comput. Mater. Sci. **161**, S1 (2019). doi: 10.1016/j.commatsci.2018.10.043