

EuFeAs₂ Structure:


A2BC_mP8_11_2e_e_e-001

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettl, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Osés, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/C60C>

https://aflow.org/prototype-encyclopedia/A2BC_mP8_11_2e_e_e-001




Prototype	As ₂ EuFe
AFLOW prototype label	A2BC_mP8_11_2e_e_e-001
ICSD	19708
CCDC	2185125
Pearson symbol	mP8
Space group number	11
Space group symbol	$P2_1/m$
AFLOW prototype command	<code>aflow --proto=A2BC_mP8_11_2e_e_e-001</code> <code>--params=a, b/a, c/a, β, x_1, z_1, x_2, z_2, x_3, z_3, x_4, z_4</code>

- The structure measured by (Yu, 2017) had a composition Eu_{0.87}La_{0.13}FeAs, with the europium and lanthanum atoms sharing the third (2e) site. The lanthanum atom positions are slightly displaced from the europium positions.

Simple Monoclinic primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= a \hat{\mathbf{x}} \\ \mathbf{a}_2 &= b \hat{\mathbf{y}} \\ \mathbf{a}_3 &= c \cos \beta \hat{\mathbf{x}} + c \sin \beta \hat{\mathbf{z}}\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$= x_1 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_1 \mathbf{a}_3$	$=$	$(ax_1 + cz_1 \cos \beta) \hat{\mathbf{x}} + \frac{1}{4}b \hat{\mathbf{y}} + cz_1 \sin \beta \hat{\mathbf{z}}$	(2e)	As I
$\mathbf{B}_2$	$= -x_1 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_1 \mathbf{a}_3$	$=$	$-(ax_1 + cz_1 \cos \beta) \hat{\mathbf{x}} + \frac{3}{4}b \hat{\mathbf{y}} - cz_1 \sin \beta \hat{\mathbf{z}}$	(2e)	As I
$\mathbf{B}_3$	$= x_2 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_2 \mathbf{a}_3$	$=$	$(ax_2 + cz_2 \cos \beta) \hat{\mathbf{x}} + \frac{1}{4}b \hat{\mathbf{y}} + cz_2 \sin \beta \hat{\mathbf{z}}$	(2e)	As II
$\mathbf{B}_4$	$= -x_2 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_2 \mathbf{a}_3$	$=$	$-(ax_2 + cz_2 \cos \beta) \hat{\mathbf{x}} + \frac{3}{4}b \hat{\mathbf{y}} - cz_2 \sin \beta \hat{\mathbf{z}}$	(2e)	As II
$\mathbf{B}_5$	$= x_3 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_3 \mathbf{a}_3$	$=$	$(ax_3 + cz_3 \cos \beta) \hat{\mathbf{x}} + \frac{1}{4}b \hat{\mathbf{y}} + cz_3 \sin \beta \hat{\mathbf{z}}$	(2e)	Eu I
$\mathbf{B}_6$	$= -x_3 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_3 \mathbf{a}_3$	$=$	$-(ax_3 + cz_3 \cos \beta) \hat{\mathbf{x}} + \frac{3}{4}b \hat{\mathbf{y}} - cz_3 \sin \beta \hat{\mathbf{z}}$	(2e)	Eu I
$\mathbf{B}_7$	$= x_4 \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$(ax_4 + cz_4 \cos \beta) \hat{\mathbf{x}} + \frac{1}{4}b \hat{\mathbf{y}} + cz_4 \sin \beta \hat{\mathbf{z}}$	(2e)	Fe I
$\mathbf{B}_8$	$= -x_4 \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_2 - z_4 \mathbf{a}_3$	$=$	$-(ax_4 + cz_4 \cos \beta) \hat{\mathbf{x}} + \frac{3}{4}b \hat{\mathbf{y}} - cz_4 \sin \beta \hat{\mathbf{z}}$	(2e)	Fe I

References

- [1] J. Yu, T. Liu, B.-J. Pan, B.-B. Ruan, X.-C. Wang, Q.-G. Mu, K. Zhao, G.-F. Chen, and Z.-A. Ren, *Discovery of a novel 112-type iron-pnictide and La-doping induced superconductivity in $\text{Eu}_{1-x}\text{La}_x\text{FeAs}_2$ ($x = 0-0.15$)*, Sci. Bull. **62**, 218–221 (2017), doi:10.1016/j.scib.2016.12.015.

First cited in

H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.