

H₂S (90 GPa) Structure: A2B_aP6_2_aei_i-001


This structure previously used the label(s) **A2B_aP6_2_aei_i**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/Q769>

https://aflow.org/prototype-encyclopedia/A2B_aP6_2_aei_i-001




Prototype	H ₂ S
AFLOW prototype label	A2B_aP6_2_aei_i-001
Pearson symbol	aP6
Space group number	2
Space group symbol	$P\bar{1}$
AFLOW prototype command	<code>aflow --proto=A2B_aP6_2_aei_i-001</code> <code>--params=a, b/a, c/a, α, β, γ, x_3, y_3, z_3, x_4, y_4, z_4</code>

- This structure was found by first-principles electronic structure calculations and is predicted to be the stable structure of H₂S in the range 80-140 GPa. The data presented here was computed at 90 GPa.
- (Li, 2014) place the hydrogen atoms on (1g), (1f) and (2i) sites, with sulfur atoms on (2i) sites. We have changed the origin so that the hydrogen atoms are now on (1a), (1e) and (2i) sites.

Triclinic primitive vectors

$$\begin{aligned}
\mathbf{a}_1 &= a \hat{\mathbf{x}} \\
\mathbf{a}_2 &= b \cos \gamma \hat{\mathbf{x}} + b \sin \gamma \hat{\mathbf{y}} \\
\mathbf{a}_3 &= c_x \hat{\mathbf{x}} + c_y \hat{\mathbf{y}} + c_z \hat{\mathbf{z}} \\
c_x &= c \cos \beta \\
c_y &= c(\cos \alpha - \cos \beta \cos \gamma) / \sin \gamma \\
c_z &= \sqrt{c^2 - c_x^2 - c_y^2}
\end{aligned}$$

a1
a2
a3



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	0	$=$	0	(1a)	H I
$\mathbf{B}_2$	$\frac{1}{2} \mathbf{a}_1 + \frac{1}{2} \mathbf{a}_2$	$=$	$\frac{1}{2} (a + b \cos \gamma) \hat{\mathbf{x}} + \frac{1}{2} b \sin \gamma \hat{\mathbf{y}}$	(1e)	H II
$\mathbf{B}_3$	$x_3 \mathbf{a}_1 + y_3 \mathbf{a}_2 + z_3 \mathbf{a}_3$	$=$	$(ax_3 + by_3 \cos \gamma + c_x z_3) \hat{\mathbf{x}} + (by_3 \sin \gamma + c_y z_3) \hat{\mathbf{y}} + c_z z_3 \hat{\mathbf{z}}$	(2i)	H III
$\mathbf{B}_4$	$-x_3 \mathbf{a}_1 - y_3 \mathbf{a}_2 - z_3 \mathbf{a}_3$	$=$	$-(ax_3 + by_3 \cos \gamma + c_x z_3) \hat{\mathbf{x}} - (by_3 \sin \gamma + c_y z_3) \hat{\mathbf{y}} - c_z z_3 \hat{\mathbf{z}}$	(2i)	H III
$\mathbf{B}_5$	$x_4 \mathbf{a}_1 + y_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$(ax_4 + by_4 \cos \gamma + c_x z_4) \hat{\mathbf{x}} + (by_4 \sin \gamma + c_y z_4) \hat{\mathbf{y}} + c_z z_4 \hat{\mathbf{z}}$	(2i)	S I
$\mathbf{B}_6$	$-x_4 \mathbf{a}_1 - y_4 \mathbf{a}_2 - z_4 \mathbf{a}_3$	$=$	$-(ax_4 + by_4 \cos \gamma + c_x z_4) \hat{\mathbf{x}} - (by_4 \sin \gamma + c_y z_4) \hat{\mathbf{y}} - c_z z_4 \hat{\mathbf{z}}$	(2i)	S I

References

- [1] Y. Li, J. Hao, H. Liu, Y. Li, and Y. Ma, *The metallization and superconductivity of dense hydrogen sulfide*, J. Chem. Phys. **140**, 174712 (2014), doi:10.1063/1.4874158.

First cited in

D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, Comput. Mater. Sci. **161**, S1 (2019). doi: 10.1016/j.commatsci.2018.10.043