

SrSi₂ Structure:

A2B_cP12_212_c_a-001


This structure previously used the label(s) **A2B_cP12_212_c_a**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettl, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/XX75>

https://aflow.org/prototype-encyclopedia/A2B_cP12_212_c_a-001



Prototype	Si ₂ Sr
AFLOW prototype label	A2B_cP12_212_c_a-001
ICSD	24145
CCDC	1600194
Pearson symbol	cP12
Space group number	212
Space group symbol	<i>P</i> ₄ 32
AFLOW prototype command	<code>aflow --proto=A2B_cP12_212_c_a-001</code> <code>--params=<i>a</i>, <i>x</i>₂</code>


Other compounds with this structure

BaSi₂, BaSi₄Sr

- This structure may also be found in the enantiomorphic space group *P*₄32 #213.

Simple Cubic primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= a \hat{\mathbf{x}} \\ \mathbf{a}_2 &= a \hat{\mathbf{y}} \\ \mathbf{a}_3 &= a \hat{\mathbf{z}}\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$= \frac{1}{8} \mathbf{a}_1 + \frac{1}{8} \mathbf{a}_2 + \frac{1}{8} \mathbf{a}_3$	$=$	$\frac{1}{8} a \hat{\mathbf{x}} + \frac{1}{8} a \hat{\mathbf{y}} + \frac{1}{8} a \hat{\mathbf{z}}$	(4a)	Sr I
$\mathbf{B}_2$	$= \frac{3}{8} \mathbf{a}_1 + \frac{7}{8} \mathbf{a}_2 + \frac{5}{8} \mathbf{a}_3$	$=$	$\frac{3}{8} a \hat{\mathbf{x}} + \frac{7}{8} a \hat{\mathbf{y}} + \frac{5}{8} a \hat{\mathbf{z}}$	(4a)	Sr I
$\mathbf{B}_3$	$= \frac{7}{8} \mathbf{a}_1 + \frac{5}{8} \mathbf{a}_2 + \frac{3}{8} \mathbf{a}_3$	$=$	$\frac{7}{8} a \hat{\mathbf{x}} + \frac{5}{8} a \hat{\mathbf{y}} + \frac{3}{8} a \hat{\mathbf{z}}$	(4a)	Sr I
$\mathbf{B}_4$	$= \frac{5}{8} \mathbf{a}_1 + \frac{3}{8} \mathbf{a}_2 + \frac{7}{8} \mathbf{a}_3$	$=$	$\frac{5}{8} a \hat{\mathbf{x}} + \frac{3}{8} a \hat{\mathbf{y}} + \frac{7}{8} a \hat{\mathbf{z}}$	(4a)	Sr I
$\mathbf{B}_5$	$= x_2 \mathbf{a}_1 + x_2 \mathbf{a}_2 + x_2 \mathbf{a}_3$	$=$	$a x_2 \hat{\mathbf{x}} + a x_2 \hat{\mathbf{y}} + a x_2 \hat{\mathbf{z}}$	(8c)	Si I
$\mathbf{B}_6$	$= -\left(x_2 - \frac{1}{2}\right) \mathbf{a}_1 - x_2 \mathbf{a}_2 + \left(x_2 + \frac{1}{2}\right) \mathbf{a}_3$	$=$	$-a \left(x_2 - \frac{1}{2}\right) \hat{\mathbf{x}} - a x_2 \hat{\mathbf{y}} + a \left(x_2 + \frac{1}{2}\right) \hat{\mathbf{z}}$	(8c)	Si I
$\mathbf{B}_7$	$= -x_2 \mathbf{a}_1 + \left(x_2 + \frac{1}{2}\right) \mathbf{a}_2 - \left(x_2 - \frac{1}{2}\right) \mathbf{a}_3$	$=$	$-a x_2 \hat{\mathbf{x}} + a \left(x_2 + \frac{1}{2}\right) \hat{\mathbf{y}} - a \left(x_2 - \frac{1}{2}\right) \hat{\mathbf{z}}$	(8c)	Si I
$\mathbf{B}_8$	$= \left(x_2 + \frac{1}{2}\right) \mathbf{a}_1 - \left(x_2 - \frac{1}{2}\right) \mathbf{a}_2 - x_2 \mathbf{a}_3$	$=$	$a \left(x_2 + \frac{1}{2}\right) \hat{\mathbf{x}} - a \left(x_2 - \frac{1}{2}\right) \hat{\mathbf{y}} - a x_2 \hat{\mathbf{z}}$	(8c)	Si I
$\mathbf{B}_9$	$= \left(x_2 + \frac{1}{4}\right) \mathbf{a}_1 + \left(x_2 + \frac{3}{4}\right) \mathbf{a}_2 - \left(x_2 - \frac{3}{4}\right) \mathbf{a}_3$	$=$	$a \left(x_2 + \frac{1}{4}\right) \hat{\mathbf{x}} + a \left(x_2 + \frac{3}{4}\right) \hat{\mathbf{y}} - a \left(x_2 - \frac{3}{4}\right) \hat{\mathbf{z}}$	(8c)	Si I
$\mathbf{B}_{10}$	$= -\left(x_2 - \frac{1}{4}\right) \mathbf{a}_1 - \left(x_2 - \frac{1}{4}\right) \mathbf{a}_2 - \left(x_2 - \frac{1}{4}\right) \mathbf{a}_3$	$=$	$-a \left(x_2 - \frac{1}{4}\right) \hat{\mathbf{x}} - a \left(x_2 - \frac{1}{4}\right) \hat{\mathbf{y}} - a \left(x_2 - \frac{1}{4}\right) \hat{\mathbf{z}}$	(8c)	Si I
$\mathbf{B}_{11}$	$= \left(x_2 + \frac{3}{4}\right) \mathbf{a}_1 - \left(x_2 - \frac{3}{4}\right) \mathbf{a}_2 + \left(x_2 + \frac{1}{4}\right) \mathbf{a}_3$	$=$	$a \left(x_2 + \frac{3}{4}\right) \hat{\mathbf{x}} - a \left(x_2 - \frac{3}{4}\right) \hat{\mathbf{y}} + a \left(x_2 + \frac{1}{4}\right) \hat{\mathbf{z}}$	(8c)	Si I
$\mathbf{B}_{12}$	$= -\left(x_2 - \frac{3}{4}\right) \mathbf{a}_1 + \left(x_2 + \frac{1}{4}\right) \mathbf{a}_2 + \left(x_2 + \frac{3}{4}\right) \mathbf{a}_3$	$=$	$-a \left(x_2 - \frac{3}{4}\right) \hat{\mathbf{x}} + a \left(x_2 + \frac{1}{4}\right) \hat{\mathbf{y}} + a \left(x_2 + \frac{3}{4}\right) \hat{\mathbf{z}}$	(8c)	Si I

References

- [1] K. Janzon, H. Schäfer, and A. Weiss, *Kristallstruktur von Strontiumdisilicid SrSi_2* , Angew. Chem. **77**, 258–259 (1965), doi:10.1002/ange.19650770605.

Found in

- [1] P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1985).

First cited in

D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, Comput. Mater. Sci. **161**, S1 (2019). doi: 10.1016/j.commatsci.2018.10.043