

Cu₂Te (C_h) Structure: A2B_hP6_191_h_e-001


This structure previously used the label(s) **A2B_hP6_191_h_e**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettl, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/X9YK>

https://aflow.org/prototype-encyclopedia/A2B_hP6_191_h_e-001



Prototype	Cu ₂ Te
AFLOW prototype label	A2B_hP6_191_h_e-001
<i>Strukturbericht</i> designation	C_h
ICSD	655706
CCDC	1765882
Pearson symbol	hP6


Space group number 191

Space group symbol $P6/mmm$

AFLOW prototype command `aflow --proto=A2B_hP6_191_h_e-001`
`--params=a, c/a, z1, z2`

Hexagonal primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= \frac{1}{2}a\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a\hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{1}{2}a\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a\hat{\mathbf{y}} \\ \mathbf{a}_3 &= c\hat{\mathbf{z}}\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$= z_1 \mathbf{a}_3$	$=$	$cz_1 \hat{\mathbf{z}}$	(2e)	Te I
$\mathbf{B}_2$	$= -z_1 \mathbf{a}_3$	$=$	$-cz_1 \hat{\mathbf{z}}$	(2e)	Te I
$\mathbf{B}_3$	$= \frac{1}{3} \mathbf{a}_1 + \frac{2}{3} \mathbf{a}_2 + z_2 \mathbf{a}_3$	$=$	$\frac{1}{2}a\hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a\hat{\mathbf{y}} + cz_2 \hat{\mathbf{z}}$	(4h)	Cu I
$\mathbf{B}_4$	$= \frac{2}{3} \mathbf{a}_1 + \frac{1}{3} \mathbf{a}_2 + z_2 \mathbf{a}_3$	$=$	$\frac{1}{2}a\hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a\hat{\mathbf{y}} + cz_2 \hat{\mathbf{z}}$	(4h)	Cu I
$\mathbf{B}_5$	$= \frac{2}{3} \mathbf{a}_1 + \frac{1}{3} \mathbf{a}_2 - z_2 \mathbf{a}_3$	$=$	$\frac{1}{2}a\hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a\hat{\mathbf{y}} - cz_2 \hat{\mathbf{z}}$	(4h)	Cu I
$\mathbf{B}_6$	$= \frac{1}{3} \mathbf{a}_1 + \frac{2}{3} \mathbf{a}_2 - z_2 \mathbf{a}_3$	$=$	$\frac{1}{2}a\hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a\hat{\mathbf{y}} - cz_2 \hat{\mathbf{z}}$	(4h)	Cu I

References

- [1] H. Nowotny, *Die Kristallstruktur von Cu₂Te*, Z. Metallkd. **37**, 40–42 (1946), doi:10.1515/ijmr-1946-371-208.

Found in

- [1] P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OH, 1991), 2nd edn.

First cited in

M. J. Mehl, D. Hicks, C. Toher, O. Levy, R. M. Hanson, G. L. W. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 1*, Comput. Mater. Sci. **136**, S1-828 (2017). doi: 10.1016/j.commatsci.2017.01.017