

β -PdCl₂ Structure: A2B_hR18_148_2f_f-001


This structure previously used the label(s) **A2B_hR18_148_2f_f**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettl, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/8GMP>

https://aflow.org/prototype-encyclopedia/A2B_hR18_148_2f_f-001



Prototype

Cl₂Pd

AFLOW prototype label

A2B_hR18_148_2f_f-001

ICSD


404624

CCDC	1725112
Pearson symbol	hR18
Space group number	148
Space group symbol	$R\bar{3}$
AFLOW prototype command	<code>aflow --proto=A2B_hR18_148_2f_f-001</code> <code>--params=a, c/a, x₁, y₁, z₁, x₂, y₂, z₂, x₃, y₃, z₃</code>

- PdCl₂ is known to exist in four different structures at ambient pressure (Evers, 2010):
 - orthorhombic α -PdCl₂,
 - rhombohedral β -PdCl₂ (this structure),
 - monoclinic γ -PdCl₂, and
 - monoclinic δ -PdCl₂.
- (Dell’Amico, 1996) did the original assessment of the crystal structure of β -PdCl₂, but it is difficult to determine the Wyckoff positions from this paper. We relied on (Villars, 2010) for the Wyckoff positions.

Rhombohedral primitive vectors

$$\begin{aligned}
 \mathbf{a}_1 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} + \frac{1}{3}c \hat{\mathbf{z}} \\
 \mathbf{a}_2 &= \frac{1}{\sqrt{3}}a \hat{\mathbf{y}} + \frac{1}{3}c \hat{\mathbf{z}} \\
 \mathbf{a}_3 &= -\frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} + \frac{1}{3}c \hat{\mathbf{z}}
 \end{aligned}$$



Basis vectors

	Lattice coordinates	Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$x_1 \mathbf{a}_1 + y_1 \mathbf{a}_2 + z_1 \mathbf{a}_3$	$= \frac{1}{2}a (x_1 - z_1) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a (x_1 - 2y_1 + z_1) \hat{\mathbf{y}} + \frac{1}{3}c (x_1 + y_1 + z_1) \hat{\mathbf{z}}$	(6f)	Cl I
$\mathbf{B}_2$	$z_1 \mathbf{a}_1 + x_1 \mathbf{a}_2 + y_1 \mathbf{a}_3$	$= -\frac{1}{2}a (y_1 - z_1) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a (2x_1 - y_1 - z_1) \hat{\mathbf{y}} + \frac{1}{3}c (x_1 + y_1 + z_1) \hat{\mathbf{z}}$	(6f)	Cl I
$\mathbf{B}_3$	$y_1 \mathbf{a}_1 + z_1 \mathbf{a}_2 + x_1 \mathbf{a}_3$	$= -\frac{1}{2}a (x_1 - y_1) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a (x_1 + y_1 - 2z_1) \hat{\mathbf{y}} + \frac{1}{3}c (x_1 + y_1 + z_1) \hat{\mathbf{z}}$	(6f)	Cl I
$\mathbf{B}_4$	$-x_1 \mathbf{a}_1 - y_1 \mathbf{a}_2 - z_1 \mathbf{a}_3$	$= -\frac{1}{2}a (x_1 - z_1) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a (x_1 - 2y_1 + z_1) \hat{\mathbf{y}} - \frac{1}{3}c (x_1 + y_1 + z_1) \hat{\mathbf{z}}$	(6f)	Cl I
$\mathbf{B}_5$	$-z_1 \mathbf{a}_1 - x_1 \mathbf{a}_2 - y_1 \mathbf{a}_3$	$= \frac{1}{2}a (y_1 - z_1) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a (2x_1 - y_1 - z_1) \hat{\mathbf{y}} - \frac{1}{3}c (x_1 + y_1 + z_1) \hat{\mathbf{z}}$	(6f)	Cl I
$\mathbf{B}_6$	$-y_1 \mathbf{a}_1 - z_1 \mathbf{a}_2 - x_1 \mathbf{a}_3$	$= \frac{1}{2}a (x_1 - y_1) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a (x_1 + y_1 - 2z_1) \hat{\mathbf{y}} - \frac{1}{3}c (x_1 + y_1 + z_1) \hat{\mathbf{z}}$	(6f)	Cl I
$\mathbf{B}_7$	$x_2 \mathbf{a}_1 + y_2 \mathbf{a}_2 + z_2 \mathbf{a}_3$	$= \frac{1}{2}a (x_2 - z_2) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a (x_2 - 2y_2 + z_2) \hat{\mathbf{y}} + \frac{1}{3}c (x_2 + y_2 + z_2) \hat{\mathbf{z}}$	(6f)	Cl II
$\mathbf{B}_8$	$z_2 \mathbf{a}_1 + x_2 \mathbf{a}_2 + y_2 \mathbf{a}_3$	$= -\frac{1}{2}a (y_2 - z_2) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a (2x_2 - y_2 - z_2) \hat{\mathbf{y}} + \frac{1}{3}c (x_2 + y_2 + z_2) \hat{\mathbf{z}}$	(6f)	Cl II

$$\begin{aligned}
\mathbf{B}_9 &= y_2 \mathbf{a}_1 + z_2 \mathbf{a}_2 + x_2 \mathbf{a}_3 &= -\frac{1}{2}a(x_2 - y_2) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a(x_2 + y_2 - 2z_2) \hat{\mathbf{y}} + \frac{1}{3}c(x_2 + y_2 + z_2) \hat{\mathbf{z}} &(6f) &\text{Cl II} \\
\mathbf{B}_{10} &= -x_2 \mathbf{a}_1 - y_2 \mathbf{a}_2 - z_2 \mathbf{a}_3 &= -\frac{1}{2}a(x_2 - z_2) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a(x_2 - 2y_2 + z_2) \hat{\mathbf{y}} - \frac{1}{3}c(x_2 + y_2 + z_2) \hat{\mathbf{z}} &(6f) &\text{Cl II} \\
\mathbf{B}_{11} &= -z_2 \mathbf{a}_1 - x_2 \mathbf{a}_2 - y_2 \mathbf{a}_3 &= \frac{1}{2}a(y_2 - z_2) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a(2x_2 - y_2 - z_2) \hat{\mathbf{y}} - \frac{1}{3}c(x_2 + y_2 + z_2) \hat{\mathbf{z}} &(6f) &\text{Cl II} \\
\mathbf{B}_{12} &= -y_2 \mathbf{a}_1 - z_2 \mathbf{a}_2 - x_2 \mathbf{a}_3 &= \frac{1}{2}a(x_2 - y_2) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a(x_2 + y_2 - 2z_2) \hat{\mathbf{y}} - \frac{1}{3}c(x_2 + y_2 + z_2) \hat{\mathbf{z}} &(6f) &\text{Cl II} \\
\mathbf{B}_{13} &= x_3 \mathbf{a}_1 + y_3 \mathbf{a}_2 + z_3 \mathbf{a}_3 &= \frac{1}{2}a(x_3 - z_3) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a(x_3 - 2y_3 + z_3) \hat{\mathbf{y}} + \frac{1}{3}c(x_3 + y_3 + z_3) \hat{\mathbf{z}} &(6f) &\text{Pd I} \\
\mathbf{B}_{14} &= z_3 \mathbf{a}_1 + x_3 \mathbf{a}_2 + y_3 \mathbf{a}_3 &= -\frac{1}{2}a(y_3 - z_3) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a(2x_3 - y_3 - z_3) \hat{\mathbf{y}} + \frac{1}{3}c(x_3 + y_3 + z_3) \hat{\mathbf{z}} &(6f) &\text{Pd I} \\
\mathbf{B}_{15} &= y_3 \mathbf{a}_1 + z_3 \mathbf{a}_2 + x_3 \mathbf{a}_3 &= -\frac{1}{2}a(x_3 - y_3) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a(x_3 + y_3 - 2z_3) \hat{\mathbf{y}} + \frac{1}{3}c(x_3 + y_3 + z_3) \hat{\mathbf{z}} &(6f) &\text{Pd I} \\
\mathbf{B}_{16} &= -x_3 \mathbf{a}_1 - y_3 \mathbf{a}_2 - z_3 \mathbf{a}_3 &= -\frac{1}{2}a(x_3 - z_3) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a(x_3 - 2y_3 + z_3) \hat{\mathbf{y}} - \frac{1}{3}c(x_3 + y_3 + z_3) \hat{\mathbf{z}} &(6f) &\text{Pd I} \\
\mathbf{B}_{17} &= -z_3 \mathbf{a}_1 - x_3 \mathbf{a}_2 - y_3 \mathbf{a}_3 &= \frac{1}{2}a(y_3 - z_3) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a(2x_3 - y_3 - z_3) \hat{\mathbf{y}} - \frac{1}{3}c(x_3 + y_3 + z_3) \hat{\mathbf{z}} &(6f) &\text{Pd I} \\
\mathbf{B}_{18} &= -y_3 \mathbf{a}_1 - z_3 \mathbf{a}_2 - x_3 \mathbf{a}_3 &= \frac{1}{2}a(x_3 - y_3) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a(x_3 + y_3 - 2z_3) \hat{\mathbf{y}} - \frac{1}{3}c(x_3 + y_3 + z_3) \hat{\mathbf{z}} &(6f) &\text{Pd I}
\end{aligned}$$

References

- [1] D. B. Dell’Amico, F. Calderazzo, F. Marchetti, and S. Ramello, *Molecular Structure of $[Pd_6Cl_{12}]$ in Single Crystals Chemically Grown at Room Temperature*, Angew. Chem. Int. Ed. **35**, 1131–1133 (1996), doi:10.1002/anie.199613311.
- [2] J. Evers, W. Beck, M. Göbel, S. Jakob, P. Mayer, G. Oehlinger, M. Rotter, and T. Klapötke, *The Structures of δ - $PdCl_2$ and γ - $PdCl_2$: Phases with Negative Thermal Expansion in One Direction*, Angew. Chem. Int. Ed. **49**, 5677–5682 (2010), doi:10.1002/anie.201000680.
- [3] P. Villars and K. Cenzual, eds., *Structure Types* (Springer, Berlin, Heidelberg, 2010), *Landolt-Börnstein – Group III Condensed Matter*, vol. 43A8, chap. Part 8: SpaceGroups (156) P3m1 – (148) R-3, doi:10.1007/978-3-540-70892-6_423.

First cited in

D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, Comput. Mater. Sci. **161**, S1 (2019). doi: 10.1016/j.commatsci.2018.10.043