

# NbAs<sub>2</sub> Structure:

## A2B\_mC12\_5\_2c\_c-001


This structure previously used the label(s) **A2B\_mC12\_5\_2c\_c**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettl, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/0898>

[https://aflow.org/prototype-encyclopedia/A2B\\_mC12\\_5\\_2c\\_c-001](https://aflow.org/prototype-encyclopedia/A2B_mC12_5_2c_c-001)



|                         |                                                                                                                                                                                                                                                                           |
|-------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Prototype               | As <sub>2</sub> Nb                                                                                                                                                                                                                                                        |
| AFLOW prototype label   | A2B_mC12_5_2c_c-001                                                                                                                                                                                                                                                       |
| ICSD                    | 18143                                                                                                                                                                                                                                                                     |
| CCDC                    | 1597699                                                                                                                                                                                                                                                                   |
| Pearson symbol          | mC12                                                                                                                                                                                                                                                                      |
| Space group number      | 5                                                                                                                                                                                                                                                                         |
| Space group symbol      | <i>C</i> 2                                                                                                                                                                                                                                                                |
| AFLOW prototype command | <code>aflow --proto=A2B_mC12_5_2c_c-001</code><br><code>--params=a, b/a, c/a, <math>\beta</math>, <math>x_1</math>, <math>y_1</math>, <math>z_1</math>, <math>x_2</math>, <math>y_2</math>, <math>z_2</math>, <math>x_3</math>, <math>y_3</math>, <math>z_3</math></code> |

### Other compounds with this structure

MoAs<sub>2</sub>, TaAs<sub>2</sub>, NbSb<sub>2</sub>, TaSb<sub>2</sub>

- The zero of the *y*-axis can be chosen arbitrarily in space group *C*2 #5. Here we choose it so that  $y_3 = \frac{1}{2}$  for the niobium atom.

### Base-centered Monoclinic primitive vectors

$$\begin{aligned}
\mathbf{a}_1 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{1}{2}b \hat{\mathbf{y}} \\
\mathbf{a}_2 &= \frac{1}{2}a \hat{\mathbf{x}} + \frac{1}{2}b \hat{\mathbf{y}} \\
\mathbf{a}_3 &= c \cos \beta \hat{\mathbf{x}} + c \sin \beta \hat{\mathbf{z}}
\end{aligned}$$



## Basis vectors

|                | Lattice<br>coordinates                                                    |     | Cartesian<br>coordinates                                                                                | Wyckoff<br>position | Atom<br>type |
|----------------|---------------------------------------------------------------------------|-----|---------------------------------------------------------------------------------------------------------|---------------------|--------------|
| $\mathbf{B}_1$ | $(x_1 - y_1) \mathbf{a}_1 + (x_1 + y_1) \mathbf{a}_2 + z_1 \mathbf{a}_3$  | $=$ | $(ax_1 + cz_1 \cos \beta) \hat{\mathbf{x}} + by_1 \hat{\mathbf{y}} + cz_1 \sin \beta \hat{\mathbf{z}}$  | (4c)                | As I         |
| $\mathbf{B}_2$ | $-(x_1 + y_1) \mathbf{a}_1 - (x_1 - y_1) \mathbf{a}_2 - z_1 \mathbf{a}_3$ | $=$ | $-(ax_1 + cz_1 \cos \beta) \hat{\mathbf{x}} + by_1 \hat{\mathbf{y}} - cz_1 \sin \beta \hat{\mathbf{z}}$ | (4c)                | As I         |
| $\mathbf{B}_3$ | $(x_2 - y_2) \mathbf{a}_1 + (x_2 + y_2) \mathbf{a}_2 + z_2 \mathbf{a}_3$  | $=$ | $(ax_2 + cz_2 \cos \beta) \hat{\mathbf{x}} + by_2 \hat{\mathbf{y}} + cz_2 \sin \beta \hat{\mathbf{z}}$  | (4c)                | As II        |
| $\mathbf{B}_4$ | $-(x_2 + y_2) \mathbf{a}_1 - (x_2 - y_2) \mathbf{a}_2 - z_2 \mathbf{a}_3$ | $=$ | $-(ax_2 + cz_2 \cos \beta) \hat{\mathbf{x}} + by_2 \hat{\mathbf{y}} - cz_2 \sin \beta \hat{\mathbf{z}}$ | (4c)                | As II        |
| $\mathbf{B}_5$ | $(x_3 - y_3) \mathbf{a}_1 + (x_3 + y_3) \mathbf{a}_2 + z_3 \mathbf{a}_3$  | $=$ | $(ax_3 + cz_3 \cos \beta) \hat{\mathbf{x}} + by_3 \hat{\mathbf{y}} + cz_3 \sin \beta \hat{\mathbf{z}}$  | (4c)                | Nb I         |
| $\mathbf{B}_6$ | $-(x_3 + y_3) \mathbf{a}_1 - (x_3 - y_3) \mathbf{a}_2 - z_3 \mathbf{a}_3$ | $=$ | $-(ax_3 + cz_3 \cos \beta) \hat{\mathbf{x}} + by_3 \hat{\mathbf{y}} - cz_3 \sin \beta \hat{\mathbf{z}}$ | (4c)                | Nb I         |

## References

- [1] S. Furuseth and A. Kjeeshus, *The Crystal Structures of NbAs<sub>2</sub> and NbSb<sub>2</sub>*, Acta Cryst. **18**, 320–324 (1965), doi:10.1107/S0365110X65000750.

## First cited in

D. Hicks, M. J. Mehl, M. Esters, C. Osos, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.