

CdAs₂ Structure:

A2B_tI12_98_f_a-001


This structure previously used the label(s) **A2B_tI12_98_f_a**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettl, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/G4QQ>

https://aflow.org/prototype-encyclopedia/A2B_tI12_98_f_a-001




Prototype	As ₂ Cd
AFLOW prototype label	A2B_tI12_98_f_a-001
ICSD	609931
CCDC	1743785
Pearson symbol	tI12
Space group number	98
Space group symbol	I4 ₁ 22
AFLOW prototype command	<code>aflow --proto=A2B_tI12_98_f_a-001</code> <code>--params=a, c/a, x₂</code>

Other compounds with this structure

CdAs_{2-x}P_x

Body-centered Tetragonal primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= -\frac{1}{2}a \hat{\mathbf{x}} + \frac{1}{2}a \hat{\mathbf{y}} + \frac{1}{2}c \hat{\mathbf{z}} \\ \mathbf{a}_2 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{1}{2}a \hat{\mathbf{y}} + \frac{1}{2}c \hat{\mathbf{z}} \\ \mathbf{a}_3 &= \frac{1}{2}a \hat{\mathbf{x}} + \frac{1}{2}a \hat{\mathbf{y}} - \frac{1}{2}c \hat{\mathbf{z}}\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	=	0	=	0	(4a) Cd I
$\mathbf{B}_2$	=	$\frac{3}{4} \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	=	$\frac{1}{2}a \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(4a) Cd I
$\mathbf{B}_3$	=	$\frac{3}{8} \mathbf{a}_1 + (x_2 + \frac{1}{8}) \mathbf{a}_2 + (x_2 + \frac{1}{4}) \mathbf{a}_3$	=	$ax_2 \hat{\mathbf{x}} + \frac{1}{4}a \hat{\mathbf{y}} + \frac{1}{8}c \hat{\mathbf{z}}$	(8f) As I
$\mathbf{B}_4$	=	$\frac{7}{8} \mathbf{a}_1 - (x_2 - \frac{1}{8}) \mathbf{a}_2 - (x_2 - \frac{3}{4}) \mathbf{a}_3$	=	$-ax_2 \hat{\mathbf{x}} + \frac{3}{4}a \hat{\mathbf{y}} + \frac{1}{8}c \hat{\mathbf{z}}$	(8f) As I
$\mathbf{B}_5$	=	$(x_2 + \frac{7}{8}) \mathbf{a}_1 + \frac{1}{8} \mathbf{a}_2 + (x_2 + \frac{1}{4}) \mathbf{a}_3$	=	$-\frac{1}{4}a \hat{\mathbf{x}} + a(x_2 + \frac{1}{2}) \hat{\mathbf{y}} + \frac{3}{8}c \hat{\mathbf{z}}$	(8f) As I
$\mathbf{B}_6$	=	$-(x_2 - \frac{7}{8}) \mathbf{a}_1 + \frac{5}{8} \mathbf{a}_2 - (x_2 - \frac{3}{4}) \mathbf{a}_3$	=	$\frac{1}{4}a \hat{\mathbf{x}} - a(x_2 - \frac{1}{2}) \hat{\mathbf{y}} + \frac{3}{8}c \hat{\mathbf{z}}$	(8f) As I

References

- [1] V. A. Rubtsov, E. M. Smolarenko, V. M. Trukhan, V. N. Yakimovich, and L. K. Orlik, *Phase diagram of the CdP₂-CdAs₂ system*, Phys. Stat. Solidi A **115**, K155–K158 (1989), doi:10.1002/pssa.2211150238.
- [2] V. N. Yakimovich, V. A. Rubtsov, and V. M. Trukhan, *Phase Relationships in the CdP₄-ZnP₂-CdAs₂-ZnAs₂ System*, Inorg. Mater. **32**, 579–582 (1996).

Found in

- [1] P. Villars and K. Cenzual, *Pearson's Crystal Data – Crystal Structure Database for Inorganic Compounds* (2013). ASM International.

First cited in

D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, Comput. Mater. Sci. **161**, S1 (2019). doi: 10.1016/j.commatsci.2018.10.043