

TlFe₃Te₃ Structure: A3B3C_hP14_176_h_h_c-001


This structure previously used the label(s) **A3B3C_hP14_176_h_h_c**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/BQR4>

https://aflow.org/prototype-encyclopedia/A3B3C_hP14_176_h_h_c-001



Prototype	Fe ₃ Te ₃ Tl
AFLOW prototype label	A3B3C_hP14_176_h_h_c-001
ICSD	100352
CCDC	1659494
Pearson symbol	hP14
Space group number	176


Space group symbol $P6_3/m$

AFLOW prototype command `aflow --proto=A3B3C_hP14_176_h_h_c-001`
`--params=a, c/a, x2, y2, x3, y3`

Other compounds with this structure

CrSr₃N₃, CsMo₃Te₃, InMo₃Se₃, InMo₃Te₃, KMo₃Se₃, KMo₃Te₃, NaMo₃Se₃, RbMo₃Te₃, TiMo₃Se₃, TiMo₃Te₃

Hexagonal primitive vectors

$$\begin{aligned} \mathbf{a}_1 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a \hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{1}{2}a \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a \hat{\mathbf{y}} \\ \mathbf{a}_3 &= c \hat{\mathbf{z}} \end{aligned}$$


Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$= \frac{1}{3} \mathbf{a}_1 + \frac{2}{3} \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(2c)	Tl I
$\mathbf{B}_2$	$= \frac{2}{3} \mathbf{a}_1 + \frac{1}{3} \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(2c)	Tl I
$\mathbf{B}_3$	$= x_2 \mathbf{a}_1 + y_2 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a (x_2 + y_2) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a (x_2 - y_2) \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(6h)	Fe I
$\mathbf{B}_4$	$= -y_2 \mathbf{a}_1 + (x_2 - y_2) \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a (x_2 - 2y_2) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a x_2 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(6h)	Fe I
$\mathbf{B}_5$	$= -(x_2 - y_2) \mathbf{a}_1 - x_2 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$-\frac{1}{2}a (2x_2 - y_2) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a y_2 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(6h)	Fe I
$\mathbf{B}_6$	$= -x_2 \mathbf{a}_1 - y_2 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$-\frac{1}{2}a (x_2 + y_2) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a (x_2 - y_2) \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(6h)	Fe I
$\mathbf{B}_7$	$= y_2 \mathbf{a}_1 - (x_2 - y_2) \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a (-x_2 + 2y_2) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a x_2 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(6h)	Fe I
$\mathbf{B}_8$	$= (x_2 - y_2) \mathbf{a}_1 + x_2 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a (2x_2 - y_2) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a y_2 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(6h)	Fe I
$\mathbf{B}_9$	$= x_3 \mathbf{a}_1 + y_3 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a (x_3 + y_3) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a (x_3 - y_3) \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(6h)	Te I
$\mathbf{B}_{10}$	$= -y_3 \mathbf{a}_1 + (x_3 - y_3) \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a (x_3 - 2y_3) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a x_3 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(6h)	Te I
$\mathbf{B}_{11}$	$= -(x_3 - y_3) \mathbf{a}_1 - x_3 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$-\frac{1}{2}a (2x_3 - y_3) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a y_3 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(6h)	Te I
$\mathbf{B}_{12}$	$= -x_3 \mathbf{a}_1 - y_3 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$-\frac{1}{2}a (x_3 + y_3) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a (x_3 - y_3) \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(6h)	Te I
$\mathbf{B}_{13}$	$= y_3 \mathbf{a}_1 - (x_3 - y_3) \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a (-x_3 + 2y_3) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a x_3 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(6h)	Te I
$\mathbf{B}_{14}$	$= (x_3 - y_3) \mathbf{a}_1 + x_3 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a (2x_3 - y_3) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a y_3 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(6h)	Te I

References

[1] K. Klepp and H. Boller, *Die Kristallstruktur von TlFe₃Te₃*, Mh. Chem. **110**, 667–684 (1979), doi:10.1007/BF00938371.

First cited in

D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, Comput. Mater. Sci. **161**, S1 (2019). doi: 10.1016/j.commatsci.2018.10.043