

# Ag<sub>3</sub>(PO<sub>4</sub>) (*H*2<sub>1</sub>) Structure: A3B4C\_cP16\_218\_c\_e\_a-001


This structure previously used the label(s) **A3B4C\_cP16\_218\_c\_e\_a**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/X143>


[https://aflow.org/prototype-encyclopedia/A3B4C\\_cP16\\_218\\_c\\_e\\_a-001](https://aflow.org/prototype-encyclopedia/A3B4C_cP16_218_c_e_a-001)



|                                    |                                                                                                             |
|------------------------------------|-------------------------------------------------------------------------------------------------------------|
| Prototype                          | Ag <sub>3</sub> O <sub>4</sub> P                                                                            |
| AFLOW prototype label              | A3B4C_cP16_218_c_e_a-001                                                                                    |
| <i>Strukturbericht</i> designation | <i>H</i> 2 <sub>1</sub>                                                                                     |
| ICSD                               | 14000                                                                                                       |
| CCDC                               | 1595415                                                                                                     |
| Pearson symbol                     | cP16                                                                                                        |
| Space group number                 | 218                                                                                                         |
| Space group symbol                 | <i>P</i> $\bar{4}3n$                                                                                        |
| AFLOW prototype command            | <code>aflow --proto=A3B4C_cP16_218_c_e_a-001</code><br><code>--params=<i>a</i>, <i>x</i><sub>3</sub></code> |

Simple Cubic primitive vectors

$$\begin{aligned}
\mathbf{a}_1 &= a \hat{\mathbf{x}} \\
\mathbf{a}_2 &= a \hat{\mathbf{y}} \\
\mathbf{a}_3 &= a \hat{\mathbf{z}}
\end{aligned}$$



## Basis vectors

|                   | Lattice<br>coordinates |                                                                                                           | Cartesian<br>coordinates | Wyckoff<br>position                                                                                                      | Atom<br>type |
|-------------------|------------------------|-----------------------------------------------------------------------------------------------------------|--------------------------|--------------------------------------------------------------------------------------------------------------------------|--------------|
| $\mathbf{B}_1$    | $=$                    | $0$                                                                                                       | $=$                      | $0$                                                                                                                      | (2a) P I     |
| $\mathbf{B}_2$    | $=$                    | $\frac{1}{2} \mathbf{a}_1 + \frac{1}{2} \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$                          | $=$                      | $\frac{1}{2} a \hat{\mathbf{x}} + \frac{1}{2} a \hat{\mathbf{y}} + \frac{1}{2} a \hat{\mathbf{z}}$                       | (2a) P I     |
| $\mathbf{B}_3$    | $=$                    | $\frac{1}{4} \mathbf{a}_1 + \frac{1}{2} \mathbf{a}_2$                                                     | $=$                      | $\frac{1}{4} a \hat{\mathbf{x}} + \frac{1}{2} a \hat{\mathbf{y}}$                                                        | (6c) Ag I    |
| $\mathbf{B}_4$    | $=$                    | $\frac{3}{4} \mathbf{a}_1 + \frac{1}{2} \mathbf{a}_2$                                                     | $=$                      | $\frac{3}{4} a \hat{\mathbf{x}} + \frac{1}{2} a \hat{\mathbf{y}}$                                                        | (6c) Ag I    |
| $\mathbf{B}_5$    | $=$                    | $\frac{1}{4} \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$                                                     | $=$                      | $\frac{1}{4} a \hat{\mathbf{y}} + \frac{1}{2} a \hat{\mathbf{z}}$                                                        | (6c) Ag I    |
| $\mathbf{B}_6$    | $=$                    | $\frac{3}{4} \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$                                                     | $=$                      | $\frac{3}{4} a \hat{\mathbf{y}} + \frac{1}{2} a \hat{\mathbf{z}}$                                                        | (6c) Ag I    |
| $\mathbf{B}_7$    | $=$                    | $\frac{1}{2} \mathbf{a}_1 + \frac{1}{4} \mathbf{a}_3$                                                     | $=$                      | $\frac{1}{2} a \hat{\mathbf{x}} + \frac{1}{4} a \hat{\mathbf{z}}$                                                        | (6c) Ag I    |
| $\mathbf{B}_8$    | $=$                    | $\frac{1}{2} \mathbf{a}_1 + \frac{3}{4} \mathbf{a}_3$                                                     | $=$                      | $\frac{1}{2} a \hat{\mathbf{x}} + \frac{3}{4} a \hat{\mathbf{z}}$                                                        | (6c) Ag I    |
| $\mathbf{B}_9$    | $=$                    | $x_3 \mathbf{a}_1 + x_3 \mathbf{a}_2 + x_3 \mathbf{a}_3$                                                  | $=$                      | $ax_3 \hat{\mathbf{x}} + ax_3 \hat{\mathbf{y}} + ax_3 \hat{\mathbf{z}}$                                                  | (8e) O I     |
| $\mathbf{B}_{10}$ | $=$                    | $-x_3 \mathbf{a}_1 - x_3 \mathbf{a}_2 + x_3 \mathbf{a}_3$                                                 | $=$                      | $-ax_3 \hat{\mathbf{x}} - ax_3 \hat{\mathbf{y}} + ax_3 \hat{\mathbf{z}}$                                                 | (8e) O I     |
| $\mathbf{B}_{11}$ | $=$                    | $-x_3 \mathbf{a}_1 + x_3 \mathbf{a}_2 - x_3 \mathbf{a}_3$                                                 | $=$                      | $-ax_3 \hat{\mathbf{x}} + ax_3 \hat{\mathbf{y}} - ax_3 \hat{\mathbf{z}}$                                                 | (8e) O I     |
| $\mathbf{B}_{12}$ | $=$                    | $x_3 \mathbf{a}_1 - x_3 \mathbf{a}_2 - x_3 \mathbf{a}_3$                                                  | $=$                      | $ax_3 \hat{\mathbf{x}} - ax_3 \hat{\mathbf{y}} - ax_3 \hat{\mathbf{z}}$                                                  | (8e) O I     |
| $\mathbf{B}_{13}$ | $=$                    | $(x_3 + \frac{1}{2}) \mathbf{a}_1 + (x_3 + \frac{1}{2}) \mathbf{a}_2 + (x_3 + \frac{1}{2}) \mathbf{a}_3$  | $=$                      | $a(x_3 + \frac{1}{2}) \hat{\mathbf{x}} + a(x_3 + \frac{1}{2}) \hat{\mathbf{y}} + a(x_3 + \frac{1}{2}) \hat{\mathbf{z}}$  | (8e) O I     |
| $\mathbf{B}_{14}$ | $=$                    | $-(x_3 - \frac{1}{2}) \mathbf{a}_1 - (x_3 - \frac{1}{2}) \mathbf{a}_2 + (x_3 + \frac{1}{2}) \mathbf{a}_3$ | $=$                      | $-a(x_3 - \frac{1}{2}) \hat{\mathbf{x}} - a(x_3 - \frac{1}{2}) \hat{\mathbf{y}} + a(x_3 + \frac{1}{2}) \hat{\mathbf{z}}$ | (8e) O I     |
| $\mathbf{B}_{15}$ | $=$                    | $(x_3 + \frac{1}{2}) \mathbf{a}_1 - (x_3 - \frac{1}{2}) \mathbf{a}_2 - (x_3 - \frac{1}{2}) \mathbf{a}_3$  | $=$                      | $a(x_3 + \frac{1}{2}) \hat{\mathbf{x}} - a(x_3 - \frac{1}{2}) \hat{\mathbf{y}} - a(x_3 - \frac{1}{2}) \hat{\mathbf{z}}$  | (8e) O I     |
| $\mathbf{B}_{16}$ | $=$                    | $-(x_3 - \frac{1}{2}) \mathbf{a}_1 + (x_3 + \frac{1}{2}) \mathbf{a}_2 - (x_3 - \frac{1}{2}) \mathbf{a}_3$ | $=$                      | $-a(x_3 - \frac{1}{2}) \hat{\mathbf{x}} + a(x_3 + \frac{1}{2}) \hat{\mathbf{y}} - a(x_3 - \frac{1}{2}) \hat{\mathbf{z}}$ | (8e) O I     |

## References

- [1] R. Masse, I. Tordjman, and A. Durif, *Affinement de la structure cristalline du monophosphate d'argent  $\text{Ag}_3\text{PO}_4$ . Existence d'une forme haute température*, Z. Kristallogr. **144**, 76–81 (1976), doi:10.1524/zkri.1976.144.16.76.

## Found in

- [1] P. Villars and K. Cenzual, *Pearson's Crystal Data – Crystal Structure Database for Inorganic Compounds* (2013). ASM International.

## First cited in

- D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, Comput. Mater. Sci. **161**, S1 (2019). doi: 10.1016/j.commatsci.2018.10.043