

W₅Si₃ (*D*8_{*m*}) Structure: A3B5_tI32_140_ah_bk-001


This structure previously used the label(s) **A3B5_tI32_140_ah_bk**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/4K4U>

https://aflow.org/prototype-encyclopedia/A3B5_tI32_140_ah_bk-001



Prototype	Si ₃ W ₅
AFLOW prototype label	A3B5_tI32_140_ah_bk-001
<i>Strukturbericht</i> designation	<i>D</i> 8 _{<i>m</i>}
ICSD	73331
CCDC	1634141
Pearson symbol	tI32
Space group number	140
Space group symbol	<i>I</i> 4/ <i>mcm</i>
AFLOW prototype command	<code>aflow --proto=A3B5_tI32_140_ah_bk-001</code> <code>--params=<i>a</i>, <i>c/a</i>, <i>x</i>₃, <i>x</i>₄, <i>y</i>₄</code>

Other compounds with this structure

Cr_5Ge_3 , Cr_5Si_3 , Mo_5Si_3 , Nb_5Si_3 , Ta_5Si_3 , Ti_5Ga_3 , V_5Si_3 , Ti_3Sb , $\text{Hf}_5\text{Co}_{1-x}\text{Sb}_{2+x}$, $\text{Hf}_5\text{Cr}_{1-x}\text{Sb}_{2+x}$, $\text{Hf}_5\text{Cu}_{1-x}\text{Sb}_{2+x}$, $\text{Hf}_5\text{Fe}_{1-x}\text{Sb}_{2+x}$, $\text{Hf}_5\text{Ni}_{1-x}\text{Sb}_{2+x}$, $\text{Hf}_5\text{Pd}_{1-x}\text{Sb}_{2+x}$, $\text{Hf}_5\text{Rh}_{1-x}\text{Sb}_{2+x}$, $\text{Hf}_5\text{Ru}_{1-x}\text{Sb}_{2+x}$, $\text{Hf}_5\text{V}_{1-x}\text{Sb}_{2+x}$, $\text{Zr}_5\text{Co}_{0.5}\text{Sb}_{2.5}$, $\text{Zr}_5\text{Cr}_{1-x}\text{Bi}_{2+x}$, $\text{Zr}_5\text{Cr}_{1-x}\text{Sb}_{2+x}$, $\text{Zr}_5\text{Fe}_{0.5}\text{Sb}_{2.5}$, $\text{Zr}_5\text{Mn}_{1-x}\text{Bi}_{2+x}$, $\text{Zr}_5\text{Mn}_{1-x}\text{Sb}_{2+x}$, $\text{Zr}_5\text{Ni}_{0.5}\text{Sb}_{2.5}$, $\text{Zr}_5\text{Rh}_{0.5}\text{Sb}_{2.5}$, $\text{Zr}_5\text{Ru}_{0.5}\text{Sb}_{2.5}$


- (Pearson, 1958) refers to this as the “T1 phase.”
- Removing the atoms from the (4b) site transforms this into the $D2_c$ U_6Mn structure or the V_4SiSb_2 structure.

Body-centered Tetragonal primitive vectors

$$\mathbf{a}_1 = -\frac{1}{2}a\hat{\mathbf{x}} + \frac{1}{2}a\hat{\mathbf{y}} + \frac{1}{2}c\hat{\mathbf{z}}$$

$$\mathbf{a}_2 = \frac{1}{2}a\hat{\mathbf{x}} - \frac{1}{2}a\hat{\mathbf{y}} + \frac{1}{2}c\hat{\mathbf{z}}$$

$$\mathbf{a}_3 = \frac{1}{2}a\hat{\mathbf{x}} + \frac{1}{2}a\hat{\mathbf{y}} - \frac{1}{2}c\hat{\mathbf{z}}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$= \frac{1}{4}\mathbf{a}_1 + \frac{1}{4}\mathbf{a}_2$	$=$	$\frac{1}{4}c\hat{\mathbf{z}}$	(4a)	Si I
$\mathbf{B}_2$	$= \frac{3}{4}\mathbf{a}_1 + \frac{3}{4}\mathbf{a}_2$	$=$	$\frac{3}{4}c\hat{\mathbf{z}}$	(4a)	Si I
$\mathbf{B}_3$	$= \frac{3}{4}\mathbf{a}_1 + \frac{1}{4}\mathbf{a}_2 + \frac{1}{2}\mathbf{a}_3$	$=$	$\frac{1}{2}a\hat{\mathbf{y}} + \frac{1}{4}c\hat{\mathbf{z}}$	(4b)	W I
$\mathbf{B}_4$	$= \frac{1}{4}\mathbf{a}_1 + \frac{3}{4}\mathbf{a}_2 + \frac{1}{2}\mathbf{a}_3$	$=$	$\frac{1}{2}a\hat{\mathbf{x}} + \frac{1}{4}c\hat{\mathbf{z}}$	(4b)	W I
$\mathbf{B}_5$	$= (x_3 + \frac{1}{2})\mathbf{a}_1 + x_3\mathbf{a}_2 + (2x_3 + \frac{1}{2})\mathbf{a}_3$	$=$	$ax_3\hat{\mathbf{x}} + a(x_3 + \frac{1}{2})\hat{\mathbf{y}}$	(8h)	Si II
$\mathbf{B}_6$	$= -(x_3 - \frac{1}{2})\mathbf{a}_1 - x_3\mathbf{a}_2 - (2x_3 - \frac{1}{2})\mathbf{a}_3$	$=$	$-ax_3\hat{\mathbf{x}} - a(x_3 - \frac{1}{2})\hat{\mathbf{y}}$	(8h)	Si II
$\mathbf{B}_7$	$= x_3\mathbf{a}_1 - (x_3 - \frac{1}{2})\mathbf{a}_2 + \frac{1}{2}\mathbf{a}_3$	$=$	$-a(x_3 - \frac{1}{2})\hat{\mathbf{x}} + ax_3\hat{\mathbf{y}}$	(8h)	Si II
$\mathbf{B}_8$	$= -x_3\mathbf{a}_1 + (x_3 + \frac{1}{2})\mathbf{a}_2 + \frac{1}{2}\mathbf{a}_3$	$=$	$a(x_3 + \frac{1}{2})\hat{\mathbf{x}} - ax_3\hat{\mathbf{y}}$	(8h)	Si II
$\mathbf{B}_9$	$= y_4\mathbf{a}_1 + x_4\mathbf{a}_2 + (x_4 + y_4)\mathbf{a}_3$	$=$	$ax_4\hat{\mathbf{x}} + ay_4\hat{\mathbf{y}}$	(16k)	W II
$\mathbf{B}_{10}$	$= -y_4\mathbf{a}_1 - x_4\mathbf{a}_2 - (x_4 + y_4)\mathbf{a}_3$	$=$	$-ax_4\hat{\mathbf{x}} - ay_4\hat{\mathbf{y}}$	(16k)	W II
$\mathbf{B}_{11}$	$= x_4\mathbf{a}_1 - y_4\mathbf{a}_2 + (x_4 - y_4)\mathbf{a}_3$	$=$	$-ay_4\hat{\mathbf{x}} + ax_4\hat{\mathbf{y}}$	(16k)	W II
$\mathbf{B}_{12}$	$= -x_4\mathbf{a}_1 + y_4\mathbf{a}_2 - (x_4 - y_4)\mathbf{a}_3$	$=$	$ay_4\hat{\mathbf{x}} - ax_4\hat{\mathbf{y}}$	(16k)	W II
$\mathbf{B}_{13}$	$= (y_4 + \frac{1}{2})\mathbf{a}_1 - (x_4 - \frac{1}{2})\mathbf{a}_2 - (x_4 - y_4)\mathbf{a}_3$	$=$	$-ax_4\hat{\mathbf{x}} + ay_4\hat{\mathbf{y}} + \frac{1}{2}c\hat{\mathbf{z}}$	(16k)	W II
$\mathbf{B}_{14}$	$= -(y_4 - \frac{1}{2})\mathbf{a}_1 + (x_4 + \frac{1}{2})\mathbf{a}_2 + (x_4 - y_4)\mathbf{a}_3$	$=$	$ax_4\hat{\mathbf{x}} - ay_4\hat{\mathbf{y}} + \frac{1}{2}c\hat{\mathbf{z}}$	(16k)	W II
$\mathbf{B}_{15}$	$= (x_4 + \frac{1}{2})\mathbf{a}_1 + (y_4 + \frac{1}{2})\mathbf{a}_2 + (x_4 + y_4)\mathbf{a}_3$	$=$	$ay_4\hat{\mathbf{x}} + ax_4\hat{\mathbf{y}} + \frac{1}{2}c\hat{\mathbf{z}}$	(16k)	W II
$\mathbf{B}_{16}$	$= -(x_4 - \frac{1}{2})\mathbf{a}_1 - (y_4 - \frac{1}{2})\mathbf{a}_2 - (x_4 + y_4)\mathbf{a}_3$	$=$	$-ay_4\hat{\mathbf{x}} - ax_4\hat{\mathbf{y}} + \frac{1}{2}c\hat{\mathbf{z}}$	(16k)	W II

References

- [1] B. Aronsson, *The Crystal Structure of Mo_5Si_3 and W_5Si_3* , Acta Chem. Scand. **9**, 1107–1110 (1955), doi:10.3891/acta.chem.scand.09-1107.

Found in

- [1] W. B. Pearson, *A Handbook of Lattice Spacings and Structures of Metals and Alloys, International Series of Monographs on Metal Physics and Physical Metallurgy*, vol. 4 (Pergamon Press, Oxford, London, Edinburgh, New York, Paris, Frankfurt, 1958), 1964 reprint with corrections edn.

First cited in

D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, Comput. Mater. Sci. **161**, S1 (2019). doi: 10.1016/j.commatsci.2018.10.043