

RbGa₃ Structure:

A3B_tI24_119_a2i_bf-001


This structure previously used the label(s) **A3B_tI24_119_b2i_af**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/6TQK>

https://aflow.org/prototype-encyclopedia/A3B_tI24_119_a2i_bf-001




Prototype	Ga ₃ Rb
AFLOW prototype label	A3B_tI24_119_a2i_bf-001
ICSD	103943
CCDC	1661873
Pearson symbol	tI24
Space group number	119
Space group symbol	$I\bar{4}m2$
AFLOW prototype command	<code>aflow --proto=A3B_tI24_119_a2i_bf-001</code> <code>--params=a, c/a, z₃, x₄, z₄, x₅, z₅</code>

Other compounds with this structure

CsGa₃, KGa₃

Body-centered Tetragonal primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= -\frac{1}{2}a\hat{\mathbf{x}} + \frac{1}{2}a\hat{\mathbf{y}} + \frac{1}{2}c\hat{\mathbf{z}} \\ \mathbf{a}_2 &= \frac{1}{2}a\hat{\mathbf{x}} - \frac{1}{2}a\hat{\mathbf{y}} + \frac{1}{2}c\hat{\mathbf{z}} \\ \mathbf{a}_3 &= \frac{1}{2}a\hat{\mathbf{x}} + \frac{1}{2}a\hat{\mathbf{y}} - \frac{1}{2}c\hat{\mathbf{z}}\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$=$	0	$=$	0	Ga I
$\mathbf{B}_2$	$=$	$\frac{1}{2}\mathbf{a}_1 + \frac{1}{2}\mathbf{a}_2$	$=$	$\frac{1}{2}c\hat{\mathbf{z}}$	Rb I
$\mathbf{B}_3$	$=$	$(z_3 + \frac{1}{2})\mathbf{a}_1 + z_3\mathbf{a}_2 + \frac{1}{2}\mathbf{a}_3$	$=$	$\frac{1}{2}a\hat{\mathbf{y}} + cz_3\hat{\mathbf{z}}$	Rb II
$\mathbf{B}_4$	$=$	$-z_3\mathbf{a}_1 - (z_3 - \frac{1}{2})\mathbf{a}_2 + \frac{1}{2}\mathbf{a}_3$	$=$	$\frac{1}{2}a\hat{\mathbf{x}} - cz_3\hat{\mathbf{z}}$	Rb II
$\mathbf{B}_5$	$=$	$z_4\mathbf{a}_1 + (x_4 + z_4)\mathbf{a}_2 + x_4\mathbf{a}_3$	$=$	$ax_4\hat{\mathbf{x}} + cz_4\hat{\mathbf{z}}$	Ga II
$\mathbf{B}_6$	$=$	$z_4\mathbf{a}_1 - (x_4 - z_4)\mathbf{a}_2 - x_4\mathbf{a}_3$	$=$	$-ax_4\hat{\mathbf{x}} + cz_4\hat{\mathbf{z}}$	Ga II
$\mathbf{B}_7$	$=$	$-(x_4 + z_4)\mathbf{a}_1 - z_4\mathbf{a}_2 - x_4\mathbf{a}_3$	$=$	$-ax_4\hat{\mathbf{y}} - cz_4\hat{\mathbf{z}}$	Ga II
$\mathbf{B}_8$	$=$	$(x_4 - z_4)\mathbf{a}_1 - z_4\mathbf{a}_2 + x_4\mathbf{a}_3$	$=$	$ax_4\hat{\mathbf{y}} - cz_4\hat{\mathbf{z}}$	Ga II
$\mathbf{B}_9$	$=$	$z_5\mathbf{a}_1 + (x_5 + z_5)\mathbf{a}_2 + x_5\mathbf{a}_3$	$=$	$ax_5\hat{\mathbf{x}} + cz_5\hat{\mathbf{z}}$	Ga III
$\mathbf{B}_{10}$	$=$	$z_5\mathbf{a}_1 - (x_5 - z_5)\mathbf{a}_2 - x_5\mathbf{a}_3$	$=$	$-ax_5\hat{\mathbf{x}} + cz_5\hat{\mathbf{z}}$	Ga III
$\mathbf{B}_{11}$	$=$	$-(x_5 + z_5)\mathbf{a}_1 - z_5\mathbf{a}_2 - x_5\mathbf{a}_3$	$=$	$-ax_5\hat{\mathbf{y}} - cz_5\hat{\mathbf{z}}$	Ga III
$\mathbf{B}_{12}$	$=$	$(x_5 - z_5)\mathbf{a}_1 - z_5\mathbf{a}_2 + x_5\mathbf{a}_3$	$=$	$ax_5\hat{\mathbf{y}} - cz_5\hat{\mathbf{z}}$	Ga III

References

- [1] R. G. Ling and C. Berlin, *Preparation and Crystal Structure Determination of the New Intermetallic Compound RbGa₃*, Z. Anorganische und Allgemeine Chemie **480**, 181–185 (1981), doi:10.1002/zaac.19814800923.

Found in

- [1] P. Villars and L. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (ASM International, Materials Park, OK, 1991), vol. III, chap. , p. 3545.

First cited in

D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, Comput. Mater. Sci. **161**, S1 (2019). doi: 10.1016/j.commatsci.2018.10.043