Th_3P_4 ($D7_3$) Structure: A4B3_cI28_220_c_a-001

This structure previously used the label(s) `A4B3_cI28_220_c_a`. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

---

https://aflow.org/prototype-encyclopedia/JM9C

https://aflow.org/prototype-encyclopedia/A4B3_cI28_220_c_a-001



Prototype	P_4Th_3
AFLOW prototype label	A4B3_cI28_220_c_a-001
***Strukturbericht* designation**	$D7_3$
ICSD	648207
CCDC	1763101
Pearson symbol	cI28
Space group number	220
Space group symbol	$I\bar{4}3d$
AFLOW prototype command	`aflow --proto=A4B3_cI28_220_c_a-001 --params=`a, x_2

Other compounds with this structure

Bi_3Yb_4, Ce_3S_4, Ce_3Se_4, Ce_3Te_4, Eu_3S_4, La_3S_4, La_3Se_4, La_3Te_4, N_3P_4, Nd_3S_4, Nd_3Se_4, Nd_3Te_4, Pa_3As_4, Pa_3P_4, Pa_3Sb_4, Pr_3S_4, Pr_3Se_4, Pr_3Te_4, Sm_3S_4, Sm_3Se_4, Sm_3Te_4, Th_3As_4, Th_3As_4, Th_3Bi_4, Th_3P_4, Th_3Sb_4, U_3As_4, U_3Bi_4, U_3P_4, U_3Sb_4, U_3Te_4, $BaCe_2S_4$, $BaCe_2Se_4$, $BaLa_2S_4$, $BaLa_2Se_4$, $BaNd_2S_4$, $BaNd_2Se_4$, $BaPr_2S_4$, $BaPr_2Se_4$, $CaCe_2S_4$, $CaDy_2S_4$, $CaGd_2S_4$, $CaLa_2S_4$, $CaNd_2S_4$, $CaPr_2S_4$, $CaSm_2S_4$, $CaTb_2S_4$, $SrCe_2S_4$, $SrCe_2Se_4$, $SrGd_2S_4$, $SrGd_2Se_4$, $SrLa_2S_4$, $SrLa_2Se_4$, $SrNd_2S_4$, $SrNd_2Se_4$, $SrPr_2S_4$, $SrPr_2Se_4$, $SrSm_2S_4$, $SrSm_2Se_4$, Ac_2S_3, Am_2S_3, Ce_2S_3, Ce_2Te_3, Gd_2S_3, La_2S_3, La_2Te_3, Nd_2S_3, Nd_2Te_3, Pr_2S_3, Pr_2Te_3, Sm_2S_3, Sm_2Te_3, Tb_2S_3

- The Th_3P_4 structure allows a large degree of disorder in the thorium (12a) site. Compounds of the form AB_2C_4 have the A and B atoms mixed on the (12a) site (Flahaut, 1965). Compounds of the form A_2B_3 should more properly be listed as $A_{3-x}B_4$, with x in the range [0,1/3] and a corresponding number of vacancies distributed statistically on the (12a) site (Zachariasen, 1949).

Body-centered Cubic primitive vectors

$$\mathbf{a_1} = -\tfrac{1}{2}a\,\hat{\mathbf{x}} + \tfrac{1}{2}a\,\hat{\mathbf{y}} + \tfrac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a_2} = \tfrac{1}{2}a\,\hat{\mathbf{x}} - \tfrac{1}{2}a\,\hat{\mathbf{y}} + \tfrac{1}{2}a\,\hat{\mathbf{z}}$$
$$\mathbf{a_3} = \tfrac{1}{2}a\,\hat{\mathbf{x}} + \tfrac{1}{2}a\,\hat{\mathbf{y}} - \tfrac{1}{2}a\,\hat{\mathbf{z}}$$



Basis vectors

		Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B_1}$	=	$\frac{1}{4}\,\mathbf{a}_1 + \frac{5}{8}\,\mathbf{a}_2 + \frac{3}{8}\,\mathbf{a}_3$	=	$\frac{3}{8}a\,\hat{\mathbf{x}} + \frac{1}{4}a\,\hat{\mathbf{z}}$	(12a)	Th I
$\mathbf{B_2}$	=	$\frac{3}{4}\,\mathbf{a}_1 + \frac{7}{8}\,\mathbf{a}_2 + \frac{1}{8}\,\mathbf{a}_3$	=	$\frac{1}{8}a\,\hat{\mathbf{x}} + \frac{3}{4}a\,\hat{\mathbf{z}}$	(12a)	Th I
$\mathbf{B_3}$	=	$\frac{3}{8}\,\mathbf{a}_1 + \frac{1}{4}\,\mathbf{a}_2 + \frac{5}{8}\,\mathbf{a}_3$	=	$\frac{1}{4}a\,\hat{\mathbf{x}} + \frac{3}{8}a\,\hat{\mathbf{y}}$	(12a)	Th I
$\mathbf{B_4}$	=	$\frac{1}{8}\,\mathbf{a}_1 + \frac{3}{4}\,\mathbf{a}_2 + \frac{7}{8}\,\mathbf{a}_3$	=	$\frac{3}{4}a\,\hat{\mathbf{x}} + \frac{1}{8}a\,\hat{\mathbf{y}}$	(12a)	Th I
$\mathbf{B_5}$	=	$\frac{5}{8}\,\mathbf{a}_1 + \frac{3}{8}\,\mathbf{a}_2 + \frac{1}{4}\,\mathbf{a}_3$	=	$\frac{1}{4}a\,\hat{\mathbf{y}} + \frac{3}{8}a\,\hat{\mathbf{z}}$	(12a)	Th I
$\mathbf{B_6}$	=	$\frac{7}{8}\,\mathbf{a}_1 + \frac{1}{8}\,\mathbf{a}_2 + \frac{3}{4}\,\mathbf{a}_3$	=	$\frac{3}{4}a\,\hat{\mathbf{y}} + \frac{1}{8}a\,\hat{\mathbf{z}}$	(12a)	Th I
$\mathbf{B_7}$	=	$2x_2\,\mathbf{a}_1 + 2x_2\,\mathbf{a}_2 + 2x_2\,\mathbf{a}_3$	=	$ax_2\,\hat{\mathbf{x}} + ax_2\,\hat{\mathbf{y}} + ax_2\,\hat{\mathbf{z}}$	(16c)	P I
$\mathbf{B_8}$	=	$\frac{1}{2}\,\mathbf{a}_1 - \left(2x_2 - \frac{1}{2}\right)\,\mathbf{a}_3$	=	$-ax_2\,\hat{\mathbf{x}} - a\left(x_2 - \frac{1}{2}\right)\,\hat{\mathbf{y}} + ax_2\,\hat{\mathbf{z}}$	(16c)	P I
$\mathbf{B_9}$	=	$-\left(2x_2 - \frac{1}{2}\right)\,\mathbf{a}_2 + \frac{1}{2}\,\mathbf{a}_3$	=	$-a\left(x_2 - \frac{1}{2}\right)\,\hat{\mathbf{x}} + ax_2\,\hat{\mathbf{y}} - ax_2\,\hat{\mathbf{z}}$	(16c)	P I
$\mathbf{B_{10}}$	=	$-\left(2x_2 - \frac{1}{2}\right)\,\mathbf{a}_1 + \frac{1}{2}\,\mathbf{a}_2$	=	$ax_2\,\hat{\mathbf{x}} - ax_2\,\hat{\mathbf{y}} - a\left(x_2 - \frac{1}{2}\right)\,\hat{\mathbf{z}}$	(16c)	P I
$\mathbf{B_{11}}$	=	$\left(2x_2 + \frac{1}{2}\right)\,\mathbf{a}_1 + \left(2x_2 + \frac{1}{2}\right)\,\mathbf{a}_2 + \left(2x_2 + \frac{1}{2}\right)\,\mathbf{a}_3$	=	$a\left(x_2 + \frac{1}{4}\right)\,\hat{\mathbf{x}} + a\left(x_2 + \frac{1}{4}\right)\,\hat{\mathbf{y}} + a\left(x_2 + \frac{1}{4}\right)\,\hat{\mathbf{z}}$	(16c)	P I
$\mathbf{B_{12}}$	=	$\frac{1}{2}\,\mathbf{a}_1 - 2x_2\,\mathbf{a}_3$	=	$-a\left(x_2 + \frac{1}{4}\right)\,\hat{\mathbf{x}} - a\left(x_2 - \frac{1}{4}\right)\,\hat{\mathbf{y}} + a\left(x_2 + \frac{1}{4}\right)\,\hat{\mathbf{z}}$	(16c)	P I
$\mathbf{B_{13}}$	=	$-2x_2\,\mathbf{a}_1 + \frac{1}{2}\,\mathbf{a}_2$	=	$a\left(x_2 + \frac{1}{4}\right)\,\hat{\mathbf{x}} - a\left(x_2 + \frac{1}{4}\right)\,\hat{\mathbf{y}} - a\left(x_2 - \frac{1}{4}\right)\,\hat{\mathbf{z}}$	(16c)	P I
$\mathbf{B_{14}}$	=	$-2x_2\,\mathbf{a}_2 + \frac{1}{2}\,\mathbf{a}_3$	=	$-a\left(x_2 - \frac{1}{4}\right)\,\hat{\mathbf{x}} + a\left(x_2 + \frac{1}{4}\right)\,\hat{\mathbf{y}} - a\left(x_2 + \frac{1}{4}\right)\,\hat{\mathbf{z}}$	(16c)	P I

References

[1] K. Meisel, *Kristallstrukturen von Thoriumphosphiden*, Z. Anorganische und Allgemeine Chemie **240**, 300–312 (1939), doi:10.1002/zaac.19392400403.

[2] J. Flahaut, M. Guittard, M. Patrie, M. P. Pardo, S. M. Golabi, and L. Domange, *Phase cubiques type Th_3P_4 dans les sulfures, les séléniures et les tellurures L_2X_3 et L_3X_4 des terres rares, et dans leurs combinaisons ML_2X_4 avec les sulfures et séléniures MX de calcium, strontium et baryum. Formation et propriétés cristallines*, Acta Cryst. **19**, 14–19 (1965), doi:10.1107/S0365110X65002694.

[3] W. H. Zachariasen, *Crystal chemical studies of the 5f-series of elements. VI. The Ce_2S_3-Ce_3S_4 type of structure*, Acta Cryst. **2**, 57–60 (1949), doi:10.1107/S0365110X49000126.

First cited in

D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, Comput. Mater. Sci. **161**, S1 (2019). doi: 10.1016/j.commatsci.2018.10.043