

Erroneous $L'1_0$ Structure: A4B_cP5_221_bc_a-001


This structure previously used the label(s) **A4B_cP5_221_bc_a**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/Q52R>

https://aflow.org/prototype-encyclopedia/A4B_cP5_221_bc_a-001




Prototype	Fe ₄ N
AFLOW prototype label	A4B_cP5_221_bc_a-001
<i>Strukturbericht</i> designation	$L'1_0$
Pearson symbol	cP5
Space group number	221
Space group symbol	$Pm\bar{3}m$
AFLOW prototype command	<code>aflow --proto=A4B_cP5_221_bc_a-001 --params=a</code>

- We (Hicks, 2019) accidentally misplaced the nickel atom in the $L'1_0$ structure. The correct structure can be found at γ' -Fe₄N $L'1_0$ page.
- Despite our error, this is a binary form of the cubic perovskite structure (AB₃C_cP5_221_a_c_b), *Strukturbericht* designation $E2_1$.

Simple Cubic primitive vectors

a₁
a₂
a₃

$$\begin{aligned}\mathbf{a}_1 &= a \hat{\mathbf{x}} \\ \mathbf{a}_2 &= a \hat{\mathbf{y}} \\ \mathbf{a}_3 &= a \hat{\mathbf{z}}\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	=	0	=	0	N I
$\mathbf{B}_2$	=	$\frac{1}{2} \mathbf{a}_1 + \frac{1}{2} \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	=	$\frac{1}{2}a \hat{\mathbf{x}} + \frac{1}{2}a \hat{\mathbf{y}} + \frac{1}{2}a \hat{\mathbf{z}}$	(1b) Fe I
$\mathbf{B}_3$	=	$\frac{1}{2} \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	=	$\frac{1}{2}a \hat{\mathbf{y}} + \frac{1}{2}a \hat{\mathbf{z}}$	(3c) Fe II
$\mathbf{B}_4$	=	$\frac{1}{2} \mathbf{a}_1 + \frac{1}{2} \mathbf{a}_3$	=	$\frac{1}{2}a \hat{\mathbf{x}} + \frac{1}{2}a \hat{\mathbf{z}}$	(3c) Fe II
$\mathbf{B}_5$	=	$\frac{1}{2} \mathbf{a}_1 + \frac{1}{2} \mathbf{a}_2$	=	$\frac{1}{2}a \hat{\mathbf{x}} + \frac{1}{2}a \hat{\mathbf{y}}$	(3c) Fe II

References

- [1] H. Jacobs, R. Rechenbach, and U. Zachwieja, *Structure determination of γ' -Fe₄N and ϵ -Fe₃Na*, J. Alloys Compd. **227**, 10–17 (1995), doi:10.1016/0925-8388(95)01610-4.
- [2] D. Hicks, M. J.Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi:10.1016/j.commatsci.2021.110450.

First cited in

D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.