

Ta₅Ti₁₁ (BCC SQS-16) Structure: A5B11_mP16_6_2abc_2a3b3c-001


This structure previously used the label(s) **A5B11_mP16_6_2abc_2a3b3c**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/EUM5>

https://aflow.org/prototype-encyclopedia/A5B11_mP16_6_2abc_2a3b3c-001




Prototype	Ta ₅ Ti ₁₁
AFLOW prototype label	A5B11_mP16_6_2abc_2a3b3c-001
Pearson symbol	mP16
Space group number	6
Space group symbol	<i>Pm</i>
AFLOW prototype command	<pre>aflow --proto=A5B11_mP16_6_2abc_2a3b3c-001 --params=a,b/a,c/a,β,x₁,z₁,x₂,z₂,x₃,z₃,x₄,z₄,x₅,z₅,x₆,z₆,x₇,z₇,x₈,z₈,x₉,y₉,z₉, x₁₀,y₁₀,z₁₀,x₁₁,y₁₁,z₁₁,x₁₂,y₁₂,z₁₂</pre>

- This is a special quasirandom structure with 16 atoms per unit cell (SQS-16) for a bcc binary substitutional alloy A_xB_{1-x} (Jiang, 2004; Chakraborty, 2016)).
- Several compositions are available:
 - TaTi₇ (AB7_hR16_166_c.c2h),
 - Ta₃Ti₁₃ (A3B13_oC32_38_ac.a2bcdef),

- TaTi₃-I (AB3_mC32_8_4a_12a) ,
- TaTi₃-II (AB3_mC32_8_4a_4a4b),
- Ta₅Ti₁₁ (A5B11_mP16_6_2abc_2a3b3c) (this structure),
- Ta₃Ti₈ (A3B5_oC32_38_abce_abcdef) ,
- TaTi (AB_aP16_2_4i_4i).

Simple Monoclinic primitive vectors



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$x_1 \mathbf{a}_1 + z_1 \mathbf{a}_3$	=	$(ax_1 + cz_1 \cos \beta) \hat{\mathbf{x}} + cz_1 \sin \beta \hat{\mathbf{z}}$	(1a)	Ta I
$\mathbf{B}_2$	$x_2 \mathbf{a}_1 + z_2 \mathbf{a}_3$	=	$(ax_2 + cz_2 \cos \beta) \hat{\mathbf{x}} + cz_2 \sin \beta \hat{\mathbf{z}}$	(1a)	Ta II
$\mathbf{B}_3$	$x_3 \mathbf{a}_1 + z_3 \mathbf{a}_3$	=	$(ax_3 + cz_3 \cos \beta) \hat{\mathbf{x}} + cz_3 \sin \beta \hat{\mathbf{z}}$	(1a)	Ti I
$\mathbf{B}_4$	$x_4 \mathbf{a}_1 + z_4 \mathbf{a}_3$	=	$(ax_4 + cz_4 \cos \beta) \hat{\mathbf{x}} + cz_4 \sin \beta \hat{\mathbf{z}}$	(1a)	Ti II
$\mathbf{B}_5$	$x_5 \mathbf{a}_1 + \frac{1}{2} \mathbf{a}_2 + z_5 \mathbf{a}_3$	=	$(ax_5 + cz_5 \cos \beta) \hat{\mathbf{x}} + \frac{1}{2} b \hat{\mathbf{y}} + cz_5 \sin \beta \hat{\mathbf{z}}$	(1b)	Ta III
$\mathbf{B}_6$	$x_6 \mathbf{a}_1 + \frac{1}{2} \mathbf{a}_2 + z_6 \mathbf{a}_3$	=	$(ax_6 + cz_6 \cos \beta) \hat{\mathbf{x}} + \frac{1}{2} b \hat{\mathbf{y}} + cz_6 \sin \beta \hat{\mathbf{z}}$	(1b)	Ti III
$\mathbf{B}_7$	$x_7 \mathbf{a}_1 + \frac{1}{2} \mathbf{a}_2 + z_7 \mathbf{a}_3$	=	$(ax_7 + cz_7 \cos \beta) \hat{\mathbf{x}} + \frac{1}{2} b \hat{\mathbf{y}} + cz_7 \sin \beta \hat{\mathbf{z}}$	(1b)	Ti IV
$\mathbf{B}_8$	$x_8 \mathbf{a}_1 + \frac{1}{2} \mathbf{a}_2 + z_8 \mathbf{a}_3$	=	$(ax_8 + cz_8 \cos \beta) \hat{\mathbf{x}} + \frac{1}{2} b \hat{\mathbf{y}} + cz_8 \sin \beta \hat{\mathbf{z}}$	(1b)	Ti V
$\mathbf{B}_9$	$x_9 \mathbf{a}_1 + y_9 \mathbf{a}_2 + z_9 \mathbf{a}_3$	=	$(ax_9 + cz_9 \cos \beta) \hat{\mathbf{x}} + by_9 \hat{\mathbf{y}} + cz_9 \sin \beta \hat{\mathbf{z}}$	(2c)	Ta IV
$\mathbf{B}_{10}$	$x_9 \mathbf{a}_1 - y_9 \mathbf{a}_2 + z_9 \mathbf{a}_3$	=	$(ax_9 + cz_9 \cos \beta) \hat{\mathbf{x}} - by_9 \hat{\mathbf{y}} + cz_9 \sin \beta \hat{\mathbf{z}}$	(2c)	Ta IV
$\mathbf{B}_{11}$	$x_{10} \mathbf{a}_1 + y_{10} \mathbf{a}_2 + z_{10} \mathbf{a}_3$	=	$(ax_{10} + cz_{10} \cos \beta) \hat{\mathbf{x}} + by_{10} \hat{\mathbf{y}} + cz_{10} \sin \beta \hat{\mathbf{z}}$	(2c)	Ti VI
$\mathbf{B}_{12}$	$x_{10} \mathbf{a}_1 - y_{10} \mathbf{a}_2 + z_{10} \mathbf{a}_3$	=	$(ax_{10} + cz_{10} \cos \beta) \hat{\mathbf{x}} - by_{10} \hat{\mathbf{y}} + cz_{10} \sin \beta \hat{\mathbf{z}}$	(2c)	Ti VI
$\mathbf{B}_{13}$	$x_{11} \mathbf{a}_1 + y_{11} \mathbf{a}_2 + z_{11} \mathbf{a}_3$	=	$(ax_{11} + cz_{11} \cos \beta) \hat{\mathbf{x}} + by_{11} \hat{\mathbf{y}} + cz_{11} \sin \beta \hat{\mathbf{z}}$	(2c)	Ti VII
$\mathbf{B}_{14}$	$x_{11} \mathbf{a}_1 - y_{11} \mathbf{a}_2 + z_{11} \mathbf{a}_3$	=	$(ax_{11} + cz_{11} \cos \beta) \hat{\mathbf{x}} - by_{11} \hat{\mathbf{y}} + cz_{11} \sin \beta \hat{\mathbf{z}}$	(2c)	Ti VII
$\mathbf{B}_{15}$	$x_{12} \mathbf{a}_1 + y_{12} \mathbf{a}_2 + z_{12} \mathbf{a}_3$	=	$(ax_{12} + cz_{12} \cos \beta) \hat{\mathbf{x}} + by_{12} \hat{\mathbf{y}} + cz_{12} \sin \beta \hat{\mathbf{z}}$	(2c)	Ti VIII
$\mathbf{B}_{16}$	$x_{12} \mathbf{a}_1 - y_{12} \mathbf{a}_2 + z_{12} \mathbf{a}_3$	=	$(ax_{12} + cz_{12} \cos \beta) \hat{\mathbf{x}} - by_{12} \hat{\mathbf{y}} + cz_{12} \sin \beta \hat{\mathbf{z}}$	(2c)	Ti VIII

References

- [1] C. Jiang, C. Wolverton, J. Sofo, L.-Q. Chen, and Z.-K. Liu, *First-principles study of binary bcc alloys using special quasirandom structures*, Phys. Rev. B **69**, 214202 (2004), doi:10.1103/PhysRevB.69.214202.
- [2] T. Chakraborty, J. Rogal, and R. Drautz, *Unraveling the composition dependence of the martensitic transformation temperature: A first-principles study of Ti-Ta alloys*, Phys. Rev. B **94**, 224104 (2016), doi:10.1103/PhysRevB.94.224104.

First cited in

D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.