

Ba₅In₄Bi₅ Structure:

A5B5C4_tP28_104_ac_ac_c-001


This structure previously used the label(s) **A5B5C4_tP28_104_ac_ac_c**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/GFEJ>

https://aflow.org/prototype-encyclopedia/A5B5C4_tP28_104_ac_ac_c-001




Prototype	Ba ₅ Bi ₅ In ₄
AFLOW prototype label	A5B5C4_tP28_104_ac_ac_c-001
ICSD	54853
CCDC	1619211
Pearson symbol	tP28
Space group number	104
Space group symbol	<i>P4nc</i>
AFLOW prototype command	<pre>aflow --proto=A5B5C4_tP28_104_ac_ac_c-001 --params=a, c/a, z₁, z₂, x₃, y₃, z₃, x₄, y₄, z₄, x₅, y₅, z₅</pre>

- Space group $P4nc$ #104 allows an arbitrary placement of the origin of the z -axis. Here we use this freedom to set $z_1 = 1/2$ for the Ba-I atoms.

Simple Tetragonal primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= a \hat{\mathbf{x}} \\ \mathbf{a}_2 &= a \hat{\mathbf{y}} \\ \mathbf{a}_3 &= c \hat{\mathbf{z}}\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$= z_1 \mathbf{a}_3$	$=$	$c z_1 \hat{\mathbf{z}}$	(2a)	Ba I
$\mathbf{B}_2$	$= \frac{1}{2} \mathbf{a}_1 + \frac{1}{2} \mathbf{a}_2 + (z_1 + \frac{1}{2}) \mathbf{a}_3$	$=$	$\frac{1}{2} a \hat{\mathbf{x}} + \frac{1}{2} a \hat{\mathbf{y}} + c (z_1 + \frac{1}{2}) \hat{\mathbf{z}}$	(2a)	Ba I
$\mathbf{B}_3$	$= z_2 \mathbf{a}_3$	$=$	$c z_2 \hat{\mathbf{z}}$	(2a)	Bi I
$\mathbf{B}_4$	$= \frac{1}{2} \mathbf{a}_1 + \frac{1}{2} \mathbf{a}_2 + (z_2 + \frac{1}{2}) \mathbf{a}_3$	$=$	$\frac{1}{2} a \hat{\mathbf{x}} + \frac{1}{2} a \hat{\mathbf{y}} + c (z_2 + \frac{1}{2}) \hat{\mathbf{z}}$	(2a)	Bi I
$\mathbf{B}_5$	$= x_3 \mathbf{a}_1 + y_3 \mathbf{a}_2 + z_3 \mathbf{a}_3$	$=$	$a x_3 \hat{\mathbf{x}} + a y_3 \hat{\mathbf{y}} + c z_3 \hat{\mathbf{z}}$	(8c)	Ba II
$\mathbf{B}_6$	$= -x_3 \mathbf{a}_1 - y_3 \mathbf{a}_2 + z_3 \mathbf{a}_3$	$=$	$-a x_3 \hat{\mathbf{x}} - a y_3 \hat{\mathbf{y}} + c z_3 \hat{\mathbf{z}}$	(8c)	Ba II
$\mathbf{B}_7$	$= -y_3 \mathbf{a}_1 + x_3 \mathbf{a}_2 + z_3 \mathbf{a}_3$	$=$	$-a y_3 \hat{\mathbf{x}} + a x_3 \hat{\mathbf{y}} + c z_3 \hat{\mathbf{z}}$	(8c)	Ba II
$\mathbf{B}_8$	$= y_3 \mathbf{a}_1 - x_3 \mathbf{a}_2 + z_3 \mathbf{a}_3$	$=$	$a y_3 \hat{\mathbf{x}} - a x_3 \hat{\mathbf{y}} + c z_3 \hat{\mathbf{z}}$	(8c)	Ba II
$\mathbf{B}_9$	$= (x_3 + \frac{1}{2}) \mathbf{a}_1 - (y_3 - \frac{1}{2}) \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	$=$	$a (x_3 + \frac{1}{2}) \hat{\mathbf{x}} - a (y_3 - \frac{1}{2}) \hat{\mathbf{y}} + c (z_3 + \frac{1}{2}) \hat{\mathbf{z}}$	(8c)	Ba II
$\mathbf{B}_{10}$	$= -(x_3 - \frac{1}{2}) \mathbf{a}_1 + (y_3 + \frac{1}{2}) \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-a (x_3 - \frac{1}{2}) \hat{\mathbf{x}} + a (y_3 + \frac{1}{2}) \hat{\mathbf{y}} + c (z_3 + \frac{1}{2}) \hat{\mathbf{z}}$	(8c)	Ba II
$\mathbf{B}_{11}$	$= -(y_3 - \frac{1}{2}) \mathbf{a}_1 - (x_3 - \frac{1}{2}) \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-a (y_3 - \frac{1}{2}) \hat{\mathbf{x}} - a (x_3 - \frac{1}{2}) \hat{\mathbf{y}} + c (z_3 + \frac{1}{2}) \hat{\mathbf{z}}$	(8c)	Ba II
$\mathbf{B}_{12}$	$= (y_3 + \frac{1}{2}) \mathbf{a}_1 + (x_3 + \frac{1}{2}) \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	$=$	$a (y_3 + \frac{1}{2}) \hat{\mathbf{x}} + a (x_3 + \frac{1}{2}) \hat{\mathbf{y}} + c (z_3 + \frac{1}{2}) \hat{\mathbf{z}}$	(8c)	Ba II
$\mathbf{B}_{13}$	$= x_4 \mathbf{a}_1 + y_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$a x_4 \hat{\mathbf{x}} + a y_4 \hat{\mathbf{y}} + c z_4 \hat{\mathbf{z}}$	(8c)	Bi II
$\mathbf{B}_{14}$	$= -x_4 \mathbf{a}_1 - y_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$-a x_4 \hat{\mathbf{x}} - a y_4 \hat{\mathbf{y}} + c z_4 \hat{\mathbf{z}}$	(8c)	Bi II
$\mathbf{B}_{15}$	$= -y_4 \mathbf{a}_1 + x_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$-a y_4 \hat{\mathbf{x}} + a x_4 \hat{\mathbf{y}} + c z_4 \hat{\mathbf{z}}$	(8c)	Bi II
$\mathbf{B}_{16}$	$= y_4 \mathbf{a}_1 - x_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$a y_4 \hat{\mathbf{x}} - a x_4 \hat{\mathbf{y}} + c z_4 \hat{\mathbf{z}}$	(8c)	Bi II
$\mathbf{B}_{17}$	$= (x_4 + \frac{1}{2}) \mathbf{a}_1 - (y_4 - \frac{1}{2}) \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	$=$	$a (x_4 + \frac{1}{2}) \hat{\mathbf{x}} - a (y_4 - \frac{1}{2}) \hat{\mathbf{y}} + c (z_4 + \frac{1}{2}) \hat{\mathbf{z}}$	(8c)	Bi II
$\mathbf{B}_{18}$	$= -(x_4 - \frac{1}{2}) \mathbf{a}_1 + (y_4 + \frac{1}{2}) \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-a (x_4 - \frac{1}{2}) \hat{\mathbf{x}} + a (y_4 + \frac{1}{2}) \hat{\mathbf{y}} + c (z_4 + \frac{1}{2}) \hat{\mathbf{z}}$	(8c)	Bi II
$\mathbf{B}_{19}$	$= -(y_4 - \frac{1}{2}) \mathbf{a}_1 - (x_4 - \frac{1}{2}) \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-a (y_4 - \frac{1}{2}) \hat{\mathbf{x}} - a (x_4 - \frac{1}{2}) \hat{\mathbf{y}} + c (z_4 + \frac{1}{2}) \hat{\mathbf{z}}$	(8c)	Bi II

$$\begin{aligned}
\mathbf{B}_{20} &= \begin{pmatrix} y_4 + \frac{1}{2} \\ z_4 + \frac{1}{2} \end{pmatrix} \mathbf{a}_1 + \begin{pmatrix} x_4 + \frac{1}{2} \\ z_4 + \frac{1}{2} \end{pmatrix} \mathbf{a}_2 + \mathbf{a}_3 &= a \begin{pmatrix} y_4 + \frac{1}{2} \\ z_4 + \frac{1}{2} \end{pmatrix} \hat{\mathbf{x}} + a \begin{pmatrix} x_4 + \frac{1}{2} \\ z_4 + \frac{1}{2} \end{pmatrix} \hat{\mathbf{y}} + c \begin{pmatrix} y_4 + \frac{1}{2} \\ z_4 + \frac{1}{2} \end{pmatrix} \hat{\mathbf{z}} &(8c) & \text{Bi II} \\
\mathbf{B}_{21} &= x_5 \mathbf{a}_1 + y_5 \mathbf{a}_2 + z_5 \mathbf{a}_3 &= ax_5 \hat{\mathbf{x}} + ay_5 \hat{\mathbf{y}} + cz_5 \hat{\mathbf{z}} &(8c) & \text{In I} \\
\mathbf{B}_{22} &= -x_5 \mathbf{a}_1 - y_5 \mathbf{a}_2 + z_5 \mathbf{a}_3 &= -ax_5 \hat{\mathbf{x}} - ay_5 \hat{\mathbf{y}} + cz_5 \hat{\mathbf{z}} &(8c) & \text{In I} \\
\mathbf{B}_{23} &= -y_5 \mathbf{a}_1 + x_5 \mathbf{a}_2 + z_5 \mathbf{a}_3 &= -ay_5 \hat{\mathbf{x}} + ax_5 \hat{\mathbf{y}} + cz_5 \hat{\mathbf{z}} &(8c) & \text{In I} \\
\mathbf{B}_{24} &= y_5 \mathbf{a}_1 - x_5 \mathbf{a}_2 + z_5 \mathbf{a}_3 &= ay_5 \hat{\mathbf{x}} - ax_5 \hat{\mathbf{y}} + cz_5 \hat{\mathbf{z}} &(8c) & \text{In I} \\
\mathbf{B}_{25} &= \begin{pmatrix} x_5 + \frac{1}{2} \\ z_5 + \frac{1}{2} \end{pmatrix} \mathbf{a}_1 - \begin{pmatrix} y_5 - \frac{1}{2} \\ z_5 + \frac{1}{2} \end{pmatrix} \mathbf{a}_2 + \mathbf{a}_3 &= a \begin{pmatrix} x_5 + \frac{1}{2} \\ z_5 + \frac{1}{2} \end{pmatrix} \hat{\mathbf{x}} - a \begin{pmatrix} y_5 - \frac{1}{2} \\ z_5 + \frac{1}{2} \end{pmatrix} \hat{\mathbf{y}} + c \begin{pmatrix} x_5 + \frac{1}{2} \\ z_5 + \frac{1}{2} \end{pmatrix} \hat{\mathbf{z}} &(8c) & \text{In I} \\
\mathbf{B}_{26} &= -\begin{pmatrix} x_5 - \frac{1}{2} \\ z_5 + \frac{1}{2} \end{pmatrix} \mathbf{a}_1 + \begin{pmatrix} y_5 + \frac{1}{2} \\ z_5 + \frac{1}{2} \end{pmatrix} \mathbf{a}_2 + \mathbf{a}_3 &= -a \begin{pmatrix} x_5 - \frac{1}{2} \\ z_5 + \frac{1}{2} \end{pmatrix} \hat{\mathbf{x}} + a \begin{pmatrix} y_5 + \frac{1}{2} \\ z_5 + \frac{1}{2} \end{pmatrix} \hat{\mathbf{y}} + c \begin{pmatrix} x_5 - \frac{1}{2} \\ z_5 + \frac{1}{2} \end{pmatrix} \hat{\mathbf{z}} &(8c) & \text{In I} \\
\mathbf{B}_{27} &= -\begin{pmatrix} y_5 - \frac{1}{2} \\ z_5 + \frac{1}{2} \end{pmatrix} \mathbf{a}_1 - \begin{pmatrix} x_5 - \frac{1}{2} \\ z_5 + \frac{1}{2} \end{pmatrix} \mathbf{a}_2 + \mathbf{a}_3 &= -a \begin{pmatrix} y_5 - \frac{1}{2} \\ z_5 + \frac{1}{2} \end{pmatrix} \hat{\mathbf{x}} - a \begin{pmatrix} x_5 - \frac{1}{2} \\ z_5 + \frac{1}{2} \end{pmatrix} \hat{\mathbf{y}} + c \begin{pmatrix} y_5 - \frac{1}{2} \\ z_5 + \frac{1}{2} \end{pmatrix} \hat{\mathbf{z}} &(8c) & \text{In I} \\
\mathbf{B}_{28} &= \begin{pmatrix} y_5 + \frac{1}{2} \\ z_5 + \frac{1}{2} \end{pmatrix} \mathbf{a}_1 + \begin{pmatrix} x_5 + \frac{1}{2} \\ z_5 + \frac{1}{2} \end{pmatrix} \mathbf{a}_2 + \mathbf{a}_3 &= a \begin{pmatrix} y_5 + \frac{1}{2} \\ z_5 + \frac{1}{2} \end{pmatrix} \hat{\mathbf{x}} + a \begin{pmatrix} x_5 + \frac{1}{2} \\ z_5 + \frac{1}{2} \end{pmatrix} \hat{\mathbf{y}} + c \begin{pmatrix} y_5 + \frac{1}{2} \\ z_5 + \frac{1}{2} \end{pmatrix} \hat{\mathbf{z}} &(8c) & \text{In I}
\end{aligned}$$

References

- [1] S. Ponou, T. F. Fässler, G. Tobías, E. Canadell, A. Cho, and S. C. Sevov, *Synthesis, Characterization, and Electronic Structure of $\text{Ba}_5\text{In}_4\text{Bi}_5$: An Acentric and One-Electron Deficient Phase*, Chem. Eur. J **10**, 3615–3621 (2004), doi:10.1002/chem.200306061.

Found in

- [1] P. Villars and K. Cenzual, *Pearson's Crystal Data – Crystal Structure Database for Inorganic Compounds* (2013). ASM International.

First cited in

D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, Comput. Mater. Sci. **161**, S1 (2019). doi: 10.1016/j.commatsci.2018.10.043