K_2Hg_7 Structure: A7B2_hP9_164_ai_d-001

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

---

https://aflow.org/prototype-encyclopedia/QCMW

https://aflow.org/prototype-encyclopedia/A7B2_hP9_164_ai_d-001



Prototype	Hg_7K_2
AFLOW prototype label	A7B2_hP9_164_ai_d-001
ICSD	107482
CCDC	1665207
Pearson symbol	hP9
Space group number	164
Space group symbol	$P\bar{3}m1$

AFLOW prototype command `aflow --proto=A7B2_hP9_164_ai_d-001 --params=`$a, c/a, z_2, x_3, z_3$

Other compounds with this structure

Rb_2Hg_7

- This is a binary form of the K_2GeF_6 ($J1_{13}$) Structure.

Trigonal (Hexagonal) primitive vectors

$$\begin{aligned}\mathbf{a_1} &= \tfrac{1}{2}a\,\hat{\mathbf{x}} - \tfrac{\sqrt{3}}{2}a\,\hat{\mathbf{y}} \\ \mathbf{a_2} &= \tfrac{1}{2}a\,\hat{\mathbf{x}} + \tfrac{\sqrt{3}}{2}a\,\hat{\mathbf{y}} \\ \mathbf{a_3} &= c\,\hat{\mathbf{z}}\end{aligned}$$



Basis vectors

		Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B_1}$	=	0	=	0	(1a)	Hg I
$\mathbf{B_2}$	=	$\frac{1}{3}\,\mathbf{a}_1 + \frac{2}{3}\,\mathbf{a}_2 + z_2\,\mathbf{a}_3$	=	$\frac{1}{2}a\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a\,\hat{\mathbf{y}} + cz_2\,\hat{\mathbf{z}}$	(2d)	K I
$\mathbf{B_3}$	=	$\frac{2}{3}\,\mathbf{a}_1 + \frac{1}{3}\,\mathbf{a}_2 - z_2\,\mathbf{a}_3$	=	$\frac{1}{2}a\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a\,\hat{\mathbf{y}} - cz_2\,\hat{\mathbf{z}}$	(2d)	K I
$\mathbf{B_4}$	=	$x_3\,\mathbf{a}_1 - x_3\,\mathbf{a}_2 + z_3\,\mathbf{a}_3$	=	$-\sqrt{3}ax_3\,\hat{\mathbf{y}} + cz_3\,\hat{\mathbf{z}}$	(6i)	Hg II
$\mathbf{B_5}$	=	$x_3\,\mathbf{a}_1 + 2x_3\,\mathbf{a}_2 + z_3\,\mathbf{a}_3$	=	$\frac{3}{2}ax_3\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_3\,\hat{\mathbf{y}} + cz_3\,\hat{\mathbf{z}}$	(6i)	Hg II
$\mathbf{B_6}$	=	$-2x_3\,\mathbf{a}_1 - x_3\,\mathbf{a}_2 + z_3\,\mathbf{a}_3$	=	$-\frac{3}{2}ax_3\,\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_3\,\hat{\mathbf{y}} + cz_3\,\hat{\mathbf{z}}$	(6i)	Hg II
$\mathbf{B_7}$	=	$-x_3\,\mathbf{a}_1 + x_3\,\mathbf{a}_2 - z_3\,\mathbf{a}_3$	=	$\sqrt{3}ax_3\,\hat{\mathbf{y}} - cz_3\,\hat{\mathbf{z}}$	(6i)	Hg II
$\mathbf{B_8}$	=	$2x_3\,\mathbf{a}_1 + x_3\,\mathbf{a}_2 - z_3\,\mathbf{a}_3$	=	$\frac{3}{2}ax_3\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ax_3\,\hat{\mathbf{y}} - cz_3\,\hat{\mathbf{z}}$	(6i)	Hg II
$\mathbf{B_9}$	=	$-x_3\,\mathbf{a}_1 - 2x_3\,\mathbf{a}_2 - z_3\,\mathbf{a}_3$	=	$-\frac{3}{2}ax_3\,\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ax_3\,\hat{\mathbf{y}} - cz_3\,\hat{\mathbf{z}}$	(6i)	Hg II

References

[1] E. Biehl and H. J. Deiseroth, *K_2Hg_7 und Rb_2Hg_7, zwei Vertreter eines neuen Strukturtyps binärer intermetallischer Verbindungen*, Z. Anorganische und Allgemeine Chemie **625**, 1337–1342 (1999), doi:10.1002/(SICI)1521-3749(199908)625:8%3C1337::AID-ZAAC1337%3E3.0.CO;2-W.

Found in

[1] A. Jain, S. Ping, G. Hautier, W. Chen, W. D. R., S. Dacek, S. Cholia, D. Gunter, D. Skinner, G. Ceder, and K. A. Persson, *Commentary: The Materials Project: A materials genome approach to accelerating materials innovation*, APL Materials **1**, 011002 (2013), doi:10.1063/1.4812323.

First cited in

H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.