

Predicted High-Pressure YCaH_{12} Structure: AB12C_cP14_221_a_h_b-001


This structure previously used the label(s) **AB12C.cP14.221.a.h.b**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettl, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/SQ16>

https://aflow.org/prototype-encyclopedia/AB12C_cP14_221_a_h_b-001




Prototype	CaH_{12}Y
AFLOW prototype label	AB12C_cP14_221_a_h_b-001
ICSD	686726
CCDC	2230688
Pearson symbol	cP14
Space group number	221
Space group symbol	$Pm\bar{3}m$
AFLOW prototype command	<code>aflow --proto=AB12C_cP14_221_a_h_b-001 --params=a, x3</code>

- This structure was determined by *ab initio* methods and is predicted to be stable in the pressure range 180-257GPa, with $T_c = 230\text{K}$ at 180GPa. We show the predicted structure at 200GPa.
- The ICSD entry is from the calculations of (Liang, 2019).

Simple Cubic primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= a \hat{\mathbf{x}} \\ \mathbf{a}_2 &= a \hat{\mathbf{y}} \\ \mathbf{a}_3 &= a \hat{\mathbf{z}}\end{aligned}$$

$\mathbf{a}_1$
 $\mathbf{a}_3$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$=$	0	$=$	0	Ca I
$\mathbf{B}_2$	$=$	$\frac{1}{2} \mathbf{a}_1 + \frac{1}{2} \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$\frac{1}{2} a \hat{\mathbf{x}} + \frac{1}{2} a \hat{\mathbf{y}} + \frac{1}{2} a \hat{\mathbf{z}}$	(1b) Y I
$\mathbf{B}_3$	$=$	$x_3 \mathbf{a}_1 + \frac{1}{2} \mathbf{a}_2$	$=$	$ax_3 \hat{\mathbf{x}} + \frac{1}{2} a \hat{\mathbf{y}}$	(12h) H I
$\mathbf{B}_4$	$=$	$-x_3 \mathbf{a}_1 + \frac{1}{2} \mathbf{a}_2$	$=$	$-ax_3 \hat{\mathbf{x}} + \frac{1}{2} a \hat{\mathbf{y}}$	(12h) H I
$\mathbf{B}_5$	$=$	$x_3 \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$ax_3 \hat{\mathbf{y}} + \frac{1}{2} a \hat{\mathbf{z}}$	(12h) H I
$\mathbf{B}_6$	$=$	$-x_3 \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$-ax_3 \hat{\mathbf{y}} + \frac{1}{2} a \hat{\mathbf{z}}$	(12h) H I
$\mathbf{B}_7$	$=$	$\frac{1}{2} \mathbf{a}_1 + x_3 \mathbf{a}_3$	$=$	$\frac{1}{2} a \hat{\mathbf{x}} + ax_3 \hat{\mathbf{z}}$	(12h) H I
$\mathbf{B}_8$	$=$	$\frac{1}{2} \mathbf{a}_1 - x_3 \mathbf{a}_3$	$=$	$\frac{1}{2} a \hat{\mathbf{x}} - ax_3 \hat{\mathbf{z}}$	(12h) H I
$\mathbf{B}_9$	$=$	$\frac{1}{2} \mathbf{a}_1 + x_3 \mathbf{a}_2$	$=$	$\frac{1}{2} a \hat{\mathbf{x}} + ax_3 \hat{\mathbf{y}}$	(12h) H I
$\mathbf{B}_{10}$	$=$	$\frac{1}{2} \mathbf{a}_1 - x_3 \mathbf{a}_2$	$=$	$\frac{1}{2} a \hat{\mathbf{x}} - ax_3 \hat{\mathbf{y}}$	(12h) H I
$\mathbf{B}_{11}$	$=$	$x_3 \mathbf{a}_1 + \frac{1}{2} \mathbf{a}_3$	$=$	$ax_3 \hat{\mathbf{x}} + \frac{1}{2} a \hat{\mathbf{z}}$	(12h) H I
$\mathbf{B}_{12}$	$=$	$-x_3 \mathbf{a}_1 + \frac{1}{2} \mathbf{a}_3$	$=$	$-ax_3 \hat{\mathbf{x}} + \frac{1}{2} a \hat{\mathbf{z}}$	(12h) H I
$\mathbf{B}_{13}$	$=$	$\frac{1}{2} \mathbf{a}_2 - x_3 \mathbf{a}_3$	$=$	$\frac{1}{2} a \hat{\mathbf{y}} - ax_3 \hat{\mathbf{z}}$	(12h) H I
$\mathbf{B}_{14}$	$=$	$\frac{1}{2} \mathbf{a}_2 + x_3 \mathbf{a}_3$	$=$	$\frac{1}{2} a \hat{\mathbf{y}} + ax_3 \hat{\mathbf{z}}$	(12h) H I

References

- [1] H. Xie, D. Duan, Z. Shao, H. Song, Y. Wang, X. Xiao, D. Li, F. Tian, B. Liu, and T. Cui, *High-temperature superconductivity in ternary clathrate YCaH_{12} under high pressures*, J. Phys.: Condens. Matter **31**, 245404 (2019), doi:10.1088/1361-648X/ab09b4.
- [2] X. Liang, A. Bergara, L. Wang, B. Wen, Z. Zhao, X.-F. Zhou, J. He, G. Gao, and Y. Tian, *Potential high- T_c superconductivity in CaYH_{12} under pressure*, Phys. Rev. B **99**, 100505(R) (2019), doi:10.1103/PhysRevB.99.100505.

First cited in

D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.