

Jacutingaite (Pt₂HgSe₃) Structure: AB2C3_hP12_164_d_ae_i-001


This structure previously used the label(s) **AB2C3_hP12_164_d_ae_i**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/DCW7>

https://aflow.org/prototype-encyclopedia/AB2C3_hP12_164_d_ae_i-001



Prototype	HgPt ₂ Se ₃
AFLOW prototype label	AB2C3_hP12_164_d_ae_i-001
Mineral name	jacutingaite
ICSD	185808
CCDC	1694989
Pearson symbol	hP12

Space group number	164
Space group symbol	$P\bar{3}m1$
AFLOW prototype command	<code>aflow --proto=AB2C3_hP12_164_d_ae_i-001</code> <code>--params=a, c/a, z₂, x₄, z₄</code>

Other compounds with this structure


Pd₂HgSe₃, Pt₂TlS₃, Pt₂TlSe₃, Pt₂TlTe₃

- Table 4 of (Vymazalová, 2012) has a small error: the positions of the Hg(1) atoms should be written (1/3 2/3 0.3507) rather than (1/3 1/3 0.3507).
- The ICSD uses Pt₂TlTe₃ to define the structuretype.

Trigonal (Hexagonal) primitive vectors

$$\begin{aligned}
\mathbf{a}_1 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a \hat{\mathbf{y}} \\
\mathbf{a}_2 &= \frac{1}{2}a \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a \hat{\mathbf{y}} \\
\mathbf{a}_3 &= c \hat{\mathbf{z}}
\end{aligned}$$

$\mathbf{a}_1^{\text{a2}}$
 $\mathbf{a}_3^{\text{a2}}$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$= 0$	$=$	0	(1a)	Pt I
$\mathbf{B}_2$	$= \frac{1}{3} \mathbf{a}_1 + \frac{2}{3} \mathbf{a}_2 + z_2 \mathbf{a}_3$	$=$	$\frac{1}{2}a \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} + cz_2 \hat{\mathbf{z}}$	(2d)	Hg I
$\mathbf{B}_3$	$= \frac{2}{3} \mathbf{a}_1 + \frac{1}{3} \mathbf{a}_2 - z_2 \mathbf{a}_3$	$=$	$\frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} - cz_2 \hat{\mathbf{z}}$	(2d)	Hg I
$\mathbf{B}_4$	$= \frac{1}{2} \mathbf{a}_1$	$=$	$\frac{1}{4}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{4}a \hat{\mathbf{y}}$	(3e)	Pt II
$\mathbf{B}_5$	$= \frac{1}{2} \mathbf{a}_2$	$=$	$\frac{1}{4}a \hat{\mathbf{x}} + \frac{\sqrt{3}}{4}a \hat{\mathbf{y}}$	(3e)	Pt II
$\mathbf{B}_6$	$= \frac{1}{2} \mathbf{a}_1 + \frac{1}{2} \mathbf{a}_2$	$=$	$\frac{1}{2}a \hat{\mathbf{x}}$	(3e)	Pt II
$\mathbf{B}_7$	$= x_4 \mathbf{a}_1 - x_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$-\sqrt{3}ax_4 \hat{\mathbf{y}} + cz_4 \hat{\mathbf{z}}$	(6i)	Se I
$\mathbf{B}_8$	$= x_4 \mathbf{a}_1 + 2x_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$\frac{3}{2}ax_4 \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_4 \hat{\mathbf{y}} + cz_4 \hat{\mathbf{z}}$	(6i)	Se I
$\mathbf{B}_9$	$= -2x_4 \mathbf{a}_1 - x_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$-\frac{3}{2}ax_4 \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_4 \hat{\mathbf{y}} + cz_4 \hat{\mathbf{z}}$	(6i)	Se I
$\mathbf{B}_{10}$	$= -x_4 \mathbf{a}_1 + x_4 \mathbf{a}_2 - z_4 \mathbf{a}_3$	$=$	$\sqrt{3}ax_4 \hat{\mathbf{y}} - cz_4 \hat{\mathbf{z}}$	(6i)	Se I
$\mathbf{B}_{11}$	$= 2x_4 \mathbf{a}_1 + x_4 \mathbf{a}_2 - z_4 \mathbf{a}_3$	$=$	$\frac{3}{2}ax_4 \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ax_4 \hat{\mathbf{y}} - cz_4 \hat{\mathbf{z}}$	(6i)	Se I
$\mathbf{B}_{12}$	$= -x_4 \mathbf{a}_1 - 2x_4 \mathbf{a}_2 - z_4 \mathbf{a}_3$	$=$	$-\frac{3}{2}ax_4 \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ax_4 \hat{\mathbf{y}} - cz_4 \hat{\mathbf{z}}$	(6i)	Se I

References

- [1] A. Vymazalová, F. Laufek, M. Drábek, A. R. Cabral, J. Haloda, T. Sidorinová, B. Lehmann, H. F., and J. Drahokoupil, *Jacutingaitite, Pt₂HgSe₃, A New Platinum-Group Mineral Species From the Cauê Iron-Ore Deposit, Itabira District, Minas Gerais, Brazil*, Can. Min. **50**, 431–440 (2012), doi:10.3749/canmin.50.2.431.

Found in

- [1] A. Marrazzo, N. Marzari, and M. Gibertini, *Emergent dual topology in the three-dimensional Kane-Mele Pt_2HgSe_3* , Phys. Rev. Research **2**, 012063(R) (2020), doi:10.1103/PhysRevResearch.2.012063.

First cited in

- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.