

NiO₂ Structure:


AB2_mC6_12_a_i-003

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettl, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Osos, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/DZY0>

https://aflow.org/prototype-encyclopedia/AB2_mC6_12_a_i-003




Prototype	NiO ₂
AFLOW prototype label	AB2_mC6_12_a_i-003
ICSD	88720
CCDC	1648455
Pearson symbol	mC6
Space group number	12
Space group symbol	$C2/m$
AFLOW prototype command	<code>aflow --proto=AB2_mC6_12_a_i-003</code> <code>--params=a, b/a, c/a, β, x_2, z_2</code>

- C34 Calverite, α -HgO₂, and NiO₂ (this structure) have the same AFLOW prototype label, AB2_mC6_12_a_i. The structures are generated by the same symmetry operations with different sets of parameters (`--params`) specified in their corresponding CIF files.

Base-centered Monoclinic primitive vectors

$$\begin{aligned}
\mathbf{a}_1 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{1}{2}b \hat{\mathbf{y}} \\
\mathbf{a}_2 &= \frac{1}{2}a \hat{\mathbf{x}} + \frac{1}{2}b \hat{\mathbf{y}} \\
\mathbf{a}_3 &= c \cos \beta \hat{\mathbf{x}} + c \sin \beta \hat{\mathbf{z}}
\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	=	0	=	0	(2a) Ni I
$\mathbf{B}_2$	=	$x_2 \mathbf{a}_1 + x_2 \mathbf{a}_2 + z_2 \mathbf{a}_3$	=	$(ax_2 + cz_2 \cos \beta) \hat{\mathbf{x}} + cz_2 \sin \beta \hat{\mathbf{z}}$	(4i) O I
$\mathbf{B}_3$	=	$-x_2 \mathbf{a}_1 - x_2 \mathbf{a}_2 - z_2 \mathbf{a}_3$	=	$-(ax_2 + cz_2 \cos \beta) \hat{\mathbf{x}} - cz_2 \sin \beta \hat{\mathbf{z}}$	(4i) O I

References

- [1] J. M. Tarascon, G. Vaughan, Y. Chabre, L. Seguin, M. Anne, P. Strobel, and G. Amatucci, In Situ *Structural and Electrochemical Study of $Ni_{1-x}Co_xO_2$ Metastable Oxides Prepared by Soft Chemistry*, J. Solid State Chem. **147**, 410–420 (1999), doi:10.1006/jssc.1999.8465.

First cited in

H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.