

# CoGe<sub>2</sub> Structure:


## AB2\_oC24\_64\_d\_ef-002

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettl, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/QB3A>

[https://aflow.org/prototype-encyclopedia/AB2\\_oC24\\_64\\_d\\_ef-002](https://aflow.org/prototype-encyclopedia/AB2_oC24_64_d_ef-002)




|                         |                                                                                                                                                  |
|-------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------|
| Prototype               | CoGe <sub>2</sub>                                                                                                                                |
| AFLOW prototype label   | AB2_oC24_64_d_ef-002                                                                                                                             |
| ICSD                    | 52964                                                                                                                                            |
| CCDC                    | 1617675                                                                                                                                          |
| Pearson symbol          | oC24                                                                                                                                             |
| Space group number      | 64                                                                                                                                               |
| Space group symbol      | <i>Cmce</i>                                                                                                                                      |
| AFLOW prototype command | <code>aflow --proto=AB2_oC24_64_d_ef-002</code><br><code>--params=a, b/a, c/a, x<sub>1</sub>, y<sub>2</sub>, y<sub>3</sub>, z<sub>3</sub></code> |

- The actual stoichiometry is Co<sub>7</sub>Ge<sub>16</sub>, as the Co (8d) sites are 87.5% occupied.
- (Schubert, 1950) described this compound as being isotypic to PdSn<sub>2</sub> (*C<sub>e</sub>*) in space group *Aba2* #41.
- (Cenzual, 1991) showed that the given *z* coordinates for the cobalt atoms were consistent with space group *Cmca* #64.
- Although (Schubert, 1950) give the lattice parameters in Ångströms, (Cenzual, 1991) asserts that they were actually in kX units and converts them to Ångströms. We use the later values for the lattice parameters.

## Base-centered Orthorhombic primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{1}{2}b \hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{1}{2}a \hat{\mathbf{x}} + \frac{1}{2}b \hat{\mathbf{y}} \\ \mathbf{a}_3 &= c \hat{\mathbf{z}}\end{aligned}$$



## Basis vectors

|                   | Lattice coordinates                                                                                                                            |  | Cartesian coordinates                                                                                      | Wyckoff position | Atom type |
|-------------------|------------------------------------------------------------------------------------------------------------------------------------------------|--|------------------------------------------------------------------------------------------------------------|------------------|-----------|
| $\mathbf{B}_1$    | $= x_1 \mathbf{a}_1 + x_1 \mathbf{a}_2 =$                                                                                                      |  | $ax_1 \hat{\mathbf{x}}$                                                                                    | (8d)             | Co I      |
| $\mathbf{B}_2$    | $= -\left(x_1 - \frac{1}{2}\right) \mathbf{a}_1 - \left(x_1 - \frac{1}{2}\right) \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3 =$                    |  | $-a\left(x_1 - \frac{1}{2}\right) \hat{\mathbf{x}} + \frac{1}{2}c \hat{\mathbf{z}}$                        | (8d)             | Co I      |
| $\mathbf{B}_3$    | $= -x_1 \mathbf{a}_1 - x_1 \mathbf{a}_2 =$                                                                                                     |  | $-ax_1 \hat{\mathbf{x}}$                                                                                   | (8d)             | Co I      |
| $\mathbf{B}_4$    | $= \left(x_1 + \frac{1}{2}\right) \mathbf{a}_1 + \left(x_1 + \frac{1}{2}\right) \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3 =$                     |  | $a\left(x_1 + \frac{1}{2}\right) \hat{\mathbf{x}} + \frac{1}{2}c \hat{\mathbf{z}}$                         | (8d)             | Co I      |
| $\mathbf{B}_5$    | $= -\left(y_2 - \frac{1}{4}\right) \mathbf{a}_1 + \left(y_2 + \frac{1}{4}\right) \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3 =$                    |  | $\frac{1}{4}a \hat{\mathbf{x}} + by_2 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$                    | (8e)             | Ge I      |
| $\mathbf{B}_6$    | $= \left(y_2 + \frac{1}{4}\right) \mathbf{a}_1 - \left(y_2 - \frac{1}{4}\right) \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3 =$                     |  | $\frac{1}{4}a \hat{\mathbf{x}} - by_2 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$                    | (8e)             | Ge I      |
| $\mathbf{B}_7$    | $= \left(y_2 + \frac{3}{4}\right) \mathbf{a}_1 - \left(y_2 - \frac{3}{4}\right) \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3 =$                     |  | $\frac{3}{4}a \hat{\mathbf{x}} - by_2 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$                    | (8e)             | Ge I      |
| $\mathbf{B}_8$    | $= -\left(y_2 - \frac{3}{4}\right) \mathbf{a}_1 + \left(y_2 + \frac{3}{4}\right) \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3 =$                    |  | $\frac{3}{4}a \hat{\mathbf{x}} + by_2 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$                    | (8e)             | Ge I      |
| $\mathbf{B}_9$    | $= -y_3 \mathbf{a}_1 + y_3 \mathbf{a}_2 + z_3 \mathbf{a}_3 =$                                                                                  |  | $by_3 \hat{\mathbf{y}} + cz_3 \hat{\mathbf{z}}$                                                            | (8f)             | Ge II     |
| $\mathbf{B}_{10}$ | $= \left(y_3 + \frac{1}{2}\right) \mathbf{a}_1 - \left(y_3 - \frac{1}{2}\right) \mathbf{a}_2 + \left(z_3 + \frac{1}{2}\right) \mathbf{a}_3 =$  |  | $\frac{1}{2}a \hat{\mathbf{x}} - by_3 \hat{\mathbf{y}} + c\left(z_3 + \frac{1}{2}\right) \hat{\mathbf{z}}$ | (8f)             | Ge II     |
| $\mathbf{B}_{11}$ | $= -\left(y_3 - \frac{1}{2}\right) \mathbf{a}_1 + \left(y_3 + \frac{1}{2}\right) \mathbf{a}_2 - \left(z_3 - \frac{1}{2}\right) \mathbf{a}_3 =$ |  | $\frac{1}{2}a \hat{\mathbf{x}} + by_3 \hat{\mathbf{y}} - c\left(z_3 - \frac{1}{2}\right) \hat{\mathbf{z}}$ | (8f)             | Ge II     |
| $\mathbf{B}_{12}$ | $= y_3 \mathbf{a}_1 - y_3 \mathbf{a}_2 - z_3 \mathbf{a}_3 =$                                                                                   |  | $-by_3 \hat{\mathbf{y}} - cz_3 \hat{\mathbf{z}}$                                                           | (8f)             | Ge II     |

## References

- [1] K. Schubert and H. Pfisterer, *Zur Kristallchemie der B-Metall-reichsten Phasen in Legierungen von Übergangsmetallen der Eisen- und Platintraden mit Elementen der vierten Nebengruppe*, Zeitschrift für Metallkunde **41**, 433–441 (1950).

## Found in

- [1] K. Cenzual, L. M. Gelato, M. Penzo, and E. Parthé, *Inorganic structure types with revised space groups. I*, Acta Crystallogr. Sect. B **47**, 433–439 (1991), doi:10.1107/S0108768191000903.

## First cited in

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.