

Post-perovskite (MgSiO₃) Structure: AB3C_oC20_63_c_cf_a-001


This structure previously used the label(s) **AB3C_oC20_63_c_cf_a**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/BCSA>

https://aflow.org/prototype-encyclopedia/AB3C_oC20_63_c_cf_a-001



Prototype	MgO ₃ Si
AFLOW prototype label	AB3C_oC20_63_c_cf_a-001
ICSD	158959
CCDC	1675456
Pearson symbol	oC20
Space group number	63
Space group symbol	<i>Cmcm</i>
AFLOW prototype command	<code>aflow --proto=AB3C_oC20_63_c_cf_a-001 --params=a, b/a, c/a, y₂, y₃, y₄, z₄</code>

Other compounds with this structure


AlNHf₃, AlNTi₃, AlNZr₃, AsCCr₃, AsCV₃, CaBrIn₃, CaIrO₃, CaPtO₃, CaRhO₃, CeYbSe₃, FeNaF₃, GeCV₃, GeNV₃, LaYbS₃, LaYbSe₃, LuNdSe₃, LuPrSe₃, MgGeO₃, NaIrO₃, NaMgF₃, NaNiF₃, NdYbSe₃, NiOZr₃, PCV₃, PNCr₃, PNV₃, POZr₃, PbTiI₃, PrYbSe₃, ScUS₃

- This structure was determined by a combination of x-ray diffraction measurements and atomistic simulations of MgSiO_3 at a pressure of 121 GPa and a temperature of 300 K. This approximates the conditions at the Earth's core-mantle boundary.
- An earlier version of this page (Hicks, 2021) inadvertently switched the positions of the silicon and magnesium atoms, producing an incorrect structure with the AFLOW label AB3C_oC20_63_a.cf.c. Searches for that structure will redirect here. We apologize for the error.
- The ground state structure of MgSiO_3 is enstatite ($S4_3$).

Base-centered Orthorhombic primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{1}{2}b \hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{1}{2}a \hat{\mathbf{x}} + \frac{1}{2}b \hat{\mathbf{y}} \\ \mathbf{a}_3 &= c \hat{\mathbf{z}}\end{aligned}$$

a b c



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$=$	0	$=$	0	Si I
$\mathbf{B}_2$	$=$	$\frac{1}{2} \mathbf{a}_3$	$=$	$\frac{1}{2} c \hat{\mathbf{z}}$	Si I
$\mathbf{B}_3$	$=$	$-y_2 \mathbf{a}_1 + y_2 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$by_2 \hat{\mathbf{y}} + \frac{1}{4} c \hat{\mathbf{z}}$	Mg I
$\mathbf{B}_4$	$=$	$y_2 \mathbf{a}_1 - y_2 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$-by_2 \hat{\mathbf{y}} + \frac{3}{4} c \hat{\mathbf{z}}$	Mg I
$\mathbf{B}_5$	$=$	$-y_3 \mathbf{a}_1 + y_3 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$by_3 \hat{\mathbf{y}} + \frac{1}{4} c \hat{\mathbf{z}}$	O I
$\mathbf{B}_6$	$=$	$y_3 \mathbf{a}_1 - y_3 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$-by_3 \hat{\mathbf{y}} + \frac{3}{4} c \hat{\mathbf{z}}$	O I
$\mathbf{B}_7$	$=$	$-y_4 \mathbf{a}_1 + y_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$by_4 \hat{\mathbf{y}} + cz_4 \hat{\mathbf{z}}$	O II
$\mathbf{B}_8$	$=$	$y_4 \mathbf{a}_1 - y_4 \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-by_4 \hat{\mathbf{y}} + c(z_4 + \frac{1}{2}) \hat{\mathbf{z}}$	O II
$\mathbf{B}_9$	$=$	$-y_4 \mathbf{a}_1 + y_4 \mathbf{a}_2 - (z_4 - \frac{1}{2}) \mathbf{a}_3$	$=$	$by_4 \hat{\mathbf{y}} - c(z_4 - \frac{1}{2}) \hat{\mathbf{z}}$	O II
$\mathbf{B}_{10}$	$=$	$y_4 \mathbf{a}_1 - y_4 \mathbf{a}_2 - z_4 \mathbf{a}_3$	$=$	$-by_4 \hat{\mathbf{y}} - cz_4 \hat{\mathbf{z}}$	O II

References

- [1] M. Murakami, K. Hirose, K. Kawamura, N. Sata, and Y. Ohishi, *Post-Perovskite Phase Transition in MgSiO_3* , *Science* **304**, 855–858 (2005), doi:10.1126/science.1095932.
- [2] D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, *Comput. Mater. Sci.* **199**, 110450 (2021), doi:10.1016/j.commatsci.2021.110450.

First cited in

D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, *Comput. Mater. Sci.* **161**, S1 (2019). doi: 10.1016/j.commatsci.2018.10.043