

AuCsCl₃ (*K*7₆) Structure: AB3C_tI20_139_ab_ah_d-001


This structure previously used the label(s) AB3C_tI20_139_ab_ah_d. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/QC4Q>

https://aflow.org/prototype-encyclopedia/AB3C_tI20_139_ab_ah_d-001




Prototype	AuCl ₃ Cs
AFLOW prototype label	AB3C_tI20_139_ab_ah_d-001
<i>Strukturbericht</i> designation	<i>K</i> 7 ₆
ICSD	26161
CCDC	1601595
Pearson symbol	tI20
Space group number	139
Space group symbol	<i>I</i> 4/ <i>mmm</i>
AFLOW prototype command	<code>aflow --proto=AB3C_tI20_139_ab_ah_d-001 --params=a, c/a, z₄, x₅</code>

Other compounds with this structure

AgAuCs₂Cl₆

Body-centered Tetragonal primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= -\frac{1}{2}a\hat{\mathbf{x}} + \frac{1}{2}a\hat{\mathbf{y}} + \frac{1}{2}c\hat{\mathbf{z}} \\ \mathbf{a}_2 &= \frac{1}{2}a\hat{\mathbf{x}} - \frac{1}{2}a\hat{\mathbf{y}} + \frac{1}{2}c\hat{\mathbf{z}} \\ \mathbf{a}_3 &= \frac{1}{2}a\hat{\mathbf{x}} + \frac{1}{2}a\hat{\mathbf{y}} - \frac{1}{2}c\hat{\mathbf{z}}\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	=	0	=	0	(2a) Au I
$\mathbf{B}_2$	=	$\frac{1}{2}\mathbf{a}_1 + \frac{1}{2}\mathbf{a}_2$	=	$\frac{1}{2}c\hat{\mathbf{z}}$	(2b) Au II
$\mathbf{B}_3$	=	$\frac{3}{4}\mathbf{a}_1 + \frac{1}{4}\mathbf{a}_2 + \frac{1}{2}\mathbf{a}_3$	=	$\frac{1}{2}a\hat{\mathbf{y}} + \frac{1}{4}c\hat{\mathbf{z}}$	(4d) Cs I
$\mathbf{B}_4$	=	$\frac{1}{4}\mathbf{a}_1 + \frac{3}{4}\mathbf{a}_2 + \frac{1}{2}\mathbf{a}_3$	=	$\frac{1}{2}a\hat{\mathbf{x}} + \frac{1}{4}c\hat{\mathbf{z}}$	(4d) Cs I
$\mathbf{B}_5$	=	$z_4\mathbf{a}_1 + z_4\mathbf{a}_2$	=	$cz_4\hat{\mathbf{z}}$	(4e) Cl I
$\mathbf{B}_6$	=	$-z_4\mathbf{a}_1 - z_4\mathbf{a}_2$	=	$-cz_4\hat{\mathbf{z}}$	(4e) Cl I
$\mathbf{B}_7$	=	$x_5\mathbf{a}_1 + x_5\mathbf{a}_2 + 2x_5\mathbf{a}_3$	=	$ax_5\hat{\mathbf{x}} + ax_5\hat{\mathbf{y}}$	(8h) Cl II
$\mathbf{B}_8$	=	$-x_5\mathbf{a}_1 - x_5\mathbf{a}_2 - 2x_5\mathbf{a}_3$	=	$-ax_5\hat{\mathbf{x}} - ax_5\hat{\mathbf{y}}$	(8h) Cl II
$\mathbf{B}_9$	=	$x_5\mathbf{a}_1 - x_5\mathbf{a}_2$	=	$-ax_5\hat{\mathbf{x}} + ax_5\hat{\mathbf{y}}$	(8h) Cl II
$\mathbf{B}_{10}$	=	$-x_5\mathbf{a}_1 + x_5\mathbf{a}_2$	=	$ax_5\hat{\mathbf{x}} - ax_5\hat{\mathbf{y}}$	(8h) Cl II

References

- [1] N. Elliott and L. Pauling, *The Crystal Structure of Cesium Aurous Auric Chloride, Cs₂AuAuCl₆, and Cesium Argentous Auric Chloride, Cs₂AgAuCl₆*, J. Am. Chem. Soc. **60**, 1846–1851 (1938), doi:10.1021/ja01275a037.

Found in

- [1] R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

First cited in

D. Hicks, M. J. Mehl, M. Esters, C. Osos, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.