

Re₃N Structure:

AB3_hP4_187_a_bh-001


This structure previously used the label(s) **AB3_hP4_187_e_fh**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/6BD5>

https://aflow.org/prototype-encyclopedia/AB3_hP4_187_a_bh-001




Prototype	NRe ₃
AFLOW prototype label	AB3_hP4_187_a_bh-001
ICSD	169884
CCDC	1685581
Pearson symbol	hP4
Space group number	187
Space group symbol	$P\bar{6}m2$
AFLOW prototype command	<code>aflow --proto=AB3_hP4_187_a_bh-001</code> <code>--params=a, c/a, z₃</code>

- The reference presents both experimental findings and the results of density functional theory calculations. We obtain our data from the density functional theory calculations at equilibrium ($P = 0$), which are consistent with the lattice constants found experimentally.

Hexagonal primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= \frac{1}{2}a\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a\hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{1}{2}a\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a\hat{\mathbf{y}} \\ \mathbf{a}_3 &= c\hat{\mathbf{z}}\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$=$	0	$=$	0	(1a) N I
$\mathbf{B}_2$	$=$	$\frac{1}{2}\mathbf{a}_3$	$=$	$\frac{1}{2}c\hat{\mathbf{z}}$	(1b) Re I
$\mathbf{B}_3$	$=$	$\frac{1}{3}\mathbf{a}_1 + \frac{2}{3}\mathbf{a}_2 + z_3\mathbf{a}_3$	$=$	$\frac{1}{2}a\hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a\hat{\mathbf{y}} + cz_3\hat{\mathbf{z}}$	(2h) Re II
$\mathbf{B}_4$	$=$	$\frac{1}{3}\mathbf{a}_1 + \frac{2}{3}\mathbf{a}_2 - z_3\mathbf{a}_3$	$=$	$\frac{1}{2}a\hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a\hat{\mathbf{y}} - cz_3\hat{\mathbf{z}}$	(2h) Re II

References

- [1] A. Friedrich, B. Winkler, L. Bayarjargal, W. Morgenroth, E. A. Juarez-Arellano, V. Milman, K. Refson, M. Kunz, and K. Chen, *Novel Rhenium Nitrides*, Phys. Rev. Lett. **105**, 085504 (2010), doi:10.1103/PhysRevLett.105.085504. August.

First cited in

D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, Comput. Mater. Sci. **161**, S1 (2019). doi: 10.1016/j.commatsci.2018.10.043