

CaCu₄P₂ Structure: AB4C2_hR7_166_a_2c_c-001


This structure previously used the label(s) **AB4C2_hR7_166_a_2c_c**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettl, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/SFS1>

https://aflow.org/prototype-encyclopedia/AB4C2_hR7_166_a_2c_c-001



Prototype

CaCu₄P₂

AFLOW prototype label

AB4C2_hR7_166_a_2c_c-001

ICSD

23251

CCDC

1599383


Pearson symbol	hR7
Space group number	166
Space group symbol	$R\bar{3}m$
AFLOW prototype command	aflow --proto=AB4C2_hR7_166_a_2c_c-001 --params= $a, c/a, x_2, x_3, x_4$

Other compounds with this structure

BaAg₄As₂, CaAg₄As₂, EuAg₄As₂, EuAg₄Sb₂, SrAg₄As₂, SrAg₄Sb₂, ZrLi₄Ge₂

Rhombohedral primitive vectors

$$\begin{aligned}
\mathbf{a}_1 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} + \frac{1}{3}c \hat{\mathbf{z}} \\
\mathbf{a}_2 &= \frac{1}{\sqrt{3}}a \hat{\mathbf{y}} + \frac{1}{3}c \hat{\mathbf{z}} \\
\mathbf{a}_3 &= -\frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} + \frac{1}{3}c \hat{\mathbf{z}}
\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	=	0	=	0	(1a) Ca I
$\mathbf{B}_2$	=	$x_2 \mathbf{a}_1 + x_2 \mathbf{a}_2 + x_2 \mathbf{a}_3$	=	$cx_2 \hat{\mathbf{z}}$	(2c) Cu I
$\mathbf{B}_3$	=	$-x_2 \mathbf{a}_1 - x_2 \mathbf{a}_2 - x_2 \mathbf{a}_3$	=	$-cx_2 \hat{\mathbf{z}}$	(2c) Cu I
$\mathbf{B}_4$	=	$x_3 \mathbf{a}_1 + x_3 \mathbf{a}_2 + x_3 \mathbf{a}_3$	=	$cx_3 \hat{\mathbf{z}}$	(2c) Cu II
$\mathbf{B}_5$	=	$-x_3 \mathbf{a}_1 - x_3 \mathbf{a}_2 - x_3 \mathbf{a}_3$	=	$-cx_3 \hat{\mathbf{z}}$	(2c) Cu II
$\mathbf{B}_6$	=	$x_4 \mathbf{a}_1 + x_4 \mathbf{a}_2 + x_4 \mathbf{a}_3$	=	$cx_4 \hat{\mathbf{z}}$	(2c) P I
$\mathbf{B}_7$	=	$-x_4 \mathbf{a}_1 - x_4 \mathbf{a}_2 - x_4 \mathbf{a}_3$	=	$-cx_4 \hat{\mathbf{z}}$	(2c) P I

References

- [1] A. Mewis, *Darstellung und Struktur der Verbindung CaCu₄P₂*, Z. Naturforsch. B **35**, 942–945 (1980), doi:10.1515/znb-1980-0802.

First cited in

D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.