

# Room Temperature NbTe<sub>4</sub> Structure: AB4\_tP10\_124\_a\_m-001


This structure previously used the label(s) **AB4\_tP10\_124\_a\_m**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettl, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/XFHX>

[https://aflow.org/prototype-encyclopedia/AB4\\_tP10\\_124\\_a\\_m-001](https://aflow.org/prototype-encyclopedia/AB4_tP10_124_a_m-001)



|                         |                                                                                                   |
|-------------------------|---------------------------------------------------------------------------------------------------|
| Prototype               | NbTe <sub>4</sub>                                                                                 |
| AFLOW prototype label   | AB4_tP10_124_a_m-001                                                                              |
| ICSD                    | 43282                                                                                             |
| CCDC                    | 1612799                                                                                           |
| Pearson symbol          | tP10                                                                                              |
| Space group number      | 124                                                                                               |
| Space group symbol      | $P4/mcc$                                                                                          |
| AFLOW prototype command | <code>aflow --proto=AB4_tP10_124_a_m-001<br/>--params=a, c/a, x<sub>2</sub>, y<sub>2</sub></code> |

## Other compounds with this structure

TaTe<sub>4</sub>

- This is the room-temperature phase of NbTe<sub>4</sub>. Above 520°C it transforms into a non-centrosymmetric structure.


---

## Simple Tetragonal primitive vectors

$$\mathbf{a}_1 = a \hat{\mathbf{x}}$$

$$\mathbf{a}_2 = a \hat{\mathbf{y}}$$

$$\mathbf{a}_3 = c \hat{\mathbf{z}}$$



---

## Basis vectors

|                   | Lattice coordinates                                                 |     | Cartesian coordinates                                                             | Wyckoff position | Atom type |
|-------------------|---------------------------------------------------------------------|-----|-----------------------------------------------------------------------------------|------------------|-----------|
| $\mathbf{B}_1$    | $= \frac{1}{4} \mathbf{a}_3$                                        | $=$ | $\frac{1}{4} c \hat{\mathbf{z}}$                                                  | (2a)             | Nb I      |
| $\mathbf{B}_2$    | $= \frac{3}{4} \mathbf{a}_3$                                        | $=$ | $\frac{3}{4} c \hat{\mathbf{z}}$                                                  | (2a)             | Nb I      |
| $\mathbf{B}_3$    | $= x_2 \mathbf{a}_1 + y_2 \mathbf{a}_2$                             | $=$ | $ax_2 \hat{\mathbf{x}} + ay_2 \hat{\mathbf{y}}$                                   | (8m)             | Te I      |
| $\mathbf{B}_4$    | $= -x_2 \mathbf{a}_1 - y_2 \mathbf{a}_2$                            | $=$ | $-ax_2 \hat{\mathbf{x}} - ay_2 \hat{\mathbf{y}}$                                  | (8m)             | Te I      |
| $\mathbf{B}_5$    | $= -y_2 \mathbf{a}_1 + x_2 \mathbf{a}_2$                            | $=$ | $-ay_2 \hat{\mathbf{x}} + ax_2 \hat{\mathbf{y}}$                                  | (8m)             | Te I      |
| $\mathbf{B}_6$    | $= y_2 \mathbf{a}_1 - x_2 \mathbf{a}_2$                             | $=$ | $ay_2 \hat{\mathbf{x}} - ax_2 \hat{\mathbf{y}}$                                   | (8m)             | Te I      |
| $\mathbf{B}_7$    | $= -x_2 \mathbf{a}_1 + y_2 \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$ | $=$ | $-ax_2 \hat{\mathbf{x}} + ay_2 \hat{\mathbf{y}} + \frac{1}{2} c \hat{\mathbf{z}}$ | (8m)             | Te I      |
| $\mathbf{B}_8$    | $= x_2 \mathbf{a}_1 - y_2 \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$  | $=$ | $ax_2 \hat{\mathbf{x}} - ay_2 \hat{\mathbf{y}} + \frac{1}{2} c \hat{\mathbf{z}}$  | (8m)             | Te I      |
| $\mathbf{B}_9$    | $= y_2 \mathbf{a}_1 + x_2 \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$  | $=$ | $ay_2 \hat{\mathbf{x}} + ax_2 \hat{\mathbf{y}} + \frac{1}{2} c \hat{\mathbf{z}}$  | (8m)             | Te I      |
| $\mathbf{B}_{10}$ | $= -y_2 \mathbf{a}_1 - x_2 \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$ | $=$ | $-ay_2 \hat{\mathbf{x}} - ax_2 \hat{\mathbf{y}} + \frac{1}{2} c \hat{\mathbf{z}}$ | (8m)             | Te I      |

## References

- [1] K. Selte and A. Kjekshus, *On the Crystal Structure of NbTe<sub>4</sub>*, Acta Chem. Scand. **18**, 690–696 (1964), doi:10.3891/acta.chem.scand.18-0690.

## Found in

- [1] P. Villars and K. Cenzual, *Pearson's Crystal Data – Crystal Structure Database for Inorganic Compounds* (2013). ASM International.

## First cited in

D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, Comput. Mater. Sci. **161**, S1 (2019). doi: 10.1016/j.commatsci.2018.10.043