

Ta₂NiS₅ Structure:

AB5C2_oC32_63_c_c2f_f-004


This structure previously used the label(s) **AB5C2_oC32_63_c_c2f_f**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Osos, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/FETU>

https://aflow.org/prototype-encyclopedia/AB5C2_oC32_63_c_c2f_f-004




Prototype	NiS ₅ Ta ₂
AFLOW prototype label	AB5C2_oC32_63_c_c2f_f-004
ICSD	61147
CCDC	1624688
Pearson symbol	oC32
Space group number	63
Space group symbol	<i>Cmcm</i>
AFLOW prototype command	<code>aflow --proto=AB5C2_oC32_63_c_c2f_f-004</code> <code>--params=a, b/a, c/a, y₁, y₂, y₃, z₃, y₄, z₄, y₅, z₅</code>

Other compounds with this structure

Ta₂NiSe₅ (above 328K)

Base-centered Orthorhombic primitive vectors

$$\begin{aligned} \mathbf{a}_1 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{1}{2}b \hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{1}{2}a \hat{\mathbf{x}} + \frac{1}{2}b \hat{\mathbf{y}} \\ \mathbf{a}_3 &= c \hat{\mathbf{z}} \end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$= -y_1 \mathbf{a}_1 + y_1 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$by_1 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(4c)	Ni I
$\mathbf{B}_2$	$= y_1 \mathbf{a}_1 - y_1 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$-by_1 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(4c)	Ni I
$\mathbf{B}_3$	$= -y_2 \mathbf{a}_1 + y_2 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$by_2 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(4c)	S I
$\mathbf{B}_4$	$= y_2 \mathbf{a}_1 - y_2 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$-by_2 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(4c)	S I
$\mathbf{B}_5$	$= -y_3 \mathbf{a}_1 + y_3 \mathbf{a}_2 + z_3 \mathbf{a}_3$	$=$	$by_3 \hat{\mathbf{y}} + cz_3 \hat{\mathbf{z}}$	(8f)	S II
$\mathbf{B}_6$	$= y_3 \mathbf{a}_1 - y_3 \mathbf{a}_2 + (z_3 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-by_3 \hat{\mathbf{y}} + c(z_3 + \frac{1}{2}) \hat{\mathbf{z}}$	(8f)	S II
$\mathbf{B}_7$	$= -y_3 \mathbf{a}_1 + y_3 \mathbf{a}_2 - (z_3 - \frac{1}{2}) \mathbf{a}_3$	$=$	$by_3 \hat{\mathbf{y}} - c(z_3 - \frac{1}{2}) \hat{\mathbf{z}}$	(8f)	S II
$\mathbf{B}_8$	$= y_3 \mathbf{a}_1 - y_3 \mathbf{a}_2 - z_3 \mathbf{a}_3$	$=$	$-by_3 \hat{\mathbf{y}} - cz_3 \hat{\mathbf{z}}$	(8f)	S II
$\mathbf{B}_9$	$= -y_4 \mathbf{a}_1 + y_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$by_4 \hat{\mathbf{y}} + cz_4 \hat{\mathbf{z}}$	(8f)	S III
$\mathbf{B}_{10}$	$= y_4 \mathbf{a}_1 - y_4 \mathbf{a}_2 + (z_4 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-by_4 \hat{\mathbf{y}} + c(z_4 + \frac{1}{2}) \hat{\mathbf{z}}$	(8f)	S III
$\mathbf{B}_{11}$	$= -y_4 \mathbf{a}_1 + y_4 \mathbf{a}_2 - (z_4 - \frac{1}{2}) \mathbf{a}_3$	$=$	$by_4 \hat{\mathbf{y}} - c(z_4 - \frac{1}{2}) \hat{\mathbf{z}}$	(8f)	S III
$\mathbf{B}_{12}$	$= y_4 \mathbf{a}_1 - y_4 \mathbf{a}_2 - z_4 \mathbf{a}_3$	$=$	$-by_4 \hat{\mathbf{y}} - cz_4 \hat{\mathbf{z}}$	(8f)	S III
$\mathbf{B}_{13}$	$= -y_5 \mathbf{a}_1 + y_5 \mathbf{a}_2 + z_5 \mathbf{a}_3$	$=$	$by_5 \hat{\mathbf{y}} + cz_5 \hat{\mathbf{z}}$	(8f)	Ta I
$\mathbf{B}_{14}$	$= y_5 \mathbf{a}_1 - y_5 \mathbf{a}_2 + (z_5 + \frac{1}{2}) \mathbf{a}_3$	$=$	$-by_5 \hat{\mathbf{y}} + c(z_5 + \frac{1}{2}) \hat{\mathbf{z}}$	(8f)	Ta I
$\mathbf{B}_{15}$	$= -y_5 \mathbf{a}_1 + y_5 \mathbf{a}_2 - (z_5 - \frac{1}{2}) \mathbf{a}_3$	$=$	$by_5 \hat{\mathbf{y}} - c(z_5 - \frac{1}{2}) \hat{\mathbf{z}}$	(8f)	Ta I
$\mathbf{B}_{16}$	$= y_5 \mathbf{a}_1 - y_5 \mathbf{a}_2 - z_5 \mathbf{a}_3$	$=$	$-by_5 \hat{\mathbf{y}} - cz_5 \hat{\mathbf{z}}$	(8f)	Ta I

References

- [1] S. A. Sunshine and J. A. Ibers, *Structure and physical properties of the new layered ternary chalcogenides tantalum nickel sulfide (Ta₂NiS₅) and tantalum nickel selenide (Ta₂NiSe₅)Ta₂NiS₅*, Inorg. Chem. **24**, 3611–3614 (1985), doi:10.1021/ic00216a027.

Found in

- [1] F. J. D. Salvo, C. H. Chen, R. M. Fleming, J. V. Waszczak, R. G. Dunn, S. A. Sunshine, and J. A. Ibers, *Physical and structural properties of the new layered compounds Ta₂NiS₅ and Ta₂NiSe₅*, J. Less-Common Met. **116**, 51–61 (1986), doi:10.1016/0022-5088(86)90216-X.

First cited in

D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.