

GdSI Structure: ABC_hP12_174_aj_dk_ej-001


This structure previously used the label(s) **ABC_hP12_174_cj_fk_aj**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/4BHM>

https://aflow.org/prototype-encyclopedia/ABC_hP12_174_aj_dk_ej-001



Prototype

GdSI

AFLOW prototype label

ABC_hP12_174_aj_dk_ej-001

ICSD

59203

CCDC

1623067


Pearson symbol	hP12
Space group number	174
Space group symbol	$P\bar{6}$
AFLOW prototype command	aflow --proto=ABC_hP12_174_aj_dk_ej-001 --params= $a, c/a, x_4, y_4, x_5, y_5, x_6, y_6$

Other compounds with this structure

TbSI, DySI

- This is a major revision of the previously published version of this page in (Hicks, 2019), however the structure from that page is nearly identical to the structure found here. We have changed our reference from the original (Dagron, 1969) to the more accessible (Beck, 1986).
- This is a high-pressure phase of GdSI. At ambient pressure it is in the SmSI structure.
- The ICSD entry for this structure is incomplete, leaving out the (1a), (1d), and (1e) sites, apparently because of a misreading of Table 4 in (Beck, 1968).

Hexagonal primitive vectors

$$\begin{aligned}
 \mathbf{a}_1 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a \hat{\mathbf{y}} \\
 \mathbf{a}_2 &= \frac{1}{2}a \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a \hat{\mathbf{y}} \\
 \mathbf{a}_3 &= c \hat{\mathbf{z}}
 \end{aligned}$$


Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$=$	0	$=$	0	(1a) Gd I
$\mathbf{B}_2$	$=$	$\frac{1}{3} \mathbf{a}_1 + \frac{2}{3} \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$\frac{1}{2}a \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} + \frac{1}{2}c \hat{\mathbf{z}}$	(1d) I I
$\mathbf{B}_3$	$=$	$\frac{2}{3} \mathbf{a}_1 + \frac{1}{3} \mathbf{a}_2$	$=$	$\frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a \hat{\mathbf{y}}$	(1e) S I
$\mathbf{B}_4$	$=$	$x_4 \mathbf{a}_1 + y_4 \mathbf{a}_2$	$=$	$\frac{1}{2}a (x_4 + y_4) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a (x_4 - y_4) \hat{\mathbf{y}}$	(3j) Gd II
$\mathbf{B}_5$	$=$	$-y_4 \mathbf{a}_1 + (x_4 - y_4) \mathbf{a}_2$	$=$	$\frac{1}{2}a (x_4 - 2y_4) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a x_4 \hat{\mathbf{y}}$	(3j) Gd II
$\mathbf{B}_6$	$=$	$-(x_4 - y_4) \mathbf{a}_1 - x_4 \mathbf{a}_2$	$=$	$-\frac{1}{2}a (2x_4 - y_4) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a y_4 \hat{\mathbf{y}}$	(3j) Gd II
$\mathbf{B}_7$	$=$	$x_5 \mathbf{a}_1 + y_5 \mathbf{a}_2$	$=$	$\frac{1}{2}a (x_5 + y_5) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a (x_5 - y_5) \hat{\mathbf{y}}$	(3j) S II
$\mathbf{B}_8$	$=$	$-y_5 \mathbf{a}_1 + (x_5 - y_5) \mathbf{a}_2$	$=$	$\frac{1}{2}a (x_5 - 2y_5) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a x_5 \hat{\mathbf{y}}$	(3j) S II
$\mathbf{B}_9$	$=$	$-(x_5 - y_5) \mathbf{a}_1 - x_5 \mathbf{a}_2$	$=$	$-\frac{1}{2}a (2x_5 - y_5) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a y_5 \hat{\mathbf{y}}$	(3j) S II
$\mathbf{B}_{10}$	$=$	$x_6 \mathbf{a}_1 + y_6 \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$\frac{1}{2}a (x_6 + y_6) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a (x_6 - y_6) \hat{\mathbf{y}} + \frac{1}{2}c \hat{\mathbf{z}}$	(3k) I II
$\mathbf{B}_{11}$	$=$	$-y_6 \mathbf{a}_1 + (x_6 - y_6) \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$\frac{1}{2}a (x_6 - 2y_6) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a x_6 \hat{\mathbf{y}} + \frac{1}{2}c \hat{\mathbf{z}}$	(3k) I II
$\mathbf{B}_{12}$	$=$	$-(x_6 - y_6) \mathbf{a}_1 - x_6 \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$-\frac{1}{2}a (2x_6 - y_6) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a y_6 \hat{\mathbf{y}} + \frac{1}{2}c \hat{\mathbf{z}}$	(3k) I II

References

- [1] H. P. Beck and C. Strobel, *Zur Hochdruckpolymorphie der Seltenerdsulfidiodide LnSI*, Z. Anorganische und Allgemeine Chemie **535**, 229–239 (1986), doi:10.1002/zaac.19865350427.

- [2] C. Dagron and F. Thevet, *Répartition des types cristallins dans la série des iodosulfures et fluorosulfures des éléments des terres rares et d'yttrium*, C. R. Hebd. Séances Acad. Sci. C **268**, 1867–1869 (1969).
- [3] D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, Comput. Mater. Sci. **161**, S1–S1011 (2019), doi:10.1016/j.commatsci.2018.10.043.

Found in

- [1] P. Villars and K. Cenzual, *Pearson's Crystal Data – Crystal Structure Database for Inorganic Compounds* (2013). ASM International.

First cited in

D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, Comput. Mater. Sci. **161**, S1 (2019). doi: 10.1016/j.commatsci.2018.10.043