


GdCBr Structure: ABC_mC12_12_i_i_i-003

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/69PJ>

https://aflow.org/prototype-encyclopedia/ABC_mC12_12_i_i_i-003




Prototype	BrCGd
AFLOW prototype label	ABC_mC12_12_i_i_i-003
ICSD	47225
CCDC	1614526
Pearson symbol	mC12
Space group number	12
Space group symbol	$C2/m$
AFLOW prototype command	<code>aflow --proto=ABC_mC12_12_i_i_i-003 --params=a, b/a, c/a, β, x_1, z_1, x_2, z_2, x_3, z_3</code>

Other compounds with this structure

TbCBr, ThCN, YCBr, YCCl, YCI

Base-centered Monoclinic primitive vectors

$$\begin{aligned}
\mathbf{a}_1 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{1}{2}b \hat{\mathbf{y}} \\
\mathbf{a}_2 &= \frac{1}{2}a \hat{\mathbf{x}} + \frac{1}{2}b \hat{\mathbf{y}} \\
\mathbf{a}_3 &= c \cos \beta \hat{\mathbf{x}} + c \sin \beta \hat{\mathbf{z}}
\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$= x_1 \mathbf{a}_1 + x_1 \mathbf{a}_2 + z_1 \mathbf{a}_3$	$=$	$(ax_1 + cz_1 \cos \beta) \hat{\mathbf{x}} + cz_1 \sin \beta \hat{\mathbf{z}}$	(4i)	Br I
$\mathbf{B}_2$	$= -x_1 \mathbf{a}_1 - x_1 \mathbf{a}_2 - z_1 \mathbf{a}_3$	$=$	$-(ax_1 + cz_1 \cos \beta) \hat{\mathbf{x}} - cz_1 \sin \beta \hat{\mathbf{z}}$	(4i)	Br I
$\mathbf{B}_3$	$= x_2 \mathbf{a}_1 + x_2 \mathbf{a}_2 + z_2 \mathbf{a}_3$	$=$	$(ax_2 + cz_2 \cos \beta) \hat{\mathbf{x}} + cz_2 \sin \beta \hat{\mathbf{z}}$	(4i)	C I
$\mathbf{B}_4$	$= -x_2 \mathbf{a}_1 - x_2 \mathbf{a}_2 - z_2 \mathbf{a}_3$	$=$	$-(ax_2 + cz_2 \cos \beta) \hat{\mathbf{x}} - cz_2 \sin \beta \hat{\mathbf{z}}$	(4i)	C I
$\mathbf{B}_5$	$= x_3 \mathbf{a}_1 + x_3 \mathbf{a}_2 + z_3 \mathbf{a}_3$	$=$	$(ax_3 + cz_3 \cos \beta) \hat{\mathbf{x}} + cz_3 \sin \beta \hat{\mathbf{z}}$	(4i)	Gd I
$\mathbf{B}_6$	$= -x_3 \mathbf{a}_1 - x_3 \mathbf{a}_2 - z_3 \mathbf{a}_3$	$=$	$-(ax_3 + cz_3 \cos \beta) \hat{\mathbf{x}} - cz_3 \sin \beta \hat{\mathbf{z}}$	(4i)	Gd I

References

- [1] U. Schwanitz-Schüller and A. Simon, *New Gadolinium Carbide Bromides: $Gd_2C_2Br_2$ and Gd_2CBr_2* , Z. Naturforsch. B **40**, 710–716 (1985), doi:10.1515/znb-1985-0602.

Found in

- [1] A. Simon, *Empty, Filled, and Condensed Metal Clusters*, J. Solid State Chem. **57**, 2–16 (1985), doi:10.1016/S0022-4596(85)80055-4.
- [2] R. W. Henn, R. K. Kremer, and A. Simon, *Magnetic Susceptibility Investigations on the Layered Superconductors $Y_2C_2Br_2:RE$ ($RE = Gd, Dy, Er$)*, J. Supercond. Nov. Magn. **13**, 471–477 (2000), doi:10.1023/A:1007771529474.

First cited in

H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.