

Troilite (FeS) Structure: AB_hP24_190_i_afh-001


This structure previously used the label(s) **AB_hP24_190_i_afh**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/6ZXP>

https://aflow.org/prototype-encyclopedia/AB_hP24_190_i_afh-001



Prototype

FeS


AFLOW prototype label

AB_hP24_190_i_afh-001

Mineral name	troilite
ICSD	633296
CCDC	2137745
Pearson symbol	hP24
Space group number	190
Space group symbol	$P\bar{6}2c$
AFLOW prototype command	aflow --proto=AB_hP24_190_i_afh-001 --params= $a, c/a, z_2, x_3, y_3, x_4, y_4, z_4$

Hexagonal primitive vectors

$$\begin{aligned}
\mathbf{a}_1 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a \hat{\mathbf{y}} \\
\mathbf{a}_2 &= \frac{1}{2}a \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a \hat{\mathbf{y}} \\
\mathbf{a}_3 &= c \hat{\mathbf{z}}
\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$= 0$	$=$	0	(2a)	S I
$\mathbf{B}_2$	$= \frac{1}{2} \mathbf{a}_3$	$=$	$\frac{1}{2}c \hat{\mathbf{z}}$	(2a)	S I
$\mathbf{B}_3$	$= \frac{1}{3} \mathbf{a}_1 + \frac{2}{3} \mathbf{a}_2 + z_2 \mathbf{a}_3$	$=$	$\frac{1}{2}a \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} + cz_2 \hat{\mathbf{z}}$	(4f)	S II
$\mathbf{B}_4$	$= \frac{1}{3} \mathbf{a}_1 + \frac{2}{3} \mathbf{a}_2 - (z_2 - \frac{1}{2}) \mathbf{a}_3$	$=$	$\frac{1}{2}a \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} - c(z_2 - \frac{1}{2}) \hat{\mathbf{z}}$	(4f)	S II
$\mathbf{B}_5$	$= \frac{2}{3} \mathbf{a}_1 + \frac{1}{3} \mathbf{a}_2 - z_2 \mathbf{a}_3$	$=$	$\frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} - cz_2 \hat{\mathbf{z}}$	(4f)	S II
$\mathbf{B}_6$	$= \frac{2}{3} \mathbf{a}_1 + \frac{1}{3} \mathbf{a}_2 + (z_2 + \frac{1}{2}) \mathbf{a}_3$	$=$	$\frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} + c(z_2 + \frac{1}{2}) \hat{\mathbf{z}}$	(4f)	S II
$\mathbf{B}_7$	$= x_3 \mathbf{a}_1 + y_3 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a(x_3 + y_3) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a(x_3 - y_3) \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(6h)	S III
$\mathbf{B}_8$	$= -y_3 \mathbf{a}_1 + (x_3 - y_3) \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a(x_3 - 2y_3) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_3 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(6h)	S III
$\mathbf{B}_9$	$= -(x_3 - y_3) \mathbf{a}_1 - x_3 \mathbf{a}_2 + \frac{1}{4} \mathbf{a}_3$	$=$	$-\frac{1}{2}a(2x_3 - y_3) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ay_3 \hat{\mathbf{y}} + \frac{1}{4}c \hat{\mathbf{z}}$	(6h)	S III
$\mathbf{B}_{10}$	$= y_3 \mathbf{a}_1 + x_3 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a(x_3 + y_3) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a(x_3 - y_3) \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(6h)	S III
$\mathbf{B}_{11}$	$= (x_3 - y_3) \mathbf{a}_1 - y_3 \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$\frac{1}{2}a(x_3 - 2y_3) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ax_3 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(6h)	S III
$\mathbf{B}_{12}$	$= -x_3 \mathbf{a}_1 - (x_3 - y_3) \mathbf{a}_2 + \frac{3}{4} \mathbf{a}_3$	$=$	$-\frac{1}{2}a(2x_3 - y_3) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ay_3 \hat{\mathbf{y}} + \frac{3}{4}c \hat{\mathbf{z}}$	(6h)	S III
$\mathbf{B}_{13}$	$= x_4 \mathbf{a}_1 + y_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$\frac{1}{2}a(x_4 + y_4) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a(x_4 - y_4) \hat{\mathbf{y}} + cz_4 \hat{\mathbf{z}}$	(12i)	Fe I
$\mathbf{B}_{14}$	$= -y_4 \mathbf{a}_1 + (x_4 - y_4) \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$\frac{1}{2}a(x_4 - 2y_4) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_4 \hat{\mathbf{y}} + cz_4 \hat{\mathbf{z}}$	(12i)	Fe I
$\mathbf{B}_{15}$	$= -(x_4 - y_4) \mathbf{a}_1 - x_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$-\frac{1}{2}a(2x_4 - y_4) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ay_4 \hat{\mathbf{y}} + cz_4 \hat{\mathbf{z}}$	(12i)	Fe I
$\mathbf{B}_{16}$	$= x_4 \mathbf{a}_1 + y_4 \mathbf{a}_2 - (z_4 - \frac{1}{2}) \mathbf{a}_3$	$=$	$\frac{1}{2}a(x_4 + y_4) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a(x_4 - y_4) \hat{\mathbf{y}} - c(z_4 - \frac{1}{2}) \hat{\mathbf{z}}$	(12i)	Fe I
$\mathbf{B}_{17}$	$= -y_4 \mathbf{a}_1 + (x_4 - y_4) \mathbf{a}_2 - (z_4 - \frac{1}{2}) \mathbf{a}_3$	$=$	$\frac{1}{2}a(x_4 - 2y_4) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_4 \hat{\mathbf{y}} - c(z_4 - \frac{1}{2}) \hat{\mathbf{z}}$	(12i)	Fe I

$$\begin{aligned}
\mathbf{B}_{18} &= - (x_4 - y_4) \mathbf{a}_1 - x_4 \mathbf{a}_2 - \left(z_4 - \frac{1}{2}\right) \mathbf{a}_3 &= -\frac{1}{2}a (2x_4 - y_4) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ay_4 \hat{\mathbf{y}} - c \left(z_4 - \frac{1}{2}\right) \hat{\mathbf{z}} &(12i) &\text{Fe I} \\
\mathbf{B}_{19} &= y_4 \mathbf{a}_1 + x_4 \mathbf{a}_2 - z_4 \mathbf{a}_3 &= \frac{1}{2}a (x_4 + y_4) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a (x_4 - y_4) \hat{\mathbf{y}} - cz_4 \hat{\mathbf{z}} &(12i) &\text{Fe I} \\
\mathbf{B}_{20} &= (x_4 - y_4) \mathbf{a}_1 - y_4 \mathbf{a}_2 - z_4 \mathbf{a}_3 &= \frac{1}{2}a (x_4 - 2y_4) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ax_4 \hat{\mathbf{y}} - cz_4 \hat{\mathbf{z}} &(12i) &\text{Fe I} \\
\mathbf{B}_{21} &= -x_4 \mathbf{a}_1 - (x_4 - y_4) \mathbf{a}_2 - z_4 \mathbf{a}_3 &= -\frac{1}{2}a (2x_4 - y_4) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ay_4 \hat{\mathbf{y}} - cz_4 \hat{\mathbf{z}} &(12i) &\text{Fe I} \\
\mathbf{B}_{22} &= y_4 \mathbf{a}_1 + x_4 \mathbf{a}_2 + \left(z_4 + \frac{1}{2}\right) \mathbf{a}_3 &= \frac{1}{2}a (x_4 + y_4) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a (x_4 - y_4) \hat{\mathbf{y}} + c \left(z_4 + \frac{1}{2}\right) \hat{\mathbf{z}} &(12i) &\text{Fe I} \\
\mathbf{B}_{23} &= (x_4 - y_4) \mathbf{a}_1 - y_4 \mathbf{a}_2 + \left(z_4 + \frac{1}{2}\right) \mathbf{a}_3 &= \frac{1}{2}a (x_4 - 2y_4) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ax_4 \hat{\mathbf{y}} + c \left(z_4 + \frac{1}{2}\right) \hat{\mathbf{z}} &(12i) &\text{Fe I} \\
\mathbf{B}_{24} &= -x_4 \mathbf{a}_1 - (x_4 - y_4) \mathbf{a}_2 + \left(z_4 + \frac{1}{2}\right) \mathbf{a}_3 &= -\frac{1}{2}a (2x_4 - y_4) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ay_4 \hat{\mathbf{y}} + c \left(z_4 + \frac{1}{2}\right) \hat{\mathbf{z}} &(12i) &\text{Fe I}
\end{aligned}$$

References

- [1] N. Morimoto, H. Nakazawa, K. Nishigucmi, and M. Tokonami, *Pyrrhotites: Stoichiometric Compounds with Composition $Fe_{n-1}S_n$ ($n \geq 8$)*, Science **168**, 964–966 (1970), doi:10.1126/science.168.3934.964.

Found in

- [1] P. Villars and K. Cenzual, *Pearson's Crystal Data – Crystal Structure Database for Inorganic Compounds* (2013). ASM International.

First cited in

D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, Comput. Mater. Sci. **161**, S1 (2019). doi: 10.1016/j.commatsci.2018.10.043