

ZnTe (high-pressure) Structure:

AB_hP6_144_a_a-001


This structure previously used the label(s) **AB_hP6_144_a_a**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/LX4R>

https://aflow.org/prototype-encyclopedia/AB_hP6_144_a_a-001




Prototype	TeZn
AFLOW prototype label	AB_hP6_144_a_a-001
ICSD	80076
CCDC	1640304
Pearson symbol	hP6
Space group number	144
Space group symbol	$P3_1$
AFLOW prototype command	<code>aflow --proto=AB_hP6_144_a_a-001</code> <code>--params=$a, c/a, x_1, y_1, z_1, x_2, y_2, z_2$</code>

- This structure was determined at 11.5 GPa.
- This structure can also be found in the enantiomorphic space group $P3_2$ #145.

Trigonal (Hexagonal) primitive vectors

$$\begin{aligned}\mathbf{a}_1 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a \hat{\mathbf{y}} \\ \mathbf{a}_2 &= \frac{1}{2}a \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a \hat{\mathbf{y}} \\ \mathbf{a}_3 &= c \hat{\mathbf{z}}\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$= x_1 \mathbf{a}_1 + y_1 \mathbf{a}_2 + z_1 \mathbf{a}_3$	$=$	$\frac{1}{2}a (x_1 + y_1) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a (x_1 - y_1) \hat{\mathbf{y}} + cz_1 \hat{\mathbf{z}}$	(3a)	Te I
$\mathbf{B}_2$	$= -y_1 \mathbf{a}_1 + (x_1 - y_1) \mathbf{a}_2 + (z_1 + \frac{1}{3}) \mathbf{a}_3$	$=$	$\frac{1}{2}a (x_1 - 2y_1) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_1 \hat{\mathbf{y}} + c(z_1 + \frac{1}{3}) \hat{\mathbf{z}}$	(3a)	Te I
$\mathbf{B}_3$	$= -(x_1 - y_1) \mathbf{a}_1 - x_1 \mathbf{a}_2 + (z_1 + \frac{2}{3}) \mathbf{a}_3$	$=$	$-\frac{1}{2}a (2x_1 - y_1) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ay_1 \hat{\mathbf{y}} + \frac{1}{3}c (3z_1 + 2) \hat{\mathbf{z}}$	(3a)	Te I
$\mathbf{B}_4$	$= x_2 \mathbf{a}_1 + y_2 \mathbf{a}_2 + z_2 \mathbf{a}_3$	$=$	$\frac{1}{2}a (x_2 + y_2) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a (x_2 - y_2) \hat{\mathbf{y}} + cz_2 \hat{\mathbf{z}}$	(3a)	Zn I
$\mathbf{B}_5$	$= -y_2 \mathbf{a}_1 + (x_2 - y_2) \mathbf{a}_2 + (z_2 + \frac{1}{3}) \mathbf{a}_3$	$=$	$\frac{1}{2}a (x_2 - 2y_2) \hat{\mathbf{x}} + \frac{\sqrt{3}}{2}ax_2 \hat{\mathbf{y}} + c(z_2 + \frac{1}{3}) \hat{\mathbf{z}}$	(3a)	Zn I
$\mathbf{B}_6$	$= -(x_2 - y_2) \mathbf{a}_1 - x_2 \mathbf{a}_2 + (z_2 + \frac{2}{3}) \mathbf{a}_3$	$=$	$-\frac{1}{2}a (2x_2 - y_2) \hat{\mathbf{x}} - \frac{\sqrt{3}}{2}ay_2 \hat{\mathbf{y}} + \frac{1}{3}c (3z_2 + 2) \hat{\mathbf{z}}$	(3a)	Zn I

References

- [1] K. Kusaba and D. J. Weidner, *Structure of high pressure phase I in ZnTe*, AIP Conference Proceedings **309**, 553 (1994), doi:10.1063/1.46096.

Found in

- [1] P. Villars and K. Cenzual, *Pearson's Crystal Data – Crystal Structure Database for Inorganic Compounds* (2013). ASM International.

First cited in

D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, Comput. Mater. Sci. **161**, S1 (2019). doi: 10.1016/j.commatsci.2018.10.043