

PdAl Structure: AB_hR26_148_a2f_b2f-001


This structure previously used the label(s) **AB_hR26_148_b2f_a2f**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettl, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/5EQ4>

https://aflow.org/prototype-encyclopedia/AB_hR26_148_a2f_b2f-001




Prototype	AlPd
AFLOW prototype label	AB_hR26_148_a2f_b2f-001
ICSD	58112
CCDC	1622141
Pearson symbol	hR26
Space group number	148
Space group symbol	$R\bar{3}$
AFLOW prototype command	aflow --proto=AB_hR26_148_a2f_b2f-001 --params= $a, c/a, x_3, y_3, z_3, x_4, y_4, z_4, x_5, y_5, z_5, x_6, y_6, z_6$

- Hexagonal settings of this structure can be obtained with the option `--hex`.

Rhombohedral primitive vectors

$$\begin{aligned}
\mathbf{a}_1 &= \frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} + \frac{1}{3}c \hat{\mathbf{z}} \\
\mathbf{a}_2 &= \frac{1}{\sqrt{3}}a \hat{\mathbf{y}} + \frac{1}{3}c \hat{\mathbf{z}} \\
\mathbf{a}_3 &= -\frac{1}{2}a \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a \hat{\mathbf{y}} + \frac{1}{3}c \hat{\mathbf{z}}
\end{aligned}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$= 0$	$=$	0	(1a)	Al I
$\mathbf{B}_2$	$= \frac{1}{2} \mathbf{a}_1 + \frac{1}{2} \mathbf{a}_2 + \frac{1}{2} \mathbf{a}_3$	$=$	$\frac{1}{2}c \hat{\mathbf{z}}$	(1b)	Pd I
$\mathbf{B}_3$	$= x_3 \mathbf{a}_1 + y_3 \mathbf{a}_2 + z_3 \mathbf{a}_3$	$=$	$\frac{1}{2}a (x_3 - z_3) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a (x_3 - 2y_3 + z_3) \hat{\mathbf{y}} + \frac{1}{3}c (x_3 + y_3 + z_3) \hat{\mathbf{z}}$	(6f)	Al II
$\mathbf{B}_4$	$= z_3 \mathbf{a}_1 + x_3 \mathbf{a}_2 + y_3 \mathbf{a}_3$	$=$	$-\frac{1}{2}a (y_3 - z_3) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a (2x_3 - y_3 - z_3) \hat{\mathbf{y}} + \frac{1}{3}c (x_3 + y_3 + z_3) \hat{\mathbf{z}}$	(6f)	Al II
$\mathbf{B}_5$	$= y_3 \mathbf{a}_1 + z_3 \mathbf{a}_2 + x_3 \mathbf{a}_3$	$=$	$-\frac{1}{2}a (x_3 - y_3) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a (x_3 + y_3 - 2z_3) \hat{\mathbf{y}} + \frac{1}{3}c (x_3 + y_3 + z_3) \hat{\mathbf{z}}$	(6f)	Al II
$\mathbf{B}_6$	$= -x_3 \mathbf{a}_1 - y_3 \mathbf{a}_2 - z_3 \mathbf{a}_3$	$=$	$-\frac{1}{2}a (x_3 - z_3) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a (x_3 - 2y_3 + z_3) \hat{\mathbf{y}} - \frac{1}{3}c (x_3 + y_3 + z_3) \hat{\mathbf{z}}$	(6f)	Al II
$\mathbf{B}_7$	$= -z_3 \mathbf{a}_1 - x_3 \mathbf{a}_2 - y_3 \mathbf{a}_3$	$=$	$\frac{1}{2}a (y_3 - z_3) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a (2x_3 - y_3 - z_3) \hat{\mathbf{y}} - \frac{1}{3}c (x_3 + y_3 + z_3) \hat{\mathbf{z}}$	(6f)	Al II
$\mathbf{B}_8$	$= -y_3 \mathbf{a}_1 - z_3 \mathbf{a}_2 - x_3 \mathbf{a}_3$	$=$	$\frac{1}{2}a (x_3 - y_3) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a (x_3 + y_3 - 2z_3) \hat{\mathbf{y}} - \frac{1}{3}c (x_3 + y_3 + z_3) \hat{\mathbf{z}}$	(6f)	Al II
$\mathbf{B}_9$	$= x_4 \mathbf{a}_1 + y_4 \mathbf{a}_2 + z_4 \mathbf{a}_3$	$=$	$\frac{1}{2}a (x_4 - z_4) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a (x_4 - 2y_4 + z_4) \hat{\mathbf{y}} + \frac{1}{3}c (x_4 + y_4 + z_4) \hat{\mathbf{z}}$	(6f)	Al III
$\mathbf{B}_{10}$	$= z_4 \mathbf{a}_1 + x_4 \mathbf{a}_2 + y_4 \mathbf{a}_3$	$=$	$-\frac{1}{2}a (y_4 - z_4) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a (2x_4 - y_4 - z_4) \hat{\mathbf{y}} + \frac{1}{3}c (x_4 + y_4 + z_4) \hat{\mathbf{z}}$	(6f)	Al III
$\mathbf{B}_{11}$	$= y_4 \mathbf{a}_1 + z_4 \mathbf{a}_2 + x_4 \mathbf{a}_3$	$=$	$-\frac{1}{2}a (x_4 - y_4) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a (x_4 + y_4 - 2z_4) \hat{\mathbf{y}} + \frac{1}{3}c (x_4 + y_4 + z_4) \hat{\mathbf{z}}$	(6f)	Al III

$$\begin{aligned}
\mathbf{B}_{12} &= -x_4 \mathbf{a}_1 - y_4 \mathbf{a}_2 - z_4 \mathbf{a}_3 &= -\frac{1}{2}a(x_4 - z_4) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a(x_4 - 2y_4 + z_4) \hat{\mathbf{y}} - \frac{1}{3}c(x_4 + y_4 + z_4) \hat{\mathbf{z}} &(6f) &\text{Al III} \\
\mathbf{B}_{13} &= -z_4 \mathbf{a}_1 - x_4 \mathbf{a}_2 - y_4 \mathbf{a}_3 &= \frac{1}{2}a(y_4 - z_4) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a(2x_4 - y_4 - z_4) \hat{\mathbf{y}} - \frac{1}{3}c(x_4 + y_4 + z_4) \hat{\mathbf{z}} &(6f) &\text{Al III} \\
\mathbf{B}_{14} &= -y_4 \mathbf{a}_1 - z_4 \mathbf{a}_2 - x_4 \mathbf{a}_3 &= \frac{1}{2}a(x_4 - y_4) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a(x_4 + y_4 - 2z_4) \hat{\mathbf{y}} - \frac{1}{3}c(x_4 + y_4 + z_4) \hat{\mathbf{z}} &(6f) &\text{Al III} \\
\mathbf{B}_{15} &= x_5 \mathbf{a}_1 + y_5 \mathbf{a}_2 + z_5 \mathbf{a}_3 &= \frac{1}{2}a(x_5 - z_5) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a(x_5 - 2y_5 + z_5) \hat{\mathbf{y}} + \frac{1}{3}c(x_5 + y_5 + z_5) \hat{\mathbf{z}} &(6f) &\text{Pd II} \\
\mathbf{B}_{16} &= z_5 \mathbf{a}_1 + x_5 \mathbf{a}_2 + y_5 \mathbf{a}_3 &= -\frac{1}{2}a(y_5 - z_5) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a(2x_5 - y_5 - z_5) \hat{\mathbf{y}} + \frac{1}{3}c(x_5 + y_5 + z_5) \hat{\mathbf{z}} &(6f) &\text{Pd II} \\
\mathbf{B}_{17} &= y_5 \mathbf{a}_1 + z_5 \mathbf{a}_2 + x_5 \mathbf{a}_3 &= -\frac{1}{2}a(x_5 - y_5) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a(x_5 + y_5 - 2z_5) \hat{\mathbf{y}} + \frac{1}{3}c(x_5 + y_5 + z_5) \hat{\mathbf{z}} &(6f) &\text{Pd II} \\
\mathbf{B}_{18} &= -x_5 \mathbf{a}_1 - y_5 \mathbf{a}_2 - z_5 \mathbf{a}_3 &= -\frac{1}{2}a(x_5 - z_5) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a(x_5 - 2y_5 + z_5) \hat{\mathbf{y}} - \frac{1}{3}c(x_5 + y_5 + z_5) \hat{\mathbf{z}} &(6f) &\text{Pd II} \\
\mathbf{B}_{19} &= -z_5 \mathbf{a}_1 - x_5 \mathbf{a}_2 - y_5 \mathbf{a}_3 &= \frac{1}{2}a(y_5 - z_5) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a(2x_5 - y_5 - z_5) \hat{\mathbf{y}} - \frac{1}{3}c(x_5 + y_5 + z_5) \hat{\mathbf{z}} &(6f) &\text{Pd II} \\
\mathbf{B}_{20} &= -y_5 \mathbf{a}_1 - z_5 \mathbf{a}_2 - x_5 \mathbf{a}_3 &= \frac{1}{2}a(x_5 - y_5) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a(x_5 + y_5 - 2z_5) \hat{\mathbf{y}} - \frac{1}{3}c(x_5 + y_5 + z_5) \hat{\mathbf{z}} &(6f) &\text{Pd II} \\
\mathbf{B}_{21} &= x_6 \mathbf{a}_1 + y_6 \mathbf{a}_2 + z_6 \mathbf{a}_3 &= \frac{1}{2}a(x_6 - z_6) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a(x_6 - 2y_6 + z_6) \hat{\mathbf{y}} + \frac{1}{3}c(x_6 + y_6 + z_6) \hat{\mathbf{z}} &(6f) &\text{Pd III} \\
\mathbf{B}_{22} &= z_6 \mathbf{a}_1 + x_6 \mathbf{a}_2 + y_6 \mathbf{a}_3 &= -\frac{1}{2}a(y_6 - z_6) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a(2x_6 - y_6 - z_6) \hat{\mathbf{y}} + \frac{1}{3}c(x_6 + y_6 + z_6) \hat{\mathbf{z}} &(6f) &\text{Pd III} \\
\mathbf{B}_{23} &= y_6 \mathbf{a}_1 + z_6 \mathbf{a}_2 + x_6 \mathbf{a}_3 &= -\frac{1}{2}a(x_6 - y_6) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a(x_6 + y_6 - 2z_6) \hat{\mathbf{y}} + \frac{1}{3}c(x_6 + y_6 + z_6) \hat{\mathbf{z}} &(6f) &\text{Pd III} \\
\mathbf{B}_{24} &= -x_6 \mathbf{a}_1 - y_6 \mathbf{a}_2 - z_6 \mathbf{a}_3 &= -\frac{1}{2}a(x_6 - z_6) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a(x_6 - 2y_6 + z_6) \hat{\mathbf{y}} - \frac{1}{3}c(x_6 + y_6 + z_6) \hat{\mathbf{z}} &(6f) &\text{Pd III} \\
\mathbf{B}_{25} &= -z_6 \mathbf{a}_1 - x_6 \mathbf{a}_2 - y_6 \mathbf{a}_3 &= \frac{1}{2}a(y_6 - z_6) \hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a(2x_6 - y_6 - z_6) \hat{\mathbf{y}} - \frac{1}{3}c(x_6 + y_6 + z_6) \hat{\mathbf{z}} &(6f) &\text{Pd III} \\
\mathbf{B}_{26} &= -y_6 \mathbf{a}_1 - z_6 \mathbf{a}_2 - x_6 \mathbf{a}_3 &= \frac{1}{2}a(x_6 - y_6) \hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a(x_6 + y_6 - 2z_6) \hat{\mathbf{y}} - \frac{1}{3}c(x_6 + y_6 + z_6) \hat{\mathbf{z}} &(6f) &\text{Pd III}
\end{aligned}$$

References

- [1] T. Matković and K. Schubert, *Kristallstruktur vo PdAl₃*, J. Less-Common Met. **55**, 45–52 (1977), doi:10.1016/0022-5088(77)90258-2.

Found in

- [1] P. Villars, K. Cenzual, J. Daams, R. Gladyshevskii, O. Shcherban, V. Dubenskyy, V. Kuprysyuk, and I. Savesyuk, *Landolt-Börnstein – Group III Condensed Matter* (Springer-Verlag GmbH, Heidelberg, 2010), chap. Structure Types. Part 8: Space Groups (156)P3m1 – (148)R-3 · PdAl rt, doi:10.1007/978-3-540-70892-6_476. Part 8.

First cited in

M. J. Mehl, D. Hicks, C. Toher, O. Levy, R. M. Hanson, G. L. W. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 1*, Comput. Mater. Sci. **136**, S1-828 (2017). doi: 10.1016/j.commatsci.2017.01.017