

Low temperature FeS Structure:

AB_oF8_22_a_c-001


This structure previously used the label(s) **AB_oF8_22_a_c**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettl, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/H691>

https://aflow.org/prototype-encyclopedia/AB_oF8_22_a_c-001



Prototype	FeS
AFLOW prototype label	AB_oF8_22_a_c-001
Pearson symbol	oF8
Space group number	22
Space group symbol	$F222$
AFLOW prototype command	<code>aflow --proto=AB_oF8_22_a_c-001</code> <code>--params=a, b/a, c/a</code>

- This is the stable structure of iron sulfide below 242K. Above that temperature it is in the zincblende ($B3$) structure. (Wintenberger, 1978).
- This data was taken at 81K. We follow (Villars, 2016) and rearrange the axis, as well as reversing the positions of the iron and sulfur atoms.

Face-centered Orthorhombic primitive vectors



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	=	0	=	0	(4a) Fe I
$\mathbf{B}_2$	=	$\frac{1}{4}\mathbf{a}_1 + \frac{1}{4}\mathbf{a}_2 + \frac{1}{4}\mathbf{a}_3$	=	$\frac{1}{4}a\hat{\mathbf{x}} + \frac{1}{4}b\hat{\mathbf{y}} + \frac{1}{4}c\hat{\mathbf{z}}$	(4c) S I

References

[1] M. Wintenberger and J. L. Buevoz, *Structure magnetique du sulfure de fer FeS de type blende*, Solid State Commun. **27**, 511–513 (1978), doi:10.1016/0038-1098(78)90383-6.

Found in

[1] P. Villars, *FeS Crystal Structure* (2016). PAULING FILE in: Inorganic Solid Phases, SpringerMaterials (online database).

First cited in

D. Hicks, M. J. Mehl, E. Gossett, C. Toher, O. Levy, R. M. Hanson, G. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 2*, Comput. Mater. Sci. **161**, S1 (2019). doi: 10.1016/j.commatsci.2018.10.043