

Hexagonal Close Packed (Mg, A3, hcp) Structure: A_hP2_194_c-001


This structure previously used the label(s) **A_hP2_194_c**. Calls to these addresses will be redirected here.

Cite this page as:

- H. Eckert, S. Divilov, M. J. Mehl, D. Hicks, A. C. Zettel, M. Esters, X. Campilongo, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 4*, Comput. Mater. Sci. **240**, 112988 (2024), doi: 10.1016/j.commatsci.2024.112988.
- D. Hicks, M. J. Mehl, M. Esters, C. Oses, O. Levy, G. L. W. Hart, C. Toher, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 3*, Comput. Mater. Sci. **199**, 110450 (2021), doi: 10.1016/j.commatsci.2021.110450.

<https://aflow.org/prototype-encyclopedia/LZW5>

https://aflow.org/prototype-encyclopedia/A_hP2_194_c-001



Prototype	Mg
AFLOW prototype label	A_hP2_194_c-001
<i>Strukturbericht</i> designation	A3
ICSD	608404
CCDC	1743051
Pearson symbol	hP2
Space group number	194
Space group symbol	$P6_3/mmc$
AFLOW prototype command	<code>aflow --proto=A_hP2_194_c-001 --params=a, c/a</code>

Other compounds with this structure

Be, Cd, Co, Dy, Er, ϵ -Fe, Gd, Hf, Ho, Lu, Os, Re, Ru, Sc, Tb, Tc, Ti, Tl, Tm, Y, Zn, Zr


- We use the ‘pure magnesium’ lattice constants from (Batchelder, 1957), but the ICSD entry uses the data for $\text{Mg}_{0.976}\text{Al}_{0.024}$.
-

Hexagonal primitive vectors

$$\mathbf{a}_1 = \frac{1}{2}a\hat{\mathbf{x}} - \frac{\sqrt{3}}{2}a\hat{\mathbf{y}}$$

$$\mathbf{a}_2 = \frac{1}{2}a\hat{\mathbf{x}} + \frac{\sqrt{3}}{2}a\hat{\mathbf{y}}$$

$$\mathbf{a}_3 = c\hat{\mathbf{z}}$$



Basis vectors

	Lattice coordinates		Cartesian coordinates	Wyckoff position	Atom type
$\mathbf{B}_1$	$=$	$\frac{1}{3}\mathbf{a}_1 + \frac{2}{3}\mathbf{a}_2 + \frac{1}{4}\mathbf{a}_3$	$=$	$\frac{1}{2}a\hat{\mathbf{x}} + \frac{\sqrt{3}}{6}a\hat{\mathbf{y}} + \frac{1}{4}c\hat{\mathbf{z}}$	(2c) Mg I
$\mathbf{B}_2$	$=$	$\frac{2}{3}\mathbf{a}_1 + \frac{1}{3}\mathbf{a}_2 + \frac{3}{4}\mathbf{a}_3$	$=$	$\frac{1}{2}a\hat{\mathbf{x}} - \frac{\sqrt{3}}{6}a\hat{\mathbf{y}} + \frac{3}{4}c\hat{\mathbf{z}}$	(2c) Mg I

References

- [1] F. W. von Batchelder and R. F. Rauechle, *Lattice Constants and Brillouin Zone Overlap in Dilute Magnesium Alloys*, Phys. Rev. **105**, 59–61 (1957), doi:10.1103/PhysRev.105.59.

Found in

- [1] R. T. Downs and M. Hall-Wallace, *The American Mineralogist Crystal Structure Database*, Am. Mineral. **88**, 247–250 (2003).

First cited in

M. J. Mehl, D. Hicks, C. Toher, O. Levy, R. M. Hanson, G. L. W. Hart, and S. Curtarolo, *The AFLOW Library of Crystallographic Prototypes: Part 1*, Comput. Mater. Sci. **136**, S1-828 (2017). doi: 10.1016/j.commatsci.2017.01.017